Impurity effects upon the Verwey transition in magnetite

Citation for published version (APA):

Brabers, V. A. M., Walz, F., & Kronmüller, H. (1998). Impurity effects upon the Verwey transition in magnetite. *Physical Review B*, 58(21), 14163-14166. <https://doi.org/10.1103/PhysRevB.58.14163>

DOI:

[10.1103/PhysRevB.58.14163](https://doi.org/10.1103/PhysRevB.58.14163)

Document status and date:

Published: 01/01/1998

Document Version:

Publisher's PDF, also known as Version of Record (includes final page, issue and volume numbers)

Please check the document version of this publication:

- A submitted manuscript is the version of the article upon submission and before peer-review. There can be important differences between the submitted version and the official published version of record. People interested in the research are advised to contact the author for the final version of the publication, or visit the DOI to the publisher's website.
- The final author version and the galley proof are versions of the publication after peer review.
- The final published version features the final layout of the paper including the volume, issue and page numbers.

[Link to publication](#)

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal.

If the publication is distributed under the terms of Article 25fa of the Dutch Copyright Act, indicated by the "Taverne" license above, please follow below link for the End User Agreement:

www.tue.nl/taverne

Take down policy

If you believe that this document breaches copyright please contact us at:

openaccess@tue.nl

providing details and we will investigate your claim.

Impurity effects upon the Verwey transition in magnetite

V. A. M. Brabers

Department of Physics, Eindhoven University of Technology, P.B. 513, 5600 MB Eindhoven, The Netherlands

F. Walz and H. Kronmüller

Max-Planck-Institut für Metallforschung, Heisenbergstrasse 1, D-70569, Stuttgart, Germany

(Received 22 May 1998)

Magnetite single crystals $\text{Fe}_{3-x}M_x\text{O}_4$ doped with $M = \text{Ni}, \text{Co}, \text{Mg}, \text{Al}, \text{Ga},$ and Ti were grown and annealed under a controlled atmosphere to produce homogeneous and oxygen stoichiometric samples. The cation vacancy concentration of the samples was proved to be lower than 10^{-6} by means of magnetic disaccommodation spectroscopy. The Verwey temperature shift as function of the substituent concentration was determined from the temperature dependence of the resistivity. The systematics of the transition temperature shift as function of the concentration and nature of the substituents is indicative that the mechanism of the transition is related to the second-neighbor Coulomb interaction of the cations on the octahedral sites.

[S0163-1829(98)00846-7]

INTRODUCTION

Although magnetite (Fe_3O_4) is one of the most studied magnetic oxides, the investigation of the physical properties of this material is still an intriguing field of research.¹ At room temperature, the crystal structure of Fe_3O_4 is the inverted spinel structure, in which the tetrahedral A sites are occupied by one-third of the Fe ions as Fe^{3+} and the remaining Fe ions are located on the octahedral B sites as mixed-valent Fe ions with an average charge of $2.5+$. Around 125 K, magnetite undergoes a first-order phase transition, which was already in the 1920's and 1930's probed by anomalies in the magnetization,² specific heat,³ and the lattice constant.⁴ Verwey⁵ related this transition to an electronic ordering of Fe^{2+} and Fe^{3+} ions on the B sites, causing a decrease in the electrical conductivity of about two orders of magnitude, which is now known as the Verwey transition.

Irrespective of the more and more refined structure models that have been developed to explain the low-temperature charge ordering in magnetite,⁶⁻¹⁴ some basic statements can be made concerning the driving forces of the ordering mechanisms at low temperatures.

(1) The Verwey transition in magnetite is not primarily induced by magnetic interactions, as follows from the small value of the magnetic anisotropy energy accompanying the magnetoelectric effect,¹⁵ the small change of the saturation magnetization at the transition temperature T_v (Ref. 16), and the absence of anomalies of the magnetic anisotropy constants on passing the critical nonstoichiometry parameter δ_i for $\text{Fe}_{3-\delta}\text{O}_4$, above which the transition disappears.¹⁷

(2) The Verwey transition is exceptional in the sense that the ordering mechanism is related to the Coulomb interactions according to which a transition temperature above 10^4 K would be expected, whereas the real transition still occurs at low temperatures around 125 K. This apparent contradiction was cleared by Anderson¹⁸ by taking into account the particular geometry of the spinel lattice. The octahedral sites in the spinel structure are arranged in tetrahedra B_4 ,

with each site belonging to two adjacent tetrahedra. In this arrangement, short-range order is imposed by the so-called Anderson condition: the charge of the individual tetrahedra must be constant, i.e., two Fe^{2+} and two Fe^{3+} ions per tetrahedron. If the interactions leading to the Verwey transition would be restricted to nearest-neighbor pairs, identical energies would be expected for all configurations fulfilling Anderson's condition and no transition should occur. However, there is a transition, which means that the driving mechanism of the transition is achieved by next-nearest-neighbor Coulomb interactions.

(3) The discussion as to whether this short-range order persists^{19,19(b)} above the Verwey transition has been decided positively by recent photoemission spectroscopy experiments on the (100) surface of Fe_3O_4 .^{20,21}

(4) Since the Verwey ordering mechanism originates from the Coulomb interactions, the effects of substitutions that alter the $\text{Fe}^{2+}/\text{Fe}^{3+}$ ratio on the octahedral sites can give more insight into this phase transition. Miyahara²² determined the shift of the transition temperature as a function of the concentration for a number of impurities. Unfortunately, the oxygen stoichiometry affects also the transition temperature.^{19,23} This may explain why no clear relations were found between the transition temperature shifts and the nature or concentration of the substituents.²² Aragon *et al.*²³ reported two regimes in the nonstoichiometry dependence of the transition temperature on either side of a critical composition $\delta_c = 0.0117$ for $\text{Fe}_{3-\delta}\text{O}_4$, with a first-order transition for $\delta < \delta_c$ and a second-order transition for $\delta > \delta_c$. Similar results were reported for stoichiometric magnetite single crystals doped with Zn and Ti, $\text{Fe}_{3-x}\text{Zn}_x\text{O}_4$ and $\text{Fe}_{3-x}\text{Ti}_x\text{O}_4$.²⁴

For Al-substituted magnetite a relative weak dependence of the T_v shift as a function of the substituent concentration was reported, which was partially attributed to a mixed distribution of Al^{3+} over the A and B sites.²⁵

So far it remains still an open question if there is a general universal dependence of T_v upon the dope concentration, irrespective of the nature of the substituent,²⁴ which is the

FIG. 1. Disaccommodation spectrum of polycrystalline, vacancy-doped $\text{Fe}_{3-\Delta}\text{O}_4$ ($\Delta = 10^{-4}$), as obtained in the temperature range 4–450 K for the measuring times $t_1 = 1$ s and $t_2 = 180$ s. Inset (a) shows the strength of the 300-K relaxation as a function of the vacancy concentration; inset (b) represents the disaccommodation spectrum for oxygen-stoichiometric $\text{Fe}_{2.97}\text{Ni}_{0.03}\text{O}_4$.

experimental basis of the mean-field analysis of the Verwey transition.²⁶

EXPERIMENT

To study the effects of impurities on the Verwey transition and to separate the impurity from the oxygen stoichiometry effects, we prepared a number of single crystals $\text{Fe}_{3-x}\text{M}_x\text{O}_4$ with $M = \text{Co}, \text{Ni}, \text{Mg}, \text{Al}, \text{Ga},$ and Ti by means of a floating-zone technique.²⁷

After crystallization, the single crystals were additionally heat treated for at least 48 h at temperatures between 1150 and 1300 °C in adjusted mixtures of CO_2 and H_2 to obtain the highest oxygen stoichiometry. With this technique, homogeneous and stoichiometric single crystals with a predetermined impurity composition could be prepared. Because the standard chemical analysis of the oxygen stoichiometry is not accurate enough for our purpose, we used a high-sensitivity magnetic disaccommodation technique, allowing us to resolve deviations in the oxygen stoichiometry smaller than 1 ppm. The pronounced vacancy-mediated peak near 300 K in the disaccommodation (DA) spectrum of magnetite²⁸ serves as probe for the detection of octahedral vacancies (cf. Fig. 1).

To determine the DA spectra the time dependence of the reciprocal initial susceptibility $r(t, T) = 1/\chi(t, T)$ is measured

FIG. 2. The resistivity of stoichiometric $\text{Fe}_{3-x}\text{Al}_x\text{O}_4$ single crystals with $x = 0.005, 0.01, 0.02,$ and 0.03 as function of temperature.

at each temperature using an automated LC oscillator technique.²⁹ The DA spectra are presented by the isochronal curves, displaying the relative reluctivity at different time intervals (t_1, t_2) :³⁰

$$\frac{\Delta r}{r_1} = \frac{r(t_2, T) - r(t_1, T)}{r(t_1, T)}. \quad (1)$$

As an example, we show in Fig. 1 the vacancy-induced 300-K relaxation of polycrystalline $\text{Fe}_{3-\delta}\text{O}_4$, with $\delta = 10^{-4}$ together with its strength dependence on the inherent vacancy content, cf. inset (a). In all our substituted samples the relaxations due to electronic processes are distinctly present in the temperature range below 150 K, whereas the vacancy induced 300-K peak is completely absent, thus indicating a vacancy concentration of lower than 10^{-6} ; cf. inset (b) of Fig. 1 representing as a typical example the disaccommodation spectra of $\text{Fe}_{2.97}\text{Ni}_{0.03}\text{O}_4$.

The Verwey temperature of the samples was determined from the temperature dependence of the electrical conductivity being measured by a four-probe technique.

RESULTS AND DISCUSSION

In Fig. 2 the electrical resistivity of the Al-doped magnetite samples is logarithmically plotted as function of the temperature. In contrast to Ref. 25, we found a strong dependence of the transition temperature upon the concentration x . For $x = 0.005$ and $x = 0.01$ a sharp first-order transition was observed, whereas for $x = 0.02$ and 0.03 a gradual change was observed pointing to a second-order transition. The maximum in the derivative of the $\ln \rho - T$ plot of these compositions was taken as the transition temperature. From the data of Fig. 2 it follows that the critical Al concentration for the transition from first to second order lies between 0.01 and 0.02, comparable with the value of 0.012 for the Zn or Ti substitutions.²⁴ The weaker composition dependence of T_v for $\text{Fe}_{3-x}\text{Al}_x\text{O}_4$ as reported by Kozłowski *et al.* may be explained by their different preparation technique that resulted in less perfect Al homogeneity.²⁵

Figure 3 presents the resistivity measurements of $\text{Fe}_{3-x}\text{Ga}_x\text{O}_4$ with $x = 0.05$ and 0.1 and stoichiometric Fe_3O_4 . The substituent concentration is much higher than that of the Al system; the transition seems to be of first order and the

FIG. 3. The resistivity of stoichiometric single crystals $\text{Fe}_{3-x}\text{Ga}_x\text{O}_4$ with $x=0, 0.05$, and 0.10 as a function of the reciprocal temperature.

transition temperatures of 116.9 and 110.6 K for $x=0.05$ and $x=0.10$, respectively, are shifted in a less pronounced way. For pure magnetite, a transition temperature of 123.9 K is found.

Doping magnetite with Ni, Co, or Mg yields a transition temperature shift that is in between that of Ga and Al as can be seen from the ΔT_v plot versus concentration in Fig. 4. For all the measured concentrations, sharp transitions were observed, thus suggesting that for all these samples the transition is still of first order. Additionally, some data for Ti substitution in stoichiometric magnetite are plotted in Fig. 4.^{26,31} Despite some qualitative agreement with the data reported by Miyahara,²² in particular concerning the weak influence of the Ga substitution, there remain substantial differences with our numerical data that are supposed to have their origin in the nonstoichiometry of Miyahara's specimens.

The T_v shift versus the substituent concentration reveals specific effects of the various substituents, which were up until now not so evident. Ni, Co, and Mg are all bivalent ionic substituents in magnetite. All three metals give similar shifts for T_v , slightly increasing from 12 K for Ni to 16 K for Mg, if the impurity content is equal to $x=0.03$. This small increase can be understood if we take into consideration that Co and Mg are slightly inverted, as in MgFe_2O_4

FIG. 4. The shift of the Verwey transition temperature for substituted stoichiometric magnetites $\text{Fe}_{3-x}\text{M}_x\text{O}_4$, with $M=\text{Ga, Ni, Co, Mg, Al, and Ti}$. The Ti data are from Refs. 26 and 31 ($x=0.003$ and 0.008).

and CoFe_2O_4 ,³² i.e., 5–20% of the Mg or Co ions are located on A sites, whereas Ni will remain at the B sites. Since these cations are two valent, the ratio of B-sited bi- and trivalent cations is for Ni exactly 2, which is a stipulation for perfect Verwey ordering, whereas for Co and Mg this ratio deviates weakly from 2.

Honig and co-workers^{24,26} reported the concentration dependence of the T_v shift in Zn-substituted magnetite to be about two times larger, as we observed for the Ni^{2+} magnetites. Zn^{2+} is known to occupy A sites, thereby changing the $\text{Fe}^{2+}/\text{Fe}^{3+}$ ratio on the B sites which, evidently, proves to be more effective in disturbing the Verwey order than the replacement of an equal number of octahedral Fe^{2+} ions by other two-valent ions M^{2+} . This becomes plausible by considering that such B-site-substituted M^{2+} ions—within a low-enough concentration range where they cannot hurt the Anderson criterion—in contrast to Fe^{2+} sites are immobile and thereby may even contribute to a stabilization of the ordered phase. The order-disturbing effect of Zn^{2+} substitutions, on the other hand, results from the fact that an equal amount of octahedral Fe^{2+} has to be replaced by Fe^{3+} , which means that $x B_4$ units have a charge of 11^+ instead of 10^+ , thereby destroying the equivalency of the B_4 units. This elucidates why Zn, though not entering the B lattice, has a larger effect upon T_v than the two-valent substitutions on the octahedral lattice. Furthermore, it is an interesting observation that trivalent Ga^{3+} , which, at least for low concentrations, enters preferentially on the tetrahedral sites,^{33,34} reveals a lower composition dependence of ΔT_v . If we estimate that only $\frac{1}{3}$ of the Ga ions enter the octahedral sites,³⁴ the T_v shift corresponding to the octahedral Ga^{3+} concentration would be identical to that of the Ni^{2+} concentration, thus indicating comparable charge-order perturbations for both fixed M^{3+} and M^{2+} ions on B sites. However, the Al^{3+} substitutions show a much stronger effect, which does not fit into the picture discussed above. This incompatibility may be explained in terms of the ionic radii of Al^{3+} (0.535 Å) and Ga^{3+} (0.620 Å) of which the latter one is much closer to that of the octahedral Fe^{3+} (0.645 Å). The geometry of a B_4 unit containing one small Al^{3+} ion will be more deformed, resulting in a variation of the Coulomb energy and, consequently, a larger effect upon the Verwey ordering. In contrast to Al^{3+} , the ionic radii of the bivalent ions Ni^{2+} , Co^{2+} , Mg^{3+} (0.69, 0.745, 0.720 Å)—though being smaller than that of Fe^{2+} (0.78 Å)—range in between the radii of Fe^{3+} and Fe^{2+} and thus, evidently, are disturbing to a smaller extent the ionic packing that governs the Verwey transition.³⁵

Recently, it has also been suggested that magnetic interactions could explain a universal T_v shift versus the concentration of respective substituents, this shift being proportional to the population difference, ΔFe^{3+} of the Fe^{3+} cations on the tetrahedral and octahedral sublattices.²⁵ However, the results obtained on the bivalent substitutions, for which $\Delta\text{Fe}^{3+}=0$, do not support this suggestion. Moreover, Al^{3+} substitutes for low concentrations only on B sites,³⁴ which would imply $\Delta\text{Fe}^{3+}=x$, thereby inducing—in terms of the proposed scaling—a much smaller T_v shift than observed. Further, if magnetic interactions were involved in the mechanism of the Verwey ordering, one would expect a substantial difference between the doping with magnetic (Ni^{2+} ,

Co^{2+}) and nonmagnetic (Mg^{2+}) ions, which is not observed. Since the magnetic interactions in magnetite, leading to the magnetically ordered state, are nearest-neighbor interactions, where the octahedral nearest-neighbor configurations are controlled by the Anderson criterion, it is unlikely that magnetic interactions play a dominant role in the Verwey order-

ing mechanism. In contrast, the systematics in the T_v shifts, in dependence of varying concentrations of specific substituents as we have found, are in favor of the next-nearest-neighbor Coulomb interactions as driving forces for the Verwey ordering.

- ¹For a recent review, see V. A. M. Brabers, in *Handbook of Magnetic Materials*, edited by K. H. J. Buschow (Elsevier Science, Amsterdam, 1995), Vol. 8, Chap. 3.
- ²P. Weiss and R. Forrer, *Ann. Phys. (Paris)* **12**, 330 (1929).
- ³G. S. Parks and K. K. Kelley, *J. Phys. Chem.* **30**, 47 (1926).
- ⁴B. S. Ellefson and N. W. Taylor, *J. Chem. Phys.* **2**, 58 (1934).
- ⁵E. W. J. Verwey, *Nature (London)* **144**, 327 (1939); E. W. J. Verwey and P. W. Haayman, *Physica (Utrecht)* **8**, 979 (1941).
- ⁶E. W. J. Verwey, P. W. Haayman, and F. C. Romeyn, *J. Chem. Phys.* **15**, 181 (1947).
- ⁷G. Shirane, S. Chikazumi, J. Akimisu, K. Chiba, M. Matsui, and Y. Fujii, *J. Phys. Soc. Jpn.* **39**, 949 (1975).
- ⁸Y. Yoshida and S. Iida, *J. Phys. Soc. Jpn.* **42**, 230 (1977).
- ⁹M. Iizumi, T. F. Koetzele, G. Shirane, S. Chikazumi, M. Matsui, and S. Todo, *Acta Crystallogr., Sect. B: Struct. Crystallogr. Cryst. Chem.* **38**, 2121 (1982).
- ¹⁰J. M. Zuo, J. C. H. Spence, and W. Petuskey, *Phys. Rev. B* **42**, 8451 (1990).
- ¹¹M. Mizoguchi, *J. Phys. Soc. Jpn.* **44**, 1501 (1978).
- ¹²M. Mizoguchi, *J. Phys. Soc. Jpn.* **54**, 2168 (1985); **54**, 4295 (1985).
- ¹³S. Iida, *Philos. Mag. B* **42**, 349 (1980).
- ¹⁴K. Siratori, E. Kita, G. Kaji, A. Tasaki, S. Kimura, I. Shindo, and K. Kohn, *J. Phys. Soc. Jpn.* **47**, 1779 (1979); G. T. Rado and J. M. Ferrari, *Phys. Rev. B* **12**, 5166 (1975); Y. Miyamoto and M. Shindo, *J. Phys. Soc. Jpn.* **62**, 1423 (1993).
- ¹⁵E. Kita, K. Siratori, K. Kohn, A. Tasaki, S. Kimura, and I. Shindo, *J. Phys. Soc. Jpn.* **47**, 1788 (1979).
- ¹⁶S. Umemura and S. Iida, *J. Phys. Soc. Jpn.* **40**, 679 (1976); M. Matsui, S. Todo, and S. Chikazumi, *ibid.* **42**, 47 (1977).
- ¹⁷Z. Kakol and J. M. Honig, *Phys. Rev. B* **40**, 9090 (1989).
- ¹⁸P. W. Anderson, *Phys. Rev.* **102**, 1008 (1956).
- ¹⁹(a) E. Gmelin, N. Lenge, and H. Kronmueller, *Phys. Status Solidi A* **79**, 465 (1983); (b) J. P. Shepherd, J. W. Koenitzer, R. Aragon, and J. M. Honig, *Phys. Rev. B* **43**, 8461 (1991); (c) M. O. Rigo, J. F. Mareche, and V. A. M. Brabers, *Philos. Mag. B* **48**, 421 (1983).
- ²⁰J. H. Park, L. H. Tjeng, J. W. Allen, P. Metcalf, and C. T. Chen, *Phys. Rev. B* **55**, 12 813 (1997).
- ²¹A. Chainani, T. Yokoya, T. Morimoto, and T. Takahashi, *Phys. Rev. B* **51**, 17 976 (1995).
- ²²Y. Miyahara, *J. Phys. Soc. Jpn.* **32**, 629 (1972).
- ²³R. Aragon, D. Buttrey, J. P. Shepherd, and J. M. Honig, *Phys. Rev. B* **31**, 430 (1985); R. Aragon and J. M. Honig, *ibid.* **37**, 209 (1988).
- ²⁴A. Kozłowski, Z. Kakol, D. Kim, R. Zalecki, and J. M. Honig, *Phys. Rev. B* **54**, 12 093 (1996).
- ²⁵A. Kozłowski, P. Metcalf, Z. Kakol, and J. M. Honig, *Phys. Rev. B* **53**, 15 113 (1996).
- ²⁶J. M. Honig, *J. Alloys Compd.* **229**, 24 (1995).
- ²⁷V. A. M. Brabers, *J. Cryst. Growth* **8**, 26 (1971).
- ²⁸F. Walz, V. A. M. Brabers, S. Chikazumi, H. Kronmüller, and M. O. Rigo, *Phys. Status Solidi B* **110**, 471 (1982).
- ²⁹F. Walz, *Phys. Status Solidi A* **82**, 179 (1984).
- ³⁰H. Kronmüller, *Nachwirkung in Ferromagnetika* (Springer-Verlag, Berlin, 1968).
- ³¹A. J. M. Kuipers and V. A. M. Brabers, *Phys. Rev. B* **20**, 594 (1979); *J. Phys. (Paris), Colloq.* **38**, C1-233 (1977).
- ³²V. A. M. Brabers and J. Klerk, *J. Phys. (Paris), Colloq.* **38**, C1-207 (1977); Y. Kawai, V. A. M. Brabers, and Z. Šimša, *IEEE Trans. Magn.* **30**, 966 (1994).
- ³³A. Ole, *Acta Phys. Pol.* **30**, 125 (1966); H. Gamari-Seale and P. Papamantellos, *Phys. Status Solidi* **29**, 323 (1968).
- ³⁴M. Rosenberg, P. Deppe, H. U. Janssen, V. A. M. Brabers, F. S. Li, and S. Dey, *J. Appl. Phys.* **57**, 3740 (1985).
- ³⁵R. D. Shannon, *Acta Crystallogr., Sect. A: Cryst. Phys., Diffraction, Theor. Gen. Crystallogr.* **32**, 751 (1976).