Sliding Wear of ZrO₂-Al₂O₃ Composite Ceramics

Citation for published version (APA):

He, Y. J., Winnubst, A. J. A., Burggraaf, A. J., Verweij, H., Varst, van der, P. G. T., & With, de, G. (1997). Sliding Wear of ZrO₂-Al₂O₃ Composite Ceramics. *Journal of the European Ceramic Society*, 17(11), 1371-1380. [https://doi.org/10.1016/S0955-2219\(96\)00239-7](https://doi.org/10.1016/S0955-2219(96)00239-7)

DOI:

[10.1016/S0955-2219\(96\)00239-7](https://doi.org/10.1016/S0955-2219(96)00239-7)

Document status and date:

Published: 01/01/1997

Document Version:

Publisher's PDF, also known as Version of Record (includes final page, issue and volume numbers)

Please check the document version of this publication:

- A submitted manuscript is the version of the article upon submission and before peer-review. There can be important differences between the submitted version and the official published version of record. People interested in the research are advised to contact the author for the final version of the publication, or visit the DOI to the publisher's website.
- The final author version and the galley proof are versions of the publication after peer review.
- The final published version features the final layout of the paper including the volume, issue and page numbers.

[Link to publication](#)

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal.

If the publication is distributed under the terms of Article 25fa of the Dutch Copyright Act, indicated by the "Taverne" license above, please follow below link for the End User Agreement:

www.tue.nl/taverne

Take down policy

If you believe that this document breaches copyright please contact us at:

openaccess@tue.nl

providing details and we will investigate your claim.

Sliding Wear of $\text{ZrO}_2\text{--Al}_2\text{O}_3$ Composite Ceramics

Y. J. He,^a A. J. A. Winnubst,^{*a} A. J. Burggraaf,^a H. Verweij,^a
P. G. T. van der Varst^b and G. de With^b

^aUniversity of Twente, Faculty of Chemical Technology, Laboratory for Inorganic Materials Science, PO Box 217, 7500AE, Enschede, The Netherlands

^bEindhoven University of Technology, Faculty of Chemical Technology, Lab. of Solid State Chemistry and Materials Science, PO Box 513, 5600 MB Eindhoven, The Netherlands

(Received 30 August 1996; accepted 11 November 1996)

Abstract

The friction and wear behaviour of two $\text{ZrO}_2\text{--Al}_2\text{O}_3$ composite materials, ADZ (20 wt% Al_2O_3 dispersed in yttria-doped ZrO_2 matrix) and ZTA ($\text{Al}_2\text{O}_3\text{--}15$ wt% ZrO_2), were investigated. Sliding wear tests were carried out on these materials under dry conditions using a ball-on-plate configuration. The effects of grain size and zirconia phase transformation on friction and wear behaviour were examined. Sinter forging was applied to determine the role of grain boundaries on the wear process. It was found that for ADZ composites the wear resistance increased with decreasing grain size. Only limited grain pull-out occurs in these systems, which also explains the fact that in this case sinter forging has no positive effect on wear resistance. For ZTA composites a compressive surface caused by zirconia phase transformation has a beneficial effect on wear resistance. Here grain pull-out is the main wear mechanism which explains the positive effect of sinter forging ZTA on wear resistance. © 1997 Elsevier Science Limited.

1 Introduction

High performance ceramics can be obtained through microstructural engineering. The microstructure can be optimized by control of, for example, grain size, porosity and grain boundary morphology and composition. The optimization of the microstructure is an important factor for improvement of properties such as strength, toughness, hardness and wear resistance. In Ref. 1 a Hall–Petch type relation was found between wear rate and grain size for yttria-doped tetragonal zirconia (Y-TZP) ceramics against SiC with plastic deformation and microcracking as the

main wear mechanisms. The same relationship was also found by Wu *et al.*² for alumina materials. Using fracture mechanics, Cho and co-workers³ and Wang *et al.*⁴ demonstrated that a Hall–Petch type relation exists between the critical stress for wear transition (from mild to fracture-controlled severe wear) and grain size for ceramics. On the other hand, Liu *et al.*⁵ combined the fracture mechanics used by Cho *et al.*² with a microcracking controlled theory to demonstrate that the wear rate is directly proportional to the grain size for alumina ceramics which was also observed for Y-TZP where the wear mechanism consists of delamination and grain pull-out.¹ The grain size has been recognized as an important factor in characterizing the wear behaviour of ceramic materials.⁶

In Y-TZP ceramics the toughness is directly related to the amount of the tetragonal phase and the transformability from tetragonal to monoclinic zirconia induced by an external stress.^{7–9} Compared to Y-TZP ceramics, polycrystalline Al_2O_3 shows a lower bulk density, higher Young's modulus and hardness, lower linear thermal expansion coefficient and higher thermal conductivity but, on the other hand, inferior mechanical properties. $\text{ZrO}_2\text{--Al}_2\text{O}_3$ composite ceramics may be very attractive materials due to the combination of both ZrO_2 and Al_2O_3 properties. Introduction of zirconia in an alumina matrix (zirconia-toughened alumina = ZTA), leads to a composite material with increased toughness. Stress-induced phase transformation toughening and/or stress-induced microcrack toughening are here the toughening mechanisms. Under certain conditions microcrack toughening occurs in ZTA by the presence of the monoclinic zirconia formed during cooling after ceramic processing resulting in stresses around the zirconia particles. This latter toughening mechanism is used effectively for increasing fracture toughness,¹⁰ but the wear resistance is reduced as compared to pure alumina.¹¹

^{*}To whom correspondence should be addressed.

It has been found that composites with 20 wt% alumina in a zirconia matrix (alumina dispersed in a zirconia matrix = ADZ), exhibit improved toughness and enhanced thermal shock resistance and hardness when compared to zirconia ceramics.¹² In addition, the elastic modulus of these composites is higher, resulting in an increase in the critical grain size for thermally induced phase transformation.¹³ These improvements could be advantageous for tribological applications. It has been reported that composite ceramic cutting tools exhibit much better cutting performance than single-phase Y-TZP.¹²

In Refs 14 and 15 it has been shown that the mechanical properties, e.g. bending strength and fracture toughness, are increased by a factor of about 1.5–2 when sinter forging techniques are used to sinter TZP and ZTA materials. Such an increase in mechanical properties confirms that the grain boundaries are improved by strengthening the bonding between the grains due to creep deformation^{15,16} in the sinter forging process.

In this paper the wear characteristics of ZTA and ADZ composites with a certain range of average grain sizes will be described. The influence of grain boundary strengthening on wear is studied. Through a better knowledge of the relation between wear and grain size/grain-boundary morphology it is possible to find the optimal microstructure for special tribological applications.

2 Experimental Procedure

A homogeneous $\text{ZrO}_2\text{--Al}_2\text{O}_3$ composite with a composition of 5 atom% Y-doped zirconia and 20 wt% (about 28 vol%) Al_2O_3 was obtained by the ' α -alumina' suspension method. In this method, commercially available α -alumina (AKP-50, Sumitomo Chemical Co. Ltd) powder was used with a particle size of 0.1–0.3 μm . A stable suspension with a concentration of 300 g/l was prepared at a pH of 3 by ultrasonic treatment (Branson Sonifier 450) and ball milling. The pH value was adjusted with HCl. A prolonged milling time of more than 24 h was very effective in reducing the alumina particle size in the suspension and obtaining a stable suspension with a high concentration. A mean particle size of 0.23 μm with a narrow size distribution was measured in the stable suspension. This stable α -alumina suspension was added to a dilute hydrochloric acid solution (0.2 M) containing YCl_3 (Cerac 99.9%) and ZrCl_4 (Merck, p.a.). The mixed solution was subsequently precipitated in an excess of NH_4OH (Merck 25%). A gel was obtained, and washed thoroughly with an ammonia/water mixture to

remove all chloride and then washed three times with ethanol to remove the residual water. The dried gel was calcined at 550°C for 2 h.

The ZTA powder with a composition of 85 wt% $\text{Al}_2\text{O}_3\text{--}15$ wt% ZrO_2 (10 vol%) was prepared by a gel-precipitation method, where a diluted metal chloride solution was hydrolysed in an excess of NH_4OH . This process is described in detail in Ref. 16. The powder used here was calcined at 1100°C for 2 h.

The powders were isostatically compacted at 400 MPa and sintered isothermally at 1400–1550°C for 4 h (heating rate 2°C/min) to obtain a microstructure with different grain sizes. The samples used for sinter forging were pre-sintered at 1100–1200°C (heating and cooling rates: 2°C/min) to a density of about 75% to improve compact strength. The samples were subsequently machined plan-parallel. Sinter forging experiments were performed for 15 min under a constant load corresponding to an initial stress of 40 MPa which is defined with respect to the dimensions just before loading. The sinter forging heating schedule was: heating from ambient temperature to 1150°C at a heating rate of 600°C/h and then at 120°C/h to 1400°C and 1450°C for ADZ and ZTA, respectively. More details of the sinter forging set-up are given in Ref. 16. Densities of green and sintered compacts were measured in Hg by the Archimedes' technique. All specimens used for wear tests have densities of at least 98% of the theoretical value. The effects of residual porosity on wear characteristics can therefore be eliminated in the present study. The linear intercept technique was used to determine the average grain sizes in two-phase polycrystalline ceramics from SEM photographs as described by Wurst and Nelson.¹⁷

Friction and wear tests were carried out on a ball (pin)-on-plate wear tester. A polished SiC sphere with a diameter of 4 mm mounted in a copper tube slides reciprocally against an ADZ or ZTA plate in a dry N_2 atmosphere (humidity <1%). A normal load of 8 N was used, corresponding to an initial Hertzian contact pressure of 858 MPa. Track length and frequency are resp. 10 mm and 4 Hz corresponding to a maximum sliding velocity of 12.5×10^{-2} m/s or an average velocity of 8×10^{-2} m/s. The configuration and experimental conditions are described in detail in Ref. 1. Prior to wear experiments all specimens were annealed at 1300°C for 10 min and ultrasonically cleaned in ethanol. After wear testing, the specimens were cleaned again in the same way. The wear volume was calculated from the weight loss, which was measured using an electronic balance (accuracy: 1.0×10^{-5} g). The worn surfaces were analysed by a JSM-35CT (JEOL) scanning electron

microscope (SEM). The surface roughness before and after wear testing was examined using a profilometer (Dek-Tak 3030, Slorn, Santa Barbara, USA). The phase composition was measured on initial and worn surfaces using an X-ray diffractometer with Cu K_α radiation (Philips PW1710) by continuous scanning of 2θ values of 26–36° with a step size of 0.015°. At each step the intensity was counted for 10 s. The volume fraction (V_m) of monoclinic ZrO₂ was calculated by means of Toraya *et al.*'s method.¹⁸ The integrated peak intensities of all (111) reflections were scanned. Intensities were adjusted for the background.

3 Results and Discussion

3.1 ADZ ceramics

The friction coefficient, f_c , and the wear rate (K_{plate} and K_{pin}) after sliding wear are listed in Table 1. Each result is an average of at least three pairs of specimens. The sliding distance for each sample is about 5.8 km. The values of the friction coefficient are obtained when the system is in a steady state after a running-in time of less than 130 min (about 624 metres sliding). The f_c values do not show significant variations with grain size. Using a ring-on-block tribometer Zum Gahr *et al.*²⁰ also indicated that the friction coefficient was independent of grain size for TZP ceramics with the grain size ranging from 0.55 μm to 1.65 μm .

The data in Table 1 show that the grain size of the composites obviously has an influence on wear resistance. The wear resistance of the materials increases with decreasing grain size in ADZ composites. The relationship between grain size and wear resistance, however, is a complex issue, since both ZrO₂ and Al₂O₃ grain sizes determine the final results. The grain sizes of both ZrO₂ and Al₂O₃ increase by almost the same factor, so a similar trend in the relationship between wear rate and grain size holds for the composite. It is important to note that the results of ADZ composites presented here are obtained for grain size as the only variable. A Vickers microhardness

value of 15 GPa and a three-point bending SENB fracture toughness value of 8 MPa $\sqrt{\text{m}}$ are measured for all samples.

In order to investigate the influence of the sinter forging technique applied to ADZ composites, wear tests were carried out on sinter forged specimens (ADZ-S) and compared with results of pressureless sintered specimens (ADZ-I). In both cases, specimens have similar grain sizes of 0.3 and 0.4 μm for ZrO₂ and Al₂O₃, respectively. For the ADZ-S both f_c and K_{plate} do not differ from those for pressureless sintered ADZ, within the experimental error. This means that in ADZ composites, the sinter forging process does not improve the wear resistance.

Compared to single-phase Y-TZP the addition of 20 wt% alumina to Y-TZP results in an obvious increase of Vickers' hardness from 13 to 15 GPa. The ADZ with high hardness can hence also have a different wear behaviour too. The wear rate of single-phase Y-TZP with a grain size of 0.3 μm as analysed under identical tribological conditions with the same tribometer is $1.7 \times 10^{-6} \text{ mm}^3/\text{N m}$,¹ which is about four times higher than that of ADZ ($0.40 \times 10^{-6} \text{ mm}^3/\text{N m}$; see Table 1).

Figures 1 and 2 show scanning electron micrographs of unworn and worn tracks of ADZ composites with small and large grain sizes. Under the present testing conditions, a mild wear occurs in all ADZ materials. The worn surface of fine-grained ADZ is very smooth with only small amounts of grain pull-out. The wear track of the coarse-grained ADZ became rougher (see Fig. 2(b)), but still no evidence of brittle fracture was present. All wear tracks are characterized by the absence of microfracture. Some wear debris is adhered to the worn surface, especially at the edge between the worn and unworn parts (Figs 1(c) and 2(c)). A pronounced difference in the tangential forces during sliding is observed between ADZ composites and Y-TZP.¹ Tested specimens of ADZ scarcely exhibit any microcrack-linked patterns on the worn surfaces or at the turning points. On the other hand, obvious geometric microcrack-linked patterns are easily and often

Table 1. Friction and wear properties of sliding wear of a SiC ball on ADZ ceramic plates

Sample code	Grain size (μm)		ADZ plate $K_{plate} (\times 10^{-6})$ ($\text{mm}^3/\text{N m}$)	SiC ball $K_{pin} (\times 10^{-6})$ ($\text{mm}^3/\text{N m}$)	Friction coefficient (f_c)	<i>m</i> -ZrO ₂	
	ZrO ₂	Al ₂ O ₃				V_b (vol%)	V_{worn}
ADZ-S ^a	0.3	0.4	0.43 $\pm$ 0.04	1.4 $\pm$ 0.3	0.37 $\pm$ 0.03	0	0
ADZ-I	0.3	0.4	0.40 $\pm$ 0.02	1.3 $\pm$ 0.1	0.34 $\pm$ 0.04	0	0
ADZ-II	0.7	0.9	0.84 $\pm$ 0.04	1.5 $\pm$ 0.2	0.37 $\pm$ 0.04	0	3
ADZ-III	0.8	1.1	1.04 $\pm$ 0.06	1.8 $\pm$ 0.2	0.35 $\pm$ 0.03	<1	10

^aADZ-S: sinter forged specimens at 40 MPa with the same grain sizes as ADZ-I.

Fig. 1. SEM of worn surface of ADZ-I: (a) polished surface before wear testing; (b) worn surface after 5.8 km sliding test; (c) worn surface with some wear debris adhered at the edges between the worn and unworn parts. The arrows indicate one direction of the reciprocal sliding.

found on the worn surface of Y-TZP,¹ which are a response to the tensile stresses which develop behind the rubbing contact resulting in a larger wear rate.

The worn track of sinter forged ADZ-S specimen reveals the same wear mechanism as in ADZ-I. In both cases scanning electron micrographs (Fig. 3) do not show any obvious difference. This observation is in agreement with wear rate results.

3.1.1 General discussion of ADZ

Observation of the wear tracks indicates that the contact surface is smooth for fine-grained ADZ. Hence, the contact forces are distributed over a

wide area. A relatively rough surface is observed for coarser-grained ADZ, which is caused by fragmenting and by the pull-out of some larger grains. This type of surface gives higher contact pressures at local asperities resulting in larger tangential stresses behind the trailing edge of rubbing contacts, which consequently causes more wear loss. About 10 vol% of monoclinic zirconia is formed during the wear test of the coarse-grained ADZ (ADZ-III in Table 1). This phase transformation is accompanied by a volume increase for zirconia of 3–5%.²¹ Forces accompanied by this volume increase can weaken the grain boundaries resulting in a grain pull-out during wear tests.

Fig. 2. SEM of worn surface of ADZ-III: (a) polished surface before wear testing; (b) worn surface after 5.8 km sliding test; (c) worn surface with some wear debris adhered at the edges between the worn and unworn parts. The arrows indicate one direction of the reciprocal sliding.

As mentioned before, the main wear mechanism for fine-grained (non-transformed) ADZ is mild wear without any brittle fracture or formation of microcracks. For such a wear mechanism, the grain boundaries do not play an important role in the wear process. Therefore sinter forging for improving the grain-boundary strength hardly reveals an improvement in wear resistance in comparison with pressureless sintered specimens.

The difference in wear mechanism between ADZ and Y-TZP¹ can be explained in terms of the difference in hardness. Using a quasi-static model, Evans *et al.*²² established a theoretical treatment of ceramic wear as a function of hardness.

They found that the wear rate is inversely proportional to a certain power of the hardness. Fischer *et al.*,²³ however, indicated that the contact area between two ceramic materials is determined either by plastic deformation or, more probably in ceramics, by elastic deformation. The contact area between harder ceramic surfaces will be less than that between relatively softer ceramic surfaces. The contact stresses are therefore larger and, consequently, the tendency for fracture wear is larger. A higher hardness may therefore cause inferior rather than superior wear resistance. As suggested by Fischer *et al.*,²³ this effect is only present for brittle materials in which the wear process

Fig. 3. SEM of worn surface of ADZ composites: (a) pressureless sintered ADZ-I with grain sizes of 0.3 μm and 0.4 μm for ZrO_2 and Al_2O_3 , respectively; (b) sinter forged ADZ-S with the same grain sizes as the ADZ-I. The arrows indicate one direction of the reciprocal sliding.

is controlled by brittle fracture. Because of its high fracture toughness (8 $\text{MPa}\sqrt{\text{m}}$) ADZ exhibits a ductile behaviour and has a high resistance to microcrack formation. As a result of these properties, the wear of ADZ composites occurs only by polishing and to a lesser extent by grain pull-out. Thus, the effects of hardness of the materials can be different from the case studied by Fischer *et al.*²³ Wang *et al.*⁴ developed a semi-empirical wear model based on an energy balance and predicted that the wear volume is inversely proportional to the indentation hardness of polycrystalline materials. He *et al.*⁶ also used this model for $\text{ZrO}_2\text{-Al}_2\text{O}_3$ (5–20 vol% ZrO_2) composite materials and found that the higher hardness of the composite materials had beneficial rather than detrimental effects on the wear resistance. These literature results strongly support the results obtained in this study.

3.2 ZTA ceramics

Wear tests were performed on ZTA ceramics with various grain sizes which were prepared by sinter forging and pressureless sintering. The friction coefficient (f_c) and wear rate (K) data are listed in Table 2. The results are given as average values of three or four similar tests. It was found that sinter forged specimens have a wear rate which is a factor of 2–3 lower if compared to pressureless sintered specimens. The friction coefficient values are the same within experimental error. As for the effects of grain size, it can be seen from Table 2 that the coarse-grained ZTA-II reveals a lower wear rate than the fine-grained ZTA-I. After wear

testing, a larger amount of tetragonal zirconia in ZTA-II has transformed to the monoclinic phase compared to ZTA-I.

Figure 4 shows SEM pictures of a ZTA-I surface before and after a wear test. The polished surface prior to the wear tests, with a roughness <50 nm, is shown in Fig. 4(a). The zirconia grains (white particles) are distributed homogeneously in the alumina matrix (black particles). After sliding wear, some microcracking perpendicular to the sliding direction and scaling patterns are found at the turning points of the wear tracks as shown in Fig. 4(b). No microcracks exist in the middle of the wear track. A high magnification SEM micrograph of the wear track (Fig. 4(c)) reveals that the wear loss of ZTA-I is caused by a polishing process and accompanying grain pull-out at places where some pits are left. Wear debris fills some local deep pits especially at the edges of the track and is smeared out during the sliding process. No plastic deformation was observed after wear tests.

For ZTA-S specimens, prepared by sinter forging, no microcracking or scaling patterns were observed. In Fig. 5, a high magnification picture of the wear tracks indicates almost the same wear mechanism as that in pressureless sintered ZTA-I. Grain pull-out in ZTA-S is, however, less than in ZTA-I.

In comparison with ZTA-I, the coarse-grained ZTA-II reveals the same wear mechanisms (Fig. 6), but no microcracks are found in the wear tracks. The worn surface of ZTA-II has a higher roughness than of ZTA-I.

Table 2. Friction and wear properties of sliding wear of the SiC ball on ZTA ceramic plates

Sample code	Grain size (μm)		ZTA plate K ($\times 10^{-6}$) ($\text{mm}^3/\text{N m}$)	SiC ball K ($\times 10^{-6}$) ($\text{mm}^3/\text{N m}$)	Friction coefficient (f_c)	$m\text{-ZrO}_2$	
	ZrO_2	Al_2O_3				V_h (vol%)	V_{worn}
ZTA-S ^a	0.3	0.8	1.44 ± 0.31	1.1 ± 0.2	0.33 ± 0.05	5	15
ZTA-I	0.3	0.8	3.40 ± 0.90	1.0 ± 0.2	0.37 ± 0.03	6	14
ZTA-II	0.5	1.6	1.28 ± 0.34	1.2 ± 0.4	0.36 ± 0.05	22	39

^aZTA sinter forged at 40 MPa with the same grain size as ZTA-I.

3.2.1 General discussion of ZTA

The observation of worn surfaces indicates that polishing and grain pull-out are the main wear mechanisms in ZTA ceramics. Microcracks exist at turning points in pressureless sintered ZTA-I,

while such microcracks have not been found in sinter forged ZTA-S. The grain pull-out during the wear process in the ZTA-I is more pronounced than in ZTA-S. The strengthening of grain boundaries by sinter forging¹⁵ prevents

Fig. 4. Scanning electron micrographs of ZTA-I materials: (a) the polished surface; (b) the worn surface with some cracking and scaling patterns; (c) a high magnification of the worn surface. The arrows indicate one direction of the reciprocal sliding.

Fig. 5. Morphology of the worn surface of ZTA-S sinter forged at 40 MPa.

cracking. The microcracks are easily formed at local flaws during a fatigue wear process and propagate along weak paths, especially at weak grain boundaries. From previous work,¹⁵ it is known that a creep deformation is exerted on the specimens during sinter forging, in which process flaws are eliminated and the bonding strength between grain boundaries is enhanced. The strengthened grain boundaries also increase the energy necessary for grain pull-out and consequently reduce the wear loss of the materials.

The coarse-grained ceramics reveal a higher wear resistance than the fine-grained ones. This

Fig. 6. Morphology of the worn surface of ZTA-II with relatively larger grains.

may result from compressive stresses at the surface caused by zirconia transformation from tetragonal to monoclinic accompanied by a grain volume increase of 3–5%, while no microcracks are formed because of the alumina matrix with higher Young's modulus than the zirconia second phase. The experimental results show that before wear testing the percentage of monoclinic zirconia which is spontaneously transformed during cooling after annealing is larger in coarse-grained ZTA than in fine-grained ZTA. The constraining force caused by the alumina matrix is in general higher in the bulk than in the surface layer. So the fraction of monoclinic zirconia in the polished surface is higher than that in the bulk. During the sliding process, a certain amount of tetragonal zirconia transforms resulting in an increase in the compressive stress in the surface layer with increasing zirconia grain size yielding an increase in compressive surface stresses. According to Green *et al.*,²⁴ the compressive stress in the surface layer can be calculated as follows:

$$\sigma_c = \frac{1}{3} \left(\frac{\Delta V}{V} \right) \frac{E V_v}{(1 - \nu)} \quad (1)$$

where σ_c is the biaxial compressive stress in the surface layer, and E and ν are the Young's modulus (375 GPa¹⁹) and the Poisson's ratio (0.3), respectively for the alumina matrix. $\Delta V/V$ is the fractional molar volume increase associated with the phase transformation (3–5%). V_v is the volume fraction of transformed zirconia, which is the difference between the amount of monoclinic zirconia at the worn surface, V_{worn} , and in the bulk, V_b . The minimum value of V_v is the volume fraction of zirconia transformed from the tetragonal to monoclinic phase during the sliding wear process (also, during cooling after sintering, some higher amount of monoclinic ZrO_2 might be present at the surface). Because the total amount of ZrO_2 in ZTA is about 10 vol%, the volume fraction (V_v) of transformed zirconia in the surface layer corresponds to:

$$V_v = (V_{\text{worn}} - V_b) \times 10 \text{ vol\%} \quad (2)$$

From eqns (1) and (2), the compressive stresses due to the transformation during sliding wear are calculated to be 57 MPa and 121 MPa for fine-grained ZTA-I and coarse-grained ZTA-II, respectively. The larger the compressive stress, the greater the resistance to crack propagation resulting from tensile stresses, hence leading to a decrease in wear loss. Therefore, it is suggested that the higher wear resistance in the coarse-grained ZTA-II is due to the larger compressive stress layer formed at the surface.

From the discussion given above it can be seen that the tetragonal zirconia transformation in ZTA has a positive effect on the wear resistance. This is different from the results of Y-TZP,¹ where the tetragonal zirconia transformation results in a tensile shear stress underneath the sliding surface. This stress promotes subsurface cracks to propagate along grain boundaries, thereby increasing the wear rate. This different function of the tetragonal zirconia transformation may be related to the amount of zirconia and its situation in different ceramics. For ZTA materials, the zirconia particles are homogeneously dispersed in the alumina matrix, so the transformed zirconia particles are separated by the alumina matrix. The tensile stresses are limited to a local area. For this situation, the tensile stress in the subsurface may not have an obvious effect. Therefore, in case of ZTA materials, the tetragonal zirconia transformation (without induced microcracks) produces a superior rather than inferior wear resistance. The increase in wear resistance of ZTA ceramics due to transformation-toughening mechanisms is also reported by other investigators.⁶

4 Conclusions

The effects of grain size and grain-boundary morphology of two zirconia-alumina composites on sliding wear are investigated using a pin-on-plate tribometer under a Hertzian contact pressure of 858 MPa.

During the wear tests of alumina dispersed in Y-TZP (ADZ) the amount of tetragonal zirconia transforming to the monoclinic crystal structure increases with increasing grain size resulting in a decrease in wear resistance. The volume increment caused by this phase transformation weakens the grain boundaries which results in grain pull-out.

In fine-grained ADZ, where no phase transformation occurs during wear tests, a decrease in wear rate of a factor 4 is observed if compared to single-phase Y-TZP with the same zirconia grain size. This improvement can be attributed to the higher hardness of the composite.

In these ADZ composites no wear track shows any microfracture while only a small amount of grain pull-out was observed. Sinter forging, which can improve the grain-boundary strength, therefore has no influence on the tribological properties of these systems.

For composites of ZrO_2 in an alumina matrix (ZTA) also a larger amount of monoclinic zirconia was observed with increasing grain size but in this case the wear rate decreases. The higher wear

resistance for coarser-grained ZTA is due to the larger compressive stress layer formed at the surface, without the formation of any subsurface cracks.

The wear mechanism in these ZTA composites is mainly polishing and grain pull-out, while microcracks arise at the turning points. Here strengthening of the grain boundaries by sinter forging has a positive effect on wear resistance. A decrease in wear rate by a factor of 2–3 is obtained if sinter forging is applied on ZTA.

References

1. He, Y. J., Winnubst, A. J. A., Burggraaf, A. J., Verweij, H., Van der Varst, P. G. T. and De With, G., Grain size dependence on sliding wear in tetragonal zirconia polycrystals. *J. Am. Ceram. Soc.*, in press (1996).
2. Wu, C. C., Rice, R. W., Johnson, D. and Platt, B. A. *Ceram. Eng. Sci. Proc.*, 1985, **6**(7–8), 995–1011.
3. Cho, S. J., Moon, H., Hockey, B. J. and Hsu, H. M., The transition from mild to severe wear in alumina during sliding. *Acta Metall. Mater.*, 1992, **40**, 185–192.
4. Wang, Y. S., He, C., Hsu, S. M. and Lacey, P. I. In *Proceedings of the Japan International Tribology Conference*, Nagoya, vol. 2, Japanese Society of Tribologists, Tokyo, Japan, 1990, pp. 1225–1230.
5. Liu, H. and Fine, M. E., Modeling of grain-size-dependent microfracture-controlled sliding wear in polycrystalline alumina. *J. Am. Ceram. Soc.*, 1993, **76**, 2393–2396.
6. He, H., Wang, Y. S., Wallace, J. S. and Hsu, S. M., Effect of microstructure on the wear transition of ZTA. *Wear*, 1993, **162–164**, 314–321.
7. Lange, F. F., Transformation toughening; part 3: experimental observations in the $\text{ZrO}_2\text{-Y}_2\text{O}_3$ system. *J. Mater. Sci.*, 1982, **17**, 240–246.
8. Butler, W. P., Transformation toughened zirconia ceramics. *Mater. Sci. Technol.*, 1985, **1**, 417–432.
9. Evans, A. G. and Cannon, R. M., Toughening of brittle solids by martensitic transformations. *Acta Metall.*, 1986, **34**, 761–800.
10. Claussen, N., Steele, J. and Pabst, R. F., Effect of induced microcracking on the fracture toughness of ceramics. *Am. Ceram. Soc. Bull.*, 1977, **56**, 559–562.
11. Trabelsi, R., Treheux, D., Orange, G., Fantozzi, G., Homerin, P. and Thevenot, F., Relationship between mechanical properties and wear of alumina-zirconia ceramic composites. *Tribology Transactions*, 1989, **32**, 77–84.
12. Sornakumar, T., Krishnamurthy, R. and Gokularathnam, C. V., Machining performance of phase transformation toughened alumina and partially stabilised zirconia composite cutting tools. *J. Eur. Ceram. Soc.*, 1993, **12**, 455–460.
13. Lange, F. F., Transformation toughening; part 1: size effects associated with the thermodynamics of constrained transformation. *J. Mater. Sci.*, 1982, **17**, 225–234.
14. He, Y. J., Winnubst, A. J. A., Verweij, H. and Burggraaf, A. J., Improvement of the mechanical properties of zirconia-toughened alumina by sinter forging. *J. Mater. Sci.*, 1994, **29**, 5868–5874.
15. He, Y. J., Winnubst, A. J. A., Sagel-Ransijn, C. D., Burggraaf, A. J. and Verweij, H., Enhanced mechanical properties by grain boundary strengthening in ultra-fine-grained TZP ceramics. *J. Eur. Ceram. Soc.*, 1996, **16**, 601–612.
16. He, Y. J., Winnubst, A. J. A., Verweij, H. and Burggraaf, A. J., Sinter forging of zirconia toughened alumina. *J. Mater. Sci.*, 1994, **29**, 6505–6512.

17. Wurst, J. C. and Nelson, J. A., Lineal intercept technique for measuring grain size in two-phase polycrystalline ceramics. *J. Am. Ceram. Soc.*, 1972, **55**, 109.
18. Toraya, H., Yoshimura, M. and Somiya, S., Calibration curve for quantitative analysis of the monoclinic-tetragonal ZrO_2 system by X-ray diffraction. *J. Am. Ceram. Soc.*, 1984, **67**, C119-C121.
19. Becher, P. F., Transient thermal stress behaviour in ZrO_2 -toughened Al_2O_3 , *J. Am. Ceram. Soc.*, 1981, **64**, 37-39.
20. Zum Gahr, K. H., Bundschuh, W. and Zimmerlin, B., Effect of grain size on friction and sliding wear of oxide ceramics. *Wear*, 1993, **162-164**, 269-279.
21. Claussen, N., Microstructural design of zirconia-toughened ceramics (ZTC). In *Advances in Ceramics Vol. 12; Science and Technology of Zirconia II*, ed. N. Claussen, M. Rühle and A. Heuer. The American Ceramic Society, Ohio, 1984, pp. 325-351.
22. Evans, A. G. and Marshall, D. B., Wear mechanisms in ceramics. In *Fundamentals of Friction and Wear of Materials*, ed. D. A. Rigney. ASM International, 1981, pp. 439-453.
23. Fischer, T. E., Anderson, M. P. and Jahanmir, S., Influence of fracture toughness on the wear resistance of yttria-doped zirconium oxide, *J. Am. Ceram. Soc.*, 1989, **72**, 252-257.
24. Green, D. J., Lange, F. F. and James, M. R., Factors influencing residual surface stresses due to a stress-induced phase transformation. *J. Am. Ceram. Soc.*, 1983, **66**, 623-629.
25. Green, D. J., Lange, F. F. and James, M. R., Residual surface stresses in Al_2O_3 - ZrO_2 composites. In *Advances in Ceramics Vol. 12; Science and Technology of Zirconia II*, ed. N. Claussen, M. Rühle and A. Heuer. The American Ceramic Society, Ohio, 1984, pp. 240-250.