1/f Noise sources

Citation for published version (APA):

Hooge, F. N. (1994). 1/f Noise sources. *IEEE Transactions on Electron Devices*, 41, 1926-1935.
<https://doi.org/10.1109/16.333808>

DOI:

[10.1109/16.333808](https://doi.org/10.1109/16.333808)

Document status and date:

Published: 01/01/1994

Document Version:

Publisher's PDF, also known as Version of Record (includes final page, issue and volume numbers)

Please check the document version of this publication:

- A submitted manuscript is the version of the article upon submission and before peer-review. There can be important differences between the submitted version and the official published version of record. People interested in the research are advised to contact the author for the final version of the publication, or visit the DOI to the publisher's website.
- The final author version and the galley proof are versions of the publication after peer review.
- The final published version features the final layout of the paper including the volume, issue and page numbers.

[Link to publication](#)

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal.

If the publication is distributed under the terms of Article 25fa of the Dutch Copyright Act, indicated by the "Taverne" license above, please follow below link for the End User Agreement:

www.tue.nl/taverne

Take down policy

If you believe that this document breaches copyright please contact us at:

openaccess@tue.nl

providing details and we will investigate your claim.

1/f Noise Sources

F. N. Hooge

Invited Paper

Abstract—This survey deals with 1/f noise in homogeneous semiconductor samples. A distinction is made between mobility noise and number noise. It is shown that there always is mobility noise with an α value with a magnitude in the order of 10^{-4} . Damaging the crystal has a strong influence on α , α may increase by orders of magnitude.

Some theoretical models are briefly discussed; none of them can explain all experimental results. The α values of several semiconductors are given. These values can be used in calculations of 1/f noise in devices.

I. NOISE SOURCES

THIS paper serves as an introduction to several papers in this special issue, which is devoted to noise in devices.

One way of analyzing the noise of a device is to assume noise sources in several parts on the device. The noise measured at the output is the summation of many contributions from the different sources modified by the device characteristics. The device may introduce coupling between different contributions. If one has a reliable model of the device and if one knows the noise sources, it is possible to calculate the output noise. One then concludes that the noise of the device is understood if agreement is observed between calculated and measured noise, as functions of voltages and currents.

It is also possible to go the other way round. Starting from the observed output noise one tries to determine the noise sources. One then estimates properties like concentrations, cross-sections and α values of 1/f noise. This procedure, from observed output to sources, is risky. Apart from the trivial requirement that the model must be treated correctly—not too many simplifying approximations—there is the difficult problem whether the model used, is a correct description of the device under investigation. Noise is much more sensitive to details than the average voltages and currents. This procedure always leads to results, but are they reliable? If one incorrectly assumes a bulk source where in fact a surface source is present, one finds an α value without any meaning. Such α values are nevertheless used as an argument for or against certain theories. The properties for the noise sources derived the second way need independent checking. One must have some idea at least of what realistic values are.

The properties of noise sources can, therefore, best be studied on homogeneous samples. The numerical results can then be used in the much more complicated problem of the

inhomogeneous and often nonlinear devices. For the same reason, α values obtained from devices are excluded from Fig. 5 at the end of this paper. There we present reliable data, all obtained from homogeneous samples.

Four types of noise are of importance in semiconductors.

- 1) **Thermal noise.** Any resistance R shows spontaneous current fluctuations or voltage fluctuations according to:

$$S_V = 4kTR \quad (1)$$

$$S_I = 4kT/R. \quad (2)$$

This white spectrum is always found, whatever the nature of the conduction process, or the nature of the mobile charge carriers. Thermal noise is generated in any physical resistor that shows dissipation if a current is passed through it. A mathematical property, which is measured in Ω , such as a dynamical resistance dV/dI of a nonlinear device must not be used in (1) or (2).

- 2) **Shot noise.** The current carried by electrons emitted from a hot cathode in a vacuum diode, or by electrons that cross a potential barrier in a semiconductor, are randomly generated. Random generation leads to fluctuations around the average current I :

$$S_I = 2qI. \quad (3)$$

The details of the emission process have no influence on the noise, provided that there is no interaction between the electrons, and that the statistics is close to Boltzmann.

- 3) **Generation-recombination noise.** The number of free electrons in the conduction band may fluctuate because of generation and recombination processes between the band and traps. The number fluctuations cause fluctuations in the conductance G , and, therefore, in the resistance R .

$$\frac{S_R}{R^2} = \frac{S_G}{G^2} = \frac{S_N}{N^2} = \frac{(\overline{\Delta N})^2}{N^2} \frac{4\tau}{1 + \omega^2\tau^2} \quad (4)$$

where τ is a relaxation time, characteristic of the trap, usually in the range of 10^{-6} s to 10^{-3} s. If there is one type of trap only, then the variance $(\overline{\Delta N})^2$ is given by

$$\frac{1}{(\overline{\Delta N})^2} = \frac{1}{N} + \frac{1}{X_n} + \frac{1}{X_p} \quad (5)$$

Manuscript received October 29, 1993; revised June 17, 1994. The review of this paper was arranged by Editor-in-Chief R. P. Jindal.

The author is with the Department of Electrical Engineering, Eindhoven University of Technology, 5600 MB Eindhoven, The Netherlands.

IEEE Log Number 9405325.

0018-9383/94\$04.00 © 1994 IEEE

where X_n is the average number of occupied traps and X_p the average number of empty traps. The variance thus approximates the smallest of the quantities N , X_n and X_p .

The complicated problem of a semiconductor with two kinds of traps, X and Y , has been solved by van Vliet and Fasset [1]. Later publications [2]–[4] deal with practical questions like, under which conditions will the observed spectrum be the superposition of two Lorentzians, one which would have been found if only X were present, the other one for the case that only Y were present. The condition for this, often naïvely assumed, situation is

$$\frac{1}{N} \ll \frac{1}{X_n} + \frac{1}{X_p} < \frac{1}{Y_n} + \frac{1}{Y_p} \quad (6)$$

[3] gives simple procedures to determine cross sections and trap concentrations from observed GR spectra too.

- 4) **1/f Noise.** This is a fluctuation in the conductance with a power spectral density proportional to $f^{-\gamma}$, where $\gamma = 1.0 \pm 0.1$ in a wide frequency range, usually measured from 1 Hz to 10 kHz. The spectrum cannot be exactly f^{-1} from $f = 0$ to $f = \infty$, since neither the integral of the power density nor the Fourier transform would be able to have finite values. At some higher frequency f_h the slope must be steeper than -1 . This f_h has never been observed for the simple reason that at higher frequencies the $1/f$ noise disappears in white thermal noise that is always present. Attempts to observe the lower limit f_l , below which the spectrum flattens, have always been in vain. Measurements down to 10^{-6} Hz showed that even there the spectrum still is f^{-1} [5]. Because of the restrictions on $\gamma \simeq 1$ we do not consider $f^{-1/2}$ and $f^{-3/2}$ as $1/f$ noise, like some people do. In semiconductor devices, such spectra usually follow from diffusion processes.

Unlike the first three sources mentioned above, which are well understood, the origin of the $1/f$ noise is still open to debate, a debate full of vehement controversies [6]–[11]. Therefore, from here on we will discuss $1/f$ noise only. Due to our present interest in devices, which operate at room temperature, we concentrate on $1/f$ noise at $T = 300$ K. Temperature influence is only discussed if it helps to elucidate the physical nature of $1/f$ noise. For the same reason we need not deal with the noise of hot electrons. In general we shall pay less attention to the theoretical problems of the physical model of the noise, than to reliable numerical values to be used in device models.

II. THE FACTOR α/N

The relation

$$\frac{S_R}{R^2} = \frac{\alpha}{fN} \quad (7)$$

was proposed 25 years ago [12] in an effort to systematically collect data on $1/f$ noise from the literature. In that collection the influence of the size of the ohmic homogeneous

samples, the carrier concentration, the frequency range of the measurements, etc., had to be eliminated. The only theoretical idea behind the relation was, that whatever the electrons do when producing $1/f$ noise, they do it independently. Thus, α is a normalized measure for the relative noise in different materials, at different temperatures, etc. There was no reason to assume that α was a constant. On the contrary, we were looking for factors influencing α . Given the inaccuracies of the individual experimental results—and with hindsight—given the rather poor qualities of the samples no systematic trend in α was found at the time. The α values were not too far apart, and it seemed reasonable to take $\alpha = 2 \times 10^{-3}$ as an average value. Later on it turned out that α depends on the quality of the crystal, and on the scattering mechanisms that determine the mobility μ . In perfect material α can be 2 or 3 orders of magnitude lower than the 2×10^{-3} originally proposed.

Before we can further discuss dependences of α on certain parameters, like temperature, dope, etc., or even before we can decide that it is meaningful to take an average of measured values, we should have some idea of what we consider to be essentially the same values. We need an idea of what random errors are, and what may point to a systematic dependence on some parameter. Noise very much depends on the physical conditions during growing, doping, intentional and unintentional surface treatment, and contacting. Fig. 1 gives an example of the best results we can get. The points on a vertical line (at the same value of μ) were measured on different samples made from the same wafer. A spread in α of a factor 1.5 is found. Each point is the average of several measurements, with different currents, on the same sample. The spread is wider if samples are made from different wafers with the same properties nominally. It is wider still if similar samples from different laboratories are compared.

For a meaningful result we need the average over many samples. The best we can hope for is that samples from different sources, measured under different conditions, give α values with the same order of magnitude. As a result, if one wants to find certain numerical values to support or refute a theoretical model one can always find them in literature. Discussing systematic dependences of α on some parameter requires a set of similar samples, expressly made for the purpose, such as the samples used for Fig. 1.

In spite of all uncertainties, Fig. 1 shows that the dependence of α on μ can be found from a set of carefully prepared samples, where only one parameter is varied. It is even possible to extrapolate the results to samples without impurity scattering, although such samples cannot be made. The inaccuracy in the extrapolated value of α_{latt} is less than 10%, despite the factor 1.5 between individual α values. The dimensions length, width, and thickness do not appear in (7), proving that $1/f$ noise is a bulk effect. Previous theories that considered $1/f$ noise as a surface effect [13] were thus refuted, at least that is for the homogeneous samples considered. The bulk $1/f$ noise, which has been proven to exist beyond any doubt in homogeneous samples, also occurs in devices where its magnitude can be estimated using the α value determined in homogeneous material. However, there is positive evidence that surface $1/f$ noise exists too. Certainly in MOST's, many

Fig. 1. Plot of $\log \alpha_{\text{meas}}$ versus $\log \mu_{\text{meas}}$ for epitaxial n-GaAs at 300 K. (Reprinted from: L. Ren and M. R. Leys, "1/f noise at room temperature in N type GaAs grown by molecular epitaxy," *Physica B*, vol. 172, pp. 319–323, 1991.)

experimental data are better explained by surface effects than by bulk effects. [14] The noise of MOST's is discussed in the paper by Vandamme, Li, and Rigaud, in this Special Issue.

If the same relation (7) holds good for metals, it is immediately clear that for noise studies in metals very small samples are required. Early experiments on point contacts [15] and thin films [16] showed that the relation does indeed hold good, and that α has the same order of magnitude as in semiconductors. The old idea that 1/f noise is exclusively a semiconductor effect was thereby proved to be incorrect.

Arguments against (7) have also been raised, not so much because of the difficulties with α (a constant or a parameter), but because of the factor N in the denominator. One argument is rather trivial. If one were to start the discussion of a theoretical model by immediately considering an "average" electron, then the number of electrons N would not appear in the final result. It has been concluded from such models that relation (7) cannot be correct because of the factor $1/N$. This discussion is summarized in [19].

In experiments one always observes a group of N electrons. In the oversimplified models with an "average" electron, a single electron is considered [17]. A proper theory, however, yields the result averaged over an ensemble of identical samples, electron systems, and so on in full agreement with experiment. Theory does not provide arguments against the use of a normalizing factor $1/N$.

Weissman [18] put forward a more serious argument that had already been brought up at some conferences. If one considers the 1/f noise as a summation of Lorentzians (see Section IV) then the very low frequencies, where 1/f noise is observed, require Lorentzians with a long characteristic time $\tau \gg 1$ s. Therefore, the electrons must stay in the sample much longer than a few seconds, in order to produce these

low-frequency Lorentzian distributions. However, even in a sample with a length of 1 cm an electron only stays about 0.1 s as its diffusion coefficient D is of the order of 10^{-3} m²/s. How then can electrons, that stay in the sample for only such a short while, produce noise at frequencies below 1 Hz? The answer is as follows: We have evidence that the 1/f noise is in the lattice scattering (see Section III). The lattice modes can scatter electrons. The scattering cross-sections fluctuate slowly with a 1/f spectrum. There are permanently N electrons—on average—that probe the slowly varying cross sections. We do not follow individual electrons. Individual electrons move in and out the sample; the lattice is permanent.

This idea has been worked out in more detail in [19]. A model was considered where N electrons were scattered by A lattice modes. This led to a relation for the noise in the current density where S_j/j^2 is proportional to $1/N$ and independent of A .

Having answered theoretical objections against the factor $1/N$, we would nevertheless like to investigate the experimental evidence at this point. We introduced N as a measure of the size of the sample. In bigger samples the relative noise must average out. Another measure for the size may do as well, like the volume, the number of atoms A , or the number of lattice modes, proportional to A . We therefore made a comparison between N and A [19]. If the relative noise is written as

$$\frac{S_R}{R^2} = \frac{\alpha}{Nf} = \frac{\gamma}{Af} \quad (8)$$

it turns out that α is a better "constant" than γ is. Values of α are found between 10^{-4} and 2×10^{-3} , whereas γ varies between 10 and 10^5 in a group of some twenty semiconductors. These experimental data give no argument for preferring γ/A to α/N .

Since it is doubtful whether α has the same value in different materials, a more direct proof for α/N being the correct factor is to study the injection of a varying number of electrons in a given volume of a semiconductor, either by electrical injection in a forward diode [20], or by persistent photoconductivity [21]. Such experiments show that the noise is proportional to $1/N$. In each experiment α turns out to be a constant. The observed constants from different experiments are in the normal range 10^{-4} to 10^{-3} .

III. EXPERIMENTAL DISTINCTION BETWEEN Δn AND $\Delta \mu$

The 1/f noise is a fluctuation in the conductivity. There is conclusive experimental evidence for this point of view. Conductivity fluctuations lead to fluctuations in the resistance R and thus to slow fluctuations in the power density of the thermal noise $4kTR$.

$$S_{S_V} \propto S_R. \quad (9)$$

Because of (1) one can measure the noise in R by measuring the noise in S_V . In such measurements no current is passed through the sample [22]. These special measurements prove that 1/f noise is not generated by the current. In conventional measurements the current is only necessary to transform the already existing conductivity fluctuations into voltage fluctuations that can be measured.

So $1/f$ noise is a fluctuation in the conductivity. This is the last point on which general agreement can be reached. Any next step causes a great deal of controversy. As the conductivity

$$\sigma = nq\mu \quad (10)$$

contains the product of n and μ the next question is: "What is fluctuating with a $1/f$ spectrum, n or μ ?"

In a series of experiments it was shown that there is a type of $1/f$ noise that is a fluctuation in the mobility. These experiments were done on homogeneous samples, mainly silicon. From these experiments it follows that this mobility $1/f$ noise is always present. It is described by (7), where the α value is in the order of magnitude of 10^{-4} in perfect material. In damaged material the mobility noise may be considerably increased. On top of the mobility noise there may be other types of $1/f$ noise, e.g., number fluctuations generated at surface states. Number fluctuations caused by trapping processes at the surface play an important part in MOST's. It seems that we see Δn noise in an N -channel MOST, whereas in a P -channel $\Delta\mu$ noise is observed. The very complicated situation of MOST noise is discussed in this Special Issue in the papers by Vandamme, Li, and Rigaud and by Chang, Abedi, and Viswanathan.

In this section we will concentrate on the fundamental mobility noise in good material. We will consider the noise in thermo EMF, Hall effect, etc. The principle of such an analysis is that in the same sample electrons move because of an applied electric field, and because of some other generalized force, e.g., a temperature gradient.

In the experiment the ratio of the two generalized forces are varied and the change in magnitude of the $1/f$ noise is observed. In the analysis one first introduces a $\Delta\mu$ term in the transport equation, and calculates the expected fluctuation in the observed voltage or current. Then such a calculation is done with a Δn source. The observed noise in voltage or current always agrees with $\Delta\mu$ fluctuations. In most cases the observed noise is far off from the line for Δn fluctuations. Sometimes the results of the calculations for Δn and $\Delta\mu$ are not that far apart, so that no distinction can be made. There was no case in which the differences between observed and calculated $\Delta\mu$ values were so large that mobility fluctuations had to be excluded in favor of Δn fluctuations. These experiments have been discussed in a review paper in 1981 [22]. At that time the result of noise measurements in the Hall effect was indecisive. The theoretical lines of Δn and $\Delta\mu$ as functions of the magnetic induction B were not that far apart. Recently, results were published on the noise in the Hall effect in $n\text{GaAs}$, where it is easy to reach high μB values ($\mu B \gg 1$). Under these conditions the theoretical lines of Δn and $\Delta\mu$ versus B deviate widely; where the experimental points follow the $\Delta\mu$ line nicely [23]. Such calculations are rather complicated, since they have to start from individual levels in the conduction band. Integration over the whole band then gives the noise magnitude that can be compared with the experimentally observed value.

A much more transparent proof for mobility fluctuations is provided by the analysis of the noise in the conductance

of semiconductor samples, where two scattering mechanisms determine the mobility. We consider a semiconductor in which two scattering mechanisms are active: lattice scattering and impurity scattering. The mobility μ_{meas} measured is given by Matthiessen's rule

$$\frac{1}{\mu_{\text{meas}}} = \frac{1}{\mu_{\text{latt}}} + \frac{1}{\mu_{\text{imp}}}. \quad (11)$$

It is certain now that only the lattice scattering generates $1/f$ noise, whereas the impurity scattering has no appreciable contribution to the noise. In order to obtain simple relations we start by assuming $\Delta\mu_{\text{imp}} = 0$. Later we shall introduce a small $\Delta\mu_{\text{imp}} > 0$ and discuss the consequences thereof. From (11) it follows that

$$\Delta\left(\frac{1}{\mu_{\text{meas}}}\right) = \Delta\left(\frac{1}{\mu_{\text{latt}}}\right) \quad (12)$$

$$\alpha_{\text{meas}} = \left(\frac{\mu_{\text{meas}}}{\mu_{\text{latt}}}\right)^2 \alpha_{\text{latt}} \quad (13)$$

where α_{meas} and α_{latt} are defined by relations corresponding to (7). From noise measurements on a series of samples with different doping, and thus different contributions of μ_{imp} , we find a straight line in a plot of $\log \alpha_{\text{meas}}$ versus $\log \mu_{\text{meas}}$. According to (13) the slope has the value 2. Fig. 1 shows how extrapolation to μ_{latt} yields the value of α_{latt} . This situation was found in all cases studied. Plots like Fig. 1—even if the slope is not exactly 2 due to the approximations in (11)—definitely prove that, in the samples investigated, the $1/f$ noise is mobility noise.

We will now discuss the situation in which there is $1/f$ noise, both in the lattice scattering and in the impurity scattering. From Matthiessen's rule we obtain

$$\Delta\left(\frac{1}{\mu_{\text{meas}}}\right) = \Delta\left(\frac{1}{\mu_{\text{latt}}}\right) + \Delta\left(\frac{1}{\mu_{\text{imp}}}\right). \quad (14)$$

From which follows

$$\alpha_{\text{meas}} = \left(\frac{\mu_{\text{meas}}}{\mu_{\text{latt}}}\right)^2 \alpha_{\text{latt}} + \left(\frac{\mu_{\text{meas}}}{\mu_{\text{imp}}}\right)^2 \alpha_{\text{imp}} \quad (15)$$

assuming that

$$\langle \Delta\mu_{\text{latt}} \cdot \Delta\mu_{\text{imp}} \rangle = 0. \quad (16)$$

The plot of $\log \alpha_{\text{meas}}$ versus $\log \mu_{\text{meas}}$ now is somewhat more complicated than Fig. 1. If the term $(\mu_{\text{meas}}/\mu_{\text{latt}})^2 \alpha_{\text{latt}}$ dominates in (15) we have the situation described by (12) and (13). This corresponds to the line with slope +2 in Fig. 2: the points a to h . If the term $(\mu_{\text{meas}}/\mu_{\text{imp}})^2 \alpha_{\text{imp}}$ dominates in (15) we have a situation where $\mu_{\text{meas}} \simeq \mu_{\text{imp}}$, so that $\alpha_{\text{meas}} \simeq \alpha_{\text{imp}}$. The noise, characterized by α_{imp} is proportional to the number of impurity centers, which in this situation is inversely proportional to $\mu_{\text{imp}} \simeq \mu_{\text{meas}}$.

$$\alpha_{\text{meas}} \simeq \alpha_{\text{imp}} \propto \mu_{\text{imp}}^{-1} \simeq \mu_{\text{meas}}^{-1}. \quad (17)$$

We find a line with slope -1 in the plot of $\log \alpha_{\text{meas}}$ versus $\log \mu_{\text{meas}}$. These are the points h to j . Fig. 2(b) gives the general situation at a constant temperature T_0 . In all situations investigated only the right hand side of the figure, with the

Fig. 2. (a) $\log \mu_{\text{meas}}$ versus $\log T$. The impurity scattering increases by equal factors in the series of samples a to j . (b) $\log \alpha_{\text{meas}}$ versus $\log \mu_{\text{meas}}$ at $T = T_0$. The noise of the samples d to h is determined by α_{latt} although $\mu_{\text{meas}} \approx \mu_{\text{imp}}$.

slope +2, was observed. It is the familiar plot of $\log \alpha$ versus $\log \mu$.

Matthiessen's rule is only an approximation. Therefore, the results for α_{meas} are also approximations. This does not raise a serious problem. We must distinguish between slopes that are close to -1 and $+2$. These values are so far apart that the distinction between lattice scattering and impurity scattering is always possible. Whether Tacano [24] is right in interpreting his value $\alpha_{\text{meas}} = 3 \times 10^{-8}$ as the value of α_{imp} of GaAs, depends on the branch his point is on. He assumes it is like point j in Fig. 2. However, if this value corresponds to point g , the same value $\alpha_{\text{meas}} = 3 \times 10^{-8}$ then points to $\alpha_{\text{latt}} \approx 5 \times 10^{-6}$, which is quite a normal value in GaAs at 50 K. From values of α_{meas} of samples with less or with more impurity scattering, it can be decided whether the samples are on the branch with slope -1 , in which case Tacano is right, or on the branch with slope $+2$.

In the case of number fluctuations, the following situations occur:

- α is proportional to 'GR centers' which create a $1/f$ spectrum, and which do not scatter electrons: $\alpha_{\text{meas}} \propto \mu_{\text{meas}}^0$.
- α is proportional to centers that also are scatterers of electrons: $\alpha \propto \mu_{\text{imp}}^{-1}$. If $\mu_{\text{meas}} \approx \mu_{\text{imp}}$: $\alpha_{\text{meas}} \propto \mu_{\text{meas}}^{-1}$.
- like b , but now with $\mu_{\text{meas}} \approx \mu_{\text{latt}}$: $\alpha_{\text{meas}} \propto \mu_{\text{imp}}^{-1} \propto \mu_{\text{meas}}^{-k}$, where $k \gg 1$.

Number fluctuations will always lead to negative slopes in plots of $\log \alpha$ versus $\log \mu$; the slope might be close to zero.

Above, we have presented experimental evidence of the fact that lattice scattering is the source of $1/f$ noise. This evidence came exclusively from measurements of electrical noise. Evidence from other experiments than those on electrical noise would, therefore, be most welcome. In a series of optical experiments, Musha *et al.* [25]–[27] showed that when photons are scattered at acoustic lattice waves the intensity of the scattered light also exhibits $1/f$ noise. With quartz it was

found that

$$S_\phi = \langle \phi \rangle^2 8 \times 10^{-5} / f \quad (18)$$

with water:

$$S_\phi = \langle \phi \rangle^2 3 / f \quad (19)$$

where $\langle \phi \rangle$ is the mean phonon number. The essential factor is the term $1/f$; the value of the numerical constant is of less importance. It should equal $(\ln f_h / f_l)^{-1}$, where f_l and f_h are the lower and higher limits of the $1/f$ spectrum. The numerical values were calculated by assuming independent fluctuations in the modes, and using a rough estimate of the number of modes in the illuminated volume.

The consequence for electrical conductivity noise is that what is observed as mobility fluctuations of electrons are essentially number fluctuations of phonons.

IV. Δn -MODELS

All Δn models are based on the same principle: the addition of Lorentzian GR spectra with a special distribution of the relaxation times τ_i . A very wide range of τ_i values is required. A $1/f$ spectrum is obtained between the frequencies $1/\tau_2$ and $1/\tau_1$ if $\tau_1 < \tau_i < \tau_2$. Below $1/\tau_2$ the spectrum is white, above $1/\tau_1$ the spectral density is proportional to f^{-2} . We use a normalized distribution function $g(\tau_i)$:

$$g(\tau_i) = 0 \quad \text{for} \quad \tau_i < \tau_1 \quad (20)$$

$$g(\tau_i) = \frac{1}{\ln \tau_2 / \tau_1} \frac{1}{\tau_i} \quad \text{for} \quad \tau_1 < \tau_i < \tau_2 \quad (21)$$

$$g(\tau_i) = 0 \quad \text{for} \quad \tau_2 < \tau_i \quad (22)$$

$$\begin{aligned} S_N &= \overline{(\Delta N)^2} \int_0^\infty g(\tau_i) \frac{4\tau_i}{1 + \omega^2 \tau_i^2} d\tau_i \\ &= \overline{(\Delta N)^2} \frac{4}{\ln \tau_2 / \tau_1} \int_{\tau_1}^{\tau_2} \frac{1}{\tau_i} \frac{\tau_i}{1 + \omega^2 \tau_i^2} d\tau_i \\ &= \overline{(\Delta N)^2} \frac{4}{\ln \tau_2 / \tau_1} \frac{1}{\omega} \arctan \omega \tau_i \Big|_{\tau_1}^{\tau_2} \end{aligned} \quad (23)$$

$$\omega \ll 1/\tau_2 \ll 1/\tau_1: S_N = \overline{(\Delta N)^2} \frac{1}{\ln \tau_2 / \tau_1} \cdot 4\tau_2 \quad (24)$$

$$1/\tau_2 \ll \omega \ll 1/\tau_1: S_N = \overline{(\Delta N)^2} \frac{1}{\ln \tau_2 / \tau_1} \cdot \frac{1}{f} \quad (25)$$

$$1/\tau_2 \ll 1/\tau_1 \ll \omega: S_N = \overline{(\Delta N)^2} \frac{1}{\ln \tau_2 / \tau_1} \cdot \frac{1}{\pi^2 \tau_1 f^2} \quad (26)$$

where the following approximations were used:

$$\arctan \delta \approx \delta \quad \text{and} \quad \arctan \frac{1}{\delta} = \frac{\pi}{2} - \delta. \quad (27)$$

The trap distribution (21) only leads to a $1/f$ spectrum if a necessary, but often overlooked, condition is fulfilled: there should be no transitions between traps with different τ 's, neither directly nor via the conduction band. See Fig. 3.

Fig. 3. Isolated traps yield a $1/f$ spectrum. Interacting traps yield a Lorentzian spectrum.

A. Isolated Traps

The variance $(\Delta X)^2$ of the free electrons or of all trapped electrons together is the sum of the variances of each individual kind of trap, characterized by its τ_i .

$$(\Delta X)^2 = \int_{\tau_1}^{\tau_2} g(\tau_i) (\Delta X_i)^2 d\tau_i. \quad (28)$$

Each individual spectrum is given by

$$S_I = \frac{(\Delta X_i)^2}{1 + (2\pi f \tau_i)^2} = \frac{(\Delta X)^2 g(\tau_i)}{1 + (2\pi f \tau_i)^2} d\tau_i. \quad (29)$$

The summation of these spectra leads to

$$S = \int_0^\infty S_i d\tau_i = \frac{(\Delta X)^2}{(\ln \tau_2 / \tau_1) 2\pi f} \times \int_0^\infty \frac{1}{1+x^2} dx = \frac{(\Delta X)^2}{\ln \tau_2 / \tau_1} \cdot \frac{1}{f} \quad (30)$$

in agreement with (25) and with the variance $\int_0^\infty S df$.

B. Transitions Between the Traps

A fluctuation in the number of free electrons now decays by interaction with all traps

$$-\frac{d\Delta X}{dt} = \Delta X \int_{\tau_1}^{\tau_2} g(\tau_i) \frac{1}{\tau_i} d\tau_i = \frac{\Delta X}{\ln \tau_2 / \tau_1} \int_{\tau_1}^{\tau_2} \frac{1}{\tau_i^2} d\tau_i \approx \frac{\Delta X}{\ln \tau_2 / \tau_1} \cdot \frac{1}{\tau_1} = \frac{\Delta X}{\tau_0} \quad (31)$$

where we define

$$\tau_0 \equiv \tau_1 \ln \tau_2 / \tau_1. \quad (32)$$

Thus one single Lorentzian is obtained with τ_1 close to τ_1 . The Lorentzian intersects the $1/f$ spectrum at the frequencies $f_1 = \tau_1 / 4\tau_0^2$ and $f_2 = 1/\pi^2 \tau_1$, which are a factor $2\tau_0/\pi\tau_1$ to the left and right from the characteristic frequency $f_0 = 1/2\pi\tau_0$.

Fig. 4 shows the two spectra, based on the same distribution function $g(\tau_i)$: a $1/f$ spectrum for isolated traps, and a Lorentzian for interacting traps. In this figure we used $\tau_2/\tau_1 = 5 \times 10^8 = e^{20}$, $\tau_0/\tau_1 = 20$.

Whatever $g(\tau)$ one may choose, the result of interacting traps will always be one average τ , hence a single Lorentzian.

A distribution $g(\tau) \propto 1/\tau$ is easily realized over a wide range of τ values, if τ exponentially depends on a quantity that is homogeneously distributed over a limited range.

Fig. 4. The Lorentzian and the $1/f$ spectrum following from Fig. 3. $\tau_2/\tau_1 = 5 \times 10^8 = e^{20}$ $\tau_0/\tau_1 = 20$.

For instance, in McWhorters surface model, traps are assumed to be homogeneously distributed in the oxide layer on a semiconductor. The probability $1/\tau$ of an electron in the semiconductor reaching a trap in the oxide layer by tunneling is given by

$$\tau = \tau_0 e^{x/d} \quad (33)$$

where x is the distance from the trap to the silicon-oxide interface, and d is a constant characteristic for the tunnel process.

$$g(\tau) = \frac{dN}{d\tau} = \frac{dN}{dx} \cdot \frac{dx}{d\tau} \propto \frac{1}{\tau} \quad (34)$$

N is the number of traps, dN/dx the concentration of traps which is constant.

The St. Petersburg group [28] has proposed a special model for GaAs, with a tail of states below the conduction band. The density of states in the tail is assumed to be exponential

$$N(E) = N(0) e^{-E/E^*} \quad (35)$$

where E is the distance of the state to the bottom of the band. For the relaxation time of the state they assume

$$\tau(E) = \tau(0) e^{-E/kT}. \quad (36)$$

The result is again $g(\tau) \propto 1/\tau$.

The required distribution $g(\tau) \propto 1/\tau$ can be obtained with processes that are thermally activated. If E_i is homogeneously distributed between E_l and E_h , and if $g(E)$ is zero outside this interval, then an exact $1/f$ spectrum is obtained at frequencies f between

$$\frac{1}{\tau_h} < 2\pi f < \frac{1}{\tau_l}. \quad (37)$$

In the Dutta Horn model [29], [30], $g(E)$ need not be a constant. A peak of E values a few kT wide is good enough

to produce a $1/f$ -like spectrum: $f^{-\gamma}$ with $\gamma = 1 \pm 0.3$. The slope will not be constant over the whole frequency range, and there will be a relation between slope and temperature dependence of the spectral power:

$$\gamma(\omega, T) = +1 - \frac{1}{\ln(\omega\tau_0)} \left[\frac{d \ln S(\omega, T)}{d \ln T} - 1 \right]. \quad (38)$$

where $\tau_0 \sim 10^{-14}$ s, an attempt time in the order of an inverse phonon frequency.

The essence of the Dutta Horn model is that a wide range of τ 's results from a rather narrow peak of activation energies. The width of the peak is determined by the disorder in the crystal. Our question now is: "Is this of interest for semiconductors at room temperature?"

In applying the model directly to generation recombination noise the activation energies of the traps will be 0.3 eV at most. The width of the peak could then be in the order of 0.03 eV. Hence, $\Delta E/kT$ is of the order 1. So there is no appreciable frequency range in which a $1/f$ spectrum can be observed. The Dutta Horn model is of little interest to number fluctuations at room temperature, but it can be applied to mobility fluctuations (to be discussed in the next section). There we need mobile lattice defects. The movement of lattice atoms requires activation energies in the order of magnitude of binding energies being 1 or 2 eV. A high degree of disorder may give a spread in the activation energy of some 10%–20%. Thus at room temperature $\Delta E/kT$ is of the order of 10, which yields $\tau_h/\tau_l \simeq 10^5$. The resulting $1/f$ spectrum of the electron mobility could then be observed in a frequency range of 5 dec. The Dutta Horn model can explain mobility noise, certainly at low temperatures.

V. $\Delta\mu$ -MODELS

We shall present two theoretical models for mobility $1/f$ noise: 1) local interference noise, 2) quantum $1/f$ noise. No critical discussion of the theories will be attempted; the emphasis is on results which can be used in a discussion of the noise of devices.

A. Local Interference Noise

This is one of the three cases where the Dutta Horn model is applied to mobile defects that act as scattering centers for the electrons [31]. The local interference model has been very successful in the study of noise in metals, especially in disordered metal films [32], [33]. Here our problem is whether it can be of interest for semiconductors at room temperature. We shall mainly be guided by Giordano's review [32].

The principle can be sketched as follows. An electron returns to its original position after a random walk during which it has been scattered by several scattering centers, in this case lattice defects. Each scattering event gives a phase shift. The electron arrives at the original position again with a certain phase shift in its wave function. If it had travelled the same path, but in the opposite direction, its final phase shift would have been the same as for the original direction. So there is constructive interference: the electron density at the original position is higher than for two uncorrelated functions.

Now the conductance between A and B is seen as a summation of all possible paths from A to B , via all scattering centers. The phase is preserved over a limited distance L_ϕ . In the universal conductance fluctuation model (UCF), the multiple scattering events of all defects in L_ϕ^3 contribute to the interference. After a defect has moved to a different position, the conductance is different, which is interpreted as mobility noise. The defects have somewhat different activation energies for jumping, and therefore, different τ values. The summation of the individual Lorentzians yields a $1/f$ spectrum, according to the Dutta Horn model. The UCF noise is found in a crystal with a high degree of disorder at very low temperatures.

The local interference model (LI) applies to electron waves singly scattered by a few neighboring defects. A special case of LI is the two-level system (TLS), where the scatterer moves from one position to an energetically equivalent second position, by tunneling through an energy barrier. Also in the LI model, the defects move with nearly the same activation energy, giving a $1/f$ spectrum by summation of Lorentzians. The LI model predicts $1/f$ noise at room temperature in weakly disordered metals.

One might think that the degree of disorder required is not to be found in nearly perfect epitaxial semiconductor films. Even though this may be true, it cannot be used as an objection against the LI model. The noise intensity α , is proportional to nn_{md} , where n is the electron density and n_{md} the density of the mobile defects ((21) in [32]). In metals we find, therefore, $\alpha \propto nn_{md} \propto An_{md}$, where A is the number of atoms per cm^3 . In semiconductors we find α proportional to n , when we investigate differently doped samples made from the same host material, with the same n_{md} in all samples. So there is no problem with the low value of n_{md}/A in high-quality semiconductors. The problem is rather that α would depend on n , contrary to all experimental evidence. LI seems not to apply to semiconductors.

A second argument against LI is that in semiconductors the exponent of the spectrum is 1.0 not $1 \pm \Delta$, as would result from the use of the Dutta Horn procedure in the local interference model. We know of one interesting example where the local interference model might apply to semiconductors: proton irradiated GaAs at low temperature ($T < 150$ K). Ren found a practically temperature independent noise, proportional to the radiation dose. There is a small peak in $\ln \alpha$ versus $1/T$, agreeing with the slope γ , which is not exactly -1 . Here (38) holds [34]. The temperatures of the peaks correspond to 0.35 eV.

Irradiation of samples that were originally doped with different donor concentrations show that this is mobility noise, since $\alpha \propto \mu_{meas}^2$ [35]. However, the quadratic dependence is characteristic of lattice scattering, whereas the local interference model is based on impurity scattering.

B. Quantum $1/f$ Noise

All three models UCF, LI, and TLS, deal with interference of waves scattered at many centers. When the spatial arrangement of the centers changes, we observe a change in the conductance, noise. Handel's model is more general: there

TABLE I

α in 10^{-9}	Si			GaAs
300 K	[39]	[40]	[41]	[39]
acoust. phonon	3	6		30
polar opt. phonon	—	—		30
intervalley	1200	300-3000	20-50	—
impurity	2-5	70	3	50-100

are $1/f$ fluctuations in each scattering event at each individual scattering center [36]. In an excellent review paper [37] van Vliet does away with many later additions of the original model, but the essential idea still stands: interference between the Bremsstrahlung and non-Bremsstrahlung part of the electron wave function.

In the scattering process a low-frequency photon is absorbed or emitted. The wave length of such a photon is much longer than the dimensions of the samples and of Faraday cages. The question is: can such photons be present or develop in this limited space? This is the so-called cage effect, which is not accepted as a serious problem by van Vliet [38]. This may be correct, but then there is no way of coming to grips experimentally with these photons. "They are lost to the universe." The model is so general that there are no specific features that lead themselves to experimental confirmation. Due to this general nature and because of the most characteristic participants—the low-frequency photons—cannot be studied, nothing else is left to us than to compare numerical results of model and experiments. Handel's model predicts the following α values (see Table I).

Handel cites some experimental α values to support the theoretical results. All experimental values, but one, are derived from noise studies of devices. The exception is Bisschop's work on polysilicon. His values $10^{-9} - 10^{-8}$ are, however, not α values at all [42].

Comparison of the theoretical values with the experimental values, as shown in Fig. 5, leads to the conclusion that the experimental results do not support Handel's theory. It could very well be that the theoretical model correctly predicts some kind of $1/f$ noise, but then this type of $1/f$ noise is different from the observed noise with a much higher α .

VI. EMPIRICAL VALUES

In proposing a model for the $1/f$ noise in devices, two kinds of assumptions for the sources must be made. These are assumptions about 1) their physical nature: Δn or $\Delta \mu$, isolated or interacting traps, bulk or surface states, etc., 2) the numerical value of α (when mobility fluctuations are considered).

Because of the latter reason we present experimental values of α here in Fig. 5 taken from literature. Only results for semiconductors, homogeneous samples and room temperature are included. We did not reject any data that do not fit in the general picture or that run against our own ideas about what α should be.

Open symbols are used for α_{meas} , whereas black symbols are used for α_{latt} . A number next to a symbol refers to the

Fig. 5. Experimental values of α_{meas} and α_{latt} of several semiconductors, measured on homogeneous samples at 300 K. The numbers refer to the list of references.

original literature, unless the value is included in an earlier survey [9], [10] and [43]. If no number is given at a point for α_{latt} , it means that α_{latt} was calculated by us from α_{meas} given by the original author.

Some of the Si data are much older than the n -GaAs data. Many GaAs data stem from modern epitaxial material. Today we are much better informed on n -GaAs than on Si. This is largely due to the work of Ren [44], [45] on epitaxial n -GaAs, where a large series of samples with the same geometry but different doping levels and different scattering mechanisms were investigated at different temperatures. All data could be summarized in one single expression

$$\alpha_{\text{latt}} = 0.1 \exp[-0.13 \text{ eV/kT}] + 7 \times 10^{-5}. \quad (39)$$

A similar study on Si is badly needed. (This study cannot be expected from the Eindhoven group, since we concentrate on III-V compounds in accordance with national science policy.) Fig. 5 shows that α_{latt} values are in the range of 10^{-5} to 10^{-3} . α_{meas} can be 10 times lower: α_{meas} is in the range of 10^{-6} to 10^{-3} . If we now have to name one single value, that can be said to be reasonably representative of α_{latt} in semiconductors at room temperature, then it is $\alpha = 10^{-4}$ instead of the historical value 2×10^{-3} of 25 years ago.

In many publications it is stated—often triumphantly—that the low values of α , which are reported there, prove the high quality of the material used by the authors. This is not necessarily correct when α_{meas} is considered. The value of α_{meas} can be low for two reasons [43]: 1) α_{latt} is low, 2) $\mu_{\text{meas}} < \mu_{\text{latt}}$.

The value of α_{meas} is low if scattering mechanisms other than lattice scattering prevail. The factor $(\mu_{\text{meas}}/\mu_{\text{latt}})^2$ in (13) then is smaller than 1, and will give a low value of α_{meas} , even when α_{latt} is not low. Only if α_{latt} itself is low, it can safely be concluded that the crystal lattice is perfect.

Damaging the crystal by mechanical stress or by irradiation strongly increases the $1/f$ noise. The electron concentration and the mobility hardly change; nevertheless the noise increases by orders of magnitude. The first explanation

that comes to mind is that the defects act as generation-recombination centers which in some, as yet unexplained, way generate $1/f$ noise. If this is correct then the induced noise is a fluctuation in the number of free carriers. However, it might also be possible that the defects act as scattering centers. If they are mobile, they will generate $1/f$ noise according to the local interference model. Therefore, one would like to see further investigations of the induced noise in damaged material, e.g., a plot of $\log \alpha_{\text{induced}}$ versus $\log \mu_{\text{meas}}$ (like Fig. 1), because that would decide whether the induced noise is mobility noise or number noise. In case of mobility noise it is important to distinguish between impurity scattering—agreeing with the LI model—and lattice scattering, as has possibly been found with proton-irradiated GaAs [35].

The relation between $1/f$ noise and damage has been critically reviewed in an extensive review by D'yakonova, Levinstein, and Rumyantsev [28]. The model favored by the authors is that the defects create the states in the tail below the conduction band. There is experimental support for this model from measurements of photo conductivity.

Papers dealing with noise and damage, that appeared after this survey, follow the lines of thinking of the survey [46]–[52]. It is immediately assumed by all authors—except one—that the induced noise is number noise. Based on this assumption some model for the generation-recombination centers is then presented without experimental evidence confirming the number fluctuations and excluding mobility fluctuations. The exception is Ren [35] who plotted α_{meas} versus μ_{meas} of the $1/f$ noise induced by proton irradiation of GaAs. He found that the noise was mobility noise.

VII. CONCLUSION

- 1) In all semiconductors there always is mobility $1/f$ noise with an α value of about 10^{-4} . Other types of $1/f$ noise may be present and may dominate the mobility noise.
- 2)

$$\alpha_{\text{meas}} = \left(\frac{\mu_{\text{meas}}}{\mu_{\text{latt}}} \right)^2 \alpha_{\text{latt}}$$

where α_{meas} directly follows from the empirical relation (7) and α_{latt} is the value that would have been found if lattice scattering only were present. This means that the lattice scattering is the origin of the mobility $1/f$ noise.

- 3) Damaging the crystal increases the $1/f$ noise considerably, whereas the mobility hardly decreases.
- 4) Each of the two values, α_{latt} and α_{meas} , has its own field of application. We need α_{meas} if we want to propose a noise model of a device. We need α_{latt} in comparisons with theoretical predictions and in assessments of the quality of semiconductor material.

REFERENCES

- [1] K. M. van Vliet and J. R. Fasset, "Fluctuations due to electronic transitions and transport in solids," in *Fluctuation Phenomena in Solids*, R. E. Burgess, Ed. New York: Academic, 1965, p. 267.
- [2] A. D. van Rheenen, G. Bosman, and C. M. van Vliet, "Decomposition of generation-recombination noise spectra in separate Lorentzians," *Solid State Electron.*, vol. 28, p. 457, 1985.
- [3] F. N. Hooge and L. Ren, "On the generation-recombination noise," *Physica*, vol. B191, p. 220, 1993.
- [4] F. N. Hooge and L. Ren, "On the variances of generation-recombination noise in a three-level system," *Physica B*, vol. B193, p. 31, 1994.
- [5] T. G. M. Kleinpenning and A. H. de Kuijper, "Relation between variance and sample duration of $1/f$ noise signals," *J. Appl. Physics*, vol. 63, p. 43, 1988.
- [6] *Proc. 7th Int. Conf. on Noise in Physical Systems, and the 3rd Int. Conf. on 1/f Noise*, Montpellier, France, May 1983, M. Savelli, G. Lecocq, and J. P. Nougier, Eds. Amsterdam: North-Holland, 1983.
- [7] *Proc. 8th Int. Conf. on Noise in Physical Systems, and the 4th Int. Conf. on 1/f Noise*, Rome, Sept. 1985; A. D'Amico and P. Mazzetti, Eds. Amsterdam: North-Holland, 1986.
- [8] *Proc. 9th Int. Conf. on Noise in Physical Systems*, Montréal, May 1987, C. M. van Vliet, Ed. Singapore: World Scientific, 1987.
- [9] *Proc. 10th Int. Conf. on Noise in Physical Systems*, Budapest, Aug. 1989, A. Ambrózy, Ed. Budapest: Akadémiai Kiadó, 1990.
- [10] *Proc. 11th Int. Conf. on Noise in Physical Systems and 1/f Fluctuations*, Kyoto, Nov. 1991, T. Musha, S. Sato, and M. Yamamoto, Eds. Tokyo: Ohmsha Ltd., 1991.
- [11] *AIP Conf. Proc.*, vol. 285, "Noise in Physical Systems and 1/f Fluctuations," St. Louis, August 1993, P. H. Handel and A. L. Chung, Eds. New York: AIP Press, 1993.
- [12] F. N. Hooge, " $1/f$ noise is no surface effect," *Phys. Lett.*, vol. 29A, p. 139, 1969.
- [13] A. L. McWhorter, " $1/f$ noise and related surface effects in germanium," Ph.D. dissertation, MIT, Cambridge, MA, 1955.
- [14] L. K. J. Vandamme, "Bulk and surface $1/f$ noise," *IEEE Trans. Electron Devices*, vol. 36, p. 987, 1989.
- [15] A. M. H. Hoppenbrouwers and F. N. Hooge, " $1/f$ noise of spreading resistances," *Philips Res. Rep.*, vol. 25, p. 69, 1970.
- [16] F. N. Hooge and A. M. H. Hoppenbrouwers, " $1/f$ noise in continuous thin gold films," *Physica*, vol. 45, p. 386, 1969.
- [17] F. N. Hooge, "On expressions for $1/f$ noise in mobility," *Physica*, vol. B114, p. 391, 1982.
- [18] M. B. Weissman, " $1/f$ noise and other slow, non-exponential kinetics in condensed matter," *Rev. Modern Phys.*, vol. 60, p. 537, 1988.
- [19] F. N. Hooge, "The relation between $1/f$ noise and number of electrons," *Physica*, vol. B162, p. 344, 1990.
- [20] T. G. M. Kleinpenning, " $1/f$ noise in p-n diodes," *Physica*, vol. B98, p. 289, 1980.
- [21] F. Hofman and R. J. J. Zijlstra, "The validity of Hooge's law for $1/f$ noise," *Solid State Commun.*, vol. 72, p. 1163, 1989.
- [22] F. N. Hooge, T. G. M. Kleinpenning, and L. K. J. Vandamme, "Experimental studies on $1/f$ noise," *Rep. on Progress in Physics*, vol. 44, p. 479, 1981.
- [23] L. Ren and J. S. Liberis, " $1/f$ noise in the Hall voltage of epitaxial n-GaAs," *Physica*, vol. B183, p. 40, 1993.
- [24] M. Tacano, "Hooge parameter determined by impurity scattering," in [11], p. 9.
- [25] T. Musha, G. Borbély and M. Shoji, " $1/f$ phonon-number fluctuations in quartz observed by laser light scattering," *Phys. Rev. Lett.*, vol. 64, p. 2394, 1990.
- [26] T. Musha and G. Borbély, " $1/f$ fluctuations of phonon energy in water," *Jap. J. Applied Physics*, vol. 31, p. L370, 1992.
- [27] T. Musha, K. Takada, and K. Nakagawa, "Fluctuations of light intensity scattered by aqueous LiCl solution," in [11], p. 141.
- [28] N. V. D'yakonova, M. E. Levinstein, and S. L. Rumyantsev, "Nature of the bulk $1/f$ noise in GaAs and Si (review)," *Sov. Phys. Semicond.*, vol. 25, p. 1241, 1991.
- [29] P. Dutta, P. Dimon, and P. M. Horn, "Energy scales for noise processes in metals," *Phys. Rev. Lett.*, vol. 43, p. 646, 1979.
- [30] P. Dutta and P. M. Horn, "Low-frequency fluctuations in solids: $1/f$ noise," *Rev. Modern Phys.*, vol. 53, p. 497, 1981.
- [31] M. Kogan and K. E. Nagaev, "On the low-frequency current $1/f$ noise in metals," *Solid State Commun.*, vol. 49, p. 387, 1984.
- [32] N. Giordano, "Defect motion and low-frequency noise in disordered metals," *Rev. Solid State Science*, vol. 3, p. 27, 1989.
- [33] J. Pelz and J. Clarke, "Quantitative local interference, model for $1/f$ noise in metal films," *Phys. Rev. B*, vol. 36, p. 4479, 1987.
- [34] L. Ren, "Intrinsic and extrinsic $1/f$ noise sources in proton irradiated n-GaAs epitaxial layers," *J. Appl. Phys.*, vol. 74, p. 4534, 1993.
- [35] L. Ren and F. N. Hooge, "Intrinsic and extrinsic $1/f$ noise sources in irradiated n-GaAs," in [11], p. 65.
- [36] P. J. Handel, " $1/f$ noise—an infrared phenomenon," *Phys. Rev. Lett.*, vol. 34, p. 1492, 1975.
- [37] C. M. van Vliet, "A survey of results and future prospects on quantum $1/f$ noise and $1/f$ noise in general," *Solid State Electron.*, vol. 34, p. 1, 1991.

- [38] C. M. van Vliet, "Further comments on Handel's theories of quantum $1/f$ noise," *Physica*, vol. A150, p. 244, 1988.
- [39] G. S. Kousik, C. M. van Vliet, G. Bosman, and P. H. Handel, "Quantum $1/f$ noise associated with ionized impurity scattering and electron-phonon scattering in condensed matter," *Advances in Physics*, vol. 34, p. 663, 1985.
- [40] G. S. Kousik, C. M. van Vliet, G. Bosman, and H. J. Luo, "Quantum $1/f$ noise associated with intervalley scattering in non-degenerate semiconductors," *Physica Status Solidi*, vol. b154, p. 713, 1989.
- [41] P. H. Handel and T. H. Chung, "Graphical representation of quantum $1/f$ mobility fluctuation spectra in silicon," in [11], p. 176.
- [42] J. Bisschop, "Experimental study on the $1/f$ noise parameter α ," Ph.D. dissertation, Univ. Eindhoven, 1983, p. 64.
- [43] F. N. Hooge and M. Tacano, "Experimental studies of $1/f$ noise in n -GaAs," *Physica*, vol. B190, p. 145, 1993.
- [44] L. Ren and M. R. Leys, " $1/f$ noise at room temperature in n -type GaAs grown by molecular beam epitaxy," *Physica*, vol. B172, p. 319, 1991.
- [45] L. Ren and F. N. Hooge, "Temperature dependence of $1/f$ noise in epitaxial n -type GaAs," *Physica*, vol. B176, p. 209, 1992.
- [46] M. E. Levinstein and S. L. Rumyantsev, "Relaxation of the photo conductivity and $1/f$ noise in GaAs subjected to damaging compression," *Soviet Physics Semiconductors*, vol. 25, p. 97, 1991.
- [47] N. V. D'yakonova, M. E. Levinstein, and S. L. Rumyantsev, "Temperature dependence of low-frequency noise in structurally perfect GaAs and after destructive compression," *Sov. Phys. Semicond.*, vol. 25, p. 217, 1991.
- [48] I. S. Baksheev, E. A. Salkov, and B. I. Khizhnyak, " $1/f$ noise in HgCdTe converted from n - to p -type by native doping," *Solid State Commun.*, vol. 81, p. 781, 1992.
- [49] I. S. Bakshi, L. A. Karachevtseva, A. V. Lyubchenko, V. A. Petryakov, E. A. Salkov, and B. I. Khizhnyak, "Influence of compensating annealing on the $1/f$ noise in CdHgTe," *Soviet Phys. Semicond.*, vol. 26, p. 97, 1992.
- [50] G. M. Gusinskii, N. V. D'yakonova, M. E. Levinstein, and S. L. Rumyantsev, "Noise of the $1/f$ type and electrical and photoelectric properties of GaAs bombarded with high-energy ions," *Sov. Phys. Semicond.*, vol. 26, p. 307, 1992.
- [51] Yu. M. Galperin and V. I. Kozub, "Disorder induced flicker noise in small structures, Normal and super conducting state," in [11], p. 39.
- [52] N. V. D'yakonova, M. E. Levinstein, and S. L. Rumyantsev, "Nature of the bulk $1/f$ noise in GaAs and Si," in [11], p. 593.
- [53] W. J. Zheng and X. C. Zhu, "The contribution of electrode to $1/f$ noise in SPRITE LWIR detectors," in [11], p. 448.
- [54] W. J. Zheng and X. C. Zhu, "Experimental studies on low frequency noise of HgCdTe photoconductors," *Infrared Physics*, vol. 33, p. 27, 1992.
- [55] M. de Murcia, F. Pascal, G. Lecoy, and L. K. J. Vandamme, "Excess noise in AlGaAs epitaxial layers," in [11], p. 31.
- [56] S. Jarrix, C. Delseny, F. Pascal, G. Lecoy, and J. Dangla, "Low frequency noise in p^+ -GaAs resistors," *Electronic Lett.*, vol. 29, p. 1571, 1993.

F. N. Hooge was born in Amsterdam in 1930. He studied chemistry at the University of Amsterdam, where he received the Doctor's degree in 1951.

He then joined Philips Research Laboratory in Eindhoven to work on semiconductors, and since 1968 he has been studying $1/f$ noise. In 1971 he was appointed Professor of electronic materials at the Department of Electrical Engineering at Eindhoven University of Technology (EUT). From 1983 to 1985 he was Dean of the department and from 1985 to 1988 was Rector Magnificus of EUT.

Dr. Hooge received the doctorate honoris causa from Strathclyde University, Scotland, in 1989.