Hydroquinone oxidation and p-benzoquinone reduction at polypyrrole and poly-N-methylpyrrole electrodes

Citation for published version (APA):

Jakobs, R. C. M., Janssen, L. J. J., & Barendrecht, E. (1985). Hydroquinone oxidation and p-benzoquinone reduction at polypyrrole and poly-N-methylpyrrole electrodes. *Electrochimica Acta*, 30(10), 1313-1321.
[https://doi.org/10.1016/0013-4686\(85\)85008-8](https://doi.org/10.1016/0013-4686(85)85008-8)

DOI:

[10.1016/0013-4686\(85\)85008-8](https://doi.org/10.1016/0013-4686(85)85008-8)

Document status and date:

Published: 01/01/1985

Document Version:

Publisher's PDF, also known as Version of Record (includes final page, issue and volume numbers)

Please check the document version of this publication:

- A submitted manuscript is the version of the article upon submission and before peer-review. There can be important differences between the submitted version and the official published version of record. People interested in the research are advised to contact the author for the final version of the publication, or visit the DOI to the publisher's website.
- The final author version and the galley proof are versions of the publication after peer review.
- The final published version features the final layout of the paper including the volume, issue and page numbers.

[Link to publication](#)

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal.

If the publication is distributed under the terms of Article 25fa of the Dutch Copyright Act, indicated by the "Taverne" license above, please follow below link for the End User Agreement:

www.tue.nl/taverne

Take down policy

If you believe that this document breaches copyright please contact us at:

openaccess@tue.nl

providing details and we will investigate your claim.

HYDROQUINONE OXIDATION AND *p*-BENZOQUINONE REDUCTION AT POLYPYRROLE AND POLY-*N*-METHYLPYRROLE ELECTRODES

R. C. M. JAKOBS, L. J. J. JANSSEN and E. BARENDRECHT

Laboratory for Electrochemistry, Department of Chemistry, Eindhoven University of Technology, P.O. Box 513, 5600 MB Eindhoven, The Netherlands

(Received 29 January 1985; in revised form 12 March 1985)

Abstract—The oxidation of hydroquinone and the reduction of *p*-benzoquinone in aqueous solution is studied at polypyrrole electrode and at a poly-*N*-methylpyrrole electrode. It is found that both types of electrodes exhibit a pronounced electrocatalytical effect. The quinone/hydroquinone redox couple, which is irreversible at an uncovered gold electrode, initially is practically reversible when a polypyrrole-covered gold electrode is used. However, after some time, an aging effect occurs, which includes an increasing inhibition of the electrode reaction by quinone-like species, immobilized at the polymer surface. Experiments with a rotating disk electrode show that the redox reactions of quinone and hydroquinone occur mainly at the interface polypyrrole/electrolyte; in this case, the polymer acts as both an electrocatalyst and an electron conductor.

NOMENCLATURE

A	area of electrode surface [m^2]
c	concentration [M , mol m^{-3}]
D	diffusion coefficient [$\text{m}^2 \text{s}^{-1}$]
E	potential [V]
E_p	peak potential [V]
ΔE_p	peak separation [V]
$E_{p/2}$	half-peak potential [V]
F	Faraday's constant [C mol^{-1}]
f	(rotation) frequency [Hz]
i	current [A]
i_l	limiting current [A]
n	number of electrons, involved in electrode reaction
v	potential scan rate [V s^{-1}]
ν	kinematic viscosity [$\text{m}^2 \text{s}^{-1}$]

Superscripts

ad	adsorbed
s	bulk

1. INTRODUCTION

In previous papers[1, 2], a study of the reduction of molecular oxygen at the polypyrrole electrode was presented. These papers deal with the reaction of an inorganic substance at an organic polymer electrode. In order to study also the electrochemical reaction of an organic compound at the organic polypyrrole electrode, the quinone–hydroquinone system was used[3].

The oxidation of hydroquinone (or 1,4-dihydroxybenzene) and the reduction of 1,4-benzoquinone are well known redox reactions in organic electrochemistry[4].

The mechanism of these reactions in protic media, such as the electrolytes used in this study, has been established by Vetter in 1952[5]. Many publications deal with the quinone/hydroquinone redox system and some of these publications concern the polypyrrole electrode, although exclusively in aprotic elec-

trolyte[6,7]. The measurements, carried out in a H_2SO_4 -containing electrolyte and presented here, do not enable the determination of the mechanism of the hydroquinone oxidation and the quinone reduction at the polypyrrole electrode. However, the results lead to (sometimes speculative) conclusions that could contribute to the elucidation of this mechanism.

2. EXPERIMENTAL

The experimental set-up for the formation of the polypyrrole and poly-*N*-methylpyrrole films was the same as described in an earlier work[8]. Unless otherwise stated, the formation electrolyte contained 0.1 M LiClO_4 (Fluka), 1 vol% pyrrole or 1 vol% *N*-methylpyrrole (Aldrich) and 0.5 vol% distilled water in acetonitrile (Janssen Chimica). The working electrode was a gold disk ($A = 5.15 \times 10^{-5} \text{m}^2$), which was polished with 0.3 μm alumina before each deposition of the polymer film.

The cell in which the measurements were carried out was a thermostatted three-electrode cell with a saturated calomel electrode (*sce*) as a reference electrode and platinum foil as a counter electrode. The reference electrode was provided with a Luggin capillary and the counter electrode was separated from the working electrode compartment by a porous glass filter. The working electrode was connected to the disk circuit of a bipotentiostat (Tacussel) and its potential was controlled by a Wenking Pos 73 scan generator. After the deposition of the polymer film at a constant potential of 1.20 V *vs sce*, the electrode was taken out of the formation electrolyte and the excess of electrolyte was removed by spinning the electrode in ambient air. Then the electrode was dried by free standing in ambient air for about 30 min before it was transferred to the measurement cell. The charge, passed during the formation of the polymer film, was always 0.6 kC m^{-2} , unless otherwise stated.

The measurements were carried out in three dif-

ferent solutions, viz (1) a solution, prepared by mixing equal volumes of 1 M H_2SO_4 in water and 96% ethanol, denoted here as $\text{H}_2\text{SO}_4/\text{EtOH}$; (2) a solution, prepared by mixing equal volumes of 1 M H_2SO_4 in water and acetonitrile, denoted as $\text{H}_2\text{SO}_4/\text{CH}_3\text{CN}$ and; (3) 0.5 M H_2SO_4 in water, denoted as H_2SO_4 . The solutions were prepared at 293 K. The concentration of the electroactive compound, i.e. 1,4-dihydroxybenzene (hydroquinone, denoted as H_2Q) or 1,4-benzoquinone (denoted as Q), was 5×10^{-3} M in each solution.

All the measurements were carried out at 298 K and 100 kPa, unless otherwise mentioned. All potentials are given against the sce.

The diffusion coefficient of Q, $D(\text{Q})$, at 298 K in $\text{H}_2\text{SO}_4/\text{EtOH}$ was determined by means of polarography. Using the averaged Ilkovich equation[9], it was found that $D(\text{Q}) = 2.3 \times 10^{-10} \text{ m}^2 \text{ s}^{-1}$ at 298 K in $\text{H}_2\text{SO}_4/\text{EtOH}$. The kinematic viscosity, ν , of the $\text{H}_2\text{SO}_4/\text{EtOH}$ solution was calculated from literature data. From the densities at 293 K of 1 M H_2SO_4 [10] and EtOH[11], the composition-by-weight of the electrolyte was calculated to be 43% in EtOH. The extrapolated density of a 43% EtOH/57% H_2O mixture at 298 K is 921 kg m^{-3} [12] and its extrapolated dynamic viscosity at 298 K $\eta = 2.39 \times 10^{-3} \text{ kg m}^{-1} \text{ s}^{-1}$ [13]. This gives a kinematic viscosity $\nu = 2.6 \times 10^{-6} \text{ m}^2 \text{ s}^{-1}$ at 298 K.

3. RESULTS

3.1. $\text{H}_2\text{SO}_4/\text{ethanol}$ electrolyte

The effect of covering a gold disk with a polypyrrole (PP) or a poly-N-methylpyrrole (PMP) film on the cyclic voltammogram in H_2Q -containing $\text{H}_2\text{SO}_4/\text{EtOH}$ electrolyte is shown in Fig. 1. The somewhat broadened peaks with $\Delta E_p \approx 200 \text{ mV}$, measured for the uncovered gold (Au) electrode, turn into narrower peaks when a PP- or PMP-covered electrode is used. For the PP(Au) electrode $\Delta E_p \approx 50 \text{ mV}$, $E_p - E_{p/2} = 35 \text{ mV}$ for the anodic peak and

Fig. 1. Cyclic voltammogram in $\text{H}_2\text{SO}_4/\text{EtOH} + 5.0 \text{ mM H}_2\text{Q}$; $\nu = 0.010 \text{ V s}^{-1}$, $f = 0 \text{ Hz}$. Electrode aged 10 min. — uncovered Au disk; --- PP(Au) electrode; ... PMP(Au) electrode.

$E_p - E_{p/2} = 40 \text{ mV}$ for the cathodic peak. For a PMP(Au) electrode $\Delta E_p = 80 \text{ mV}$, $E_p - E_{p/2} = 45 \text{ mV}$ for the anodic peak and $E_p - E_{p/2} = 50 \text{ mV}$ for the cathodic peak.

For a PP film on a platinum disk, a similar effect has been found as that for the gold disk. However, the cyclic voltammogram for a platinum (Pt) electrode is obscured by a background current from the oxidation of ethanol or contaminants present in the solution, at $E > 0.6 \text{ V}$. To avoid interference with the studied redox reaction, from now, only gold substrates were used.

A plot of the limiting current I_l vs $\sqrt{f}$ for H_2Q oxidation (Fig. 2) shows that the slope of the straight curve is independent of the polypyrrole layer thickness and that I_l increases slightly with increasing layer thickness. The data in Fig. 2 are not corrected for background signals. It is likely that the increase of I_l for thicker polymer films is caused by oxidation of the polymer film, for which the current increases with increasing amount of polymer. A plot of $-I_l$ vs $\sqrt{f}$ for reduction of Q shows nearly the same effects: practically parallel straight curves and increase of $-I_l$ with increasing polymer layer thickness. For formation potentials between 0.9 and 1.2 V, it has been found that there is no effect of the formation potential on the $I_l/\sqrt{f}$ curve for a PP electrode on which H_2Q is oxidized or Q is reduced.

The slope S_1 of a $-I_l$ vs $\sqrt{f}$ plot for the uncovered Au electrode in Q-containing solution is equal to $2.63 \times 10^{-4} \text{ A s}^{1/2}$. Using:

$$n = \frac{S}{0.62 A F c^s [D(\text{Q})]^{2/3} \nu^{1/6} \sqrt{2\pi}} \quad (1)$$

with a disk surface area $A = 5.15 \times 10^{-5} \text{ m}^2$, $D(\text{Q}) = 2.3 \times 10^{-10} \text{ m}^2 \text{ s}^{-1}$, $\nu = 2.6 \times 10^{-6} \text{ m}^2 \text{ s}^{-1}$ and $c^s = 5.0 \text{ mol m}^{-3}$, this gives $n = 2.1$.

Since the diffusion coefficient of H_2Q , $D(\text{H}_2\text{Q})$,

Fig. 2. I_l vs $\sqrt{f}$ in $\text{H}_2\text{SO}_4/\text{EtOH} + 5.0 \text{ mM H}_2\text{Q}$. Electrodes aged 10 min. Uncovered Au disk (x); PP(Au) electrodes with formation charges: 0.30 kC m^{-2} (o), 0.60 kC m^{-2} (Δ) and 1.20 kC m^{-2} ($\bullet$).

could not be determined polarographically, $D(\text{H}_2\text{Q})$ is determined from the results of Fig. 2. The slope S_2 of the I_1 vs $\sqrt{f}$ plot for the uncovered Au electrode in Fig. 2 is $2.90 \times 10^{-4} \text{ A s}^{1/2}$. Taking $n = 2$ for both reduction of Q and oxidation of H_2Q and using Equation (1), it follows that $D(\text{H}_2\text{Q})/D(\text{Q}) = (S_2/S_1)^{3/2}$. From $D(\text{Q})$ and the experimental slopes S_1 and S_2 it follows that $D(\text{H}_2\text{Q}) = 2.7 \times 10^{-10} \text{ m}^2 \text{ s}^{-1}$.

From Fig. 2 and a plot of $-I_1$ vs $\sqrt{f}$ for the reduction of Q, it is concluded that the oxidation of 1,4-dihydroxybenzene and the reduction of 1,4-benzoquinone in $\text{H}_2\text{SO}_4/\text{EtOH}$ electrolyte takes place at the interface polypyrrole/electrolyte, which means that the polypyrrole film conducts the electrons that are involved in the redox reactions.

It is likely that when the reacting solute is transported through the polymer film, a decrease in limiting current with increasing film thickness should be observed, according to a two-phase diffusion model[14].

Plots of $\log [I/(I_1 - I)]$ vs E are given in Fig. 3 for H_2Q oxidation and Q reduction at a PP(Au) electrode and at an uncovered Au electrode. The currents are not corrected for the relatively small currents due to background processes. In the figure, the slopes of the curves for the PP(Au) electrode are about equal to the slopes of the corresponding curves for the uncovered Au electrode.

Additionally, the slopes of the curves are nearly independent of the polymer layer thickness. For the PP(Au) electrode, the slope in Fig. 3 is 102 mV for the H_2Q oxidation and 130 mV for the Q reduction. To investigate the effect of aging, a PP(Au) electrode in a $\text{H}_2\text{SO}_4/\text{EtOH}$ solution containing H_2Q , and rotated with $f = 10 \text{ Hz}$, is charged with a continuous triangu-

lar potential scan between 0.0 and 0.7 V with $v = 0.010 \text{ V s}^{-1}$. After 10 min, 1 h and 2 h scanning, current/potential curves were measured at various rotation rates. Fig. 4 shows $1/I$ at $E = 0.70 \text{ V}$ as a function of $1/\sqrt{f}$. This so-called "Koutecky-Levich plot"[15] shows that during the aging period, the H_2Q oxidation reaction is increasingly limited by its kinetics, as follows from the increasing intercept of the $1/I$ vs $1/\sqrt{f}$ curve at $1/\sqrt{f} = 0$. For the Q reduction at a PP electrode, a $-1/I$ vs $1/\sqrt{f}$ plot shows the same aging effect. It appears that the magnitude of this aging effect is less for the reduction of Q than for the oxidation of H_2Q .

For the PMP(Au) electrode, the Koutecky-Levich plots for the oxidation of H_2Q and the reduction of Q show that the aging effect is larger for this electrode than for the PP electrode. For the H_2Q oxidation, for example, the aging of the electrode, already aged for 10 min, occurs with such a high rate during the measurements, that a bent curve is obtained in the $1/I$ vs $1/\sqrt{f}$ plot (the curve was measured with increasing rotation frequency). For PP electrodes it has been found that the rate of the aging process increases with increasing temperature. Uncovered Au electrodes show no aging effect. The aging of the PP and PMP electrodes during H_2Q oxidation is also illustrated by Figs 5 and 6, in which voltammograms are given at $f = 0 \text{ Hz}$ and $f = 16 \text{ Hz}$ for each electrode. Figure 5 and cyclic voltammograms in Q-containing electrolyte show that, in all cases, during the aging of the PP electrode one wave occurs in the curves at $f = 16 \text{ Hz}$. Its height decreases with increasing aging time. Figure 6 shows that for a PMP electrode in a H_2Q -containing solution two waves are observed in the sweep curve at $f = 16 \text{ Hz}$ [Fig. 6(b) and (c)]. The wave at $E < 450 \text{ mV}$ for the PMP electrode is practically independent of the aging time, while the wave at $E > 450 \text{ mV}$ decreases with increasing aging time.

The effect of water addition to the formation electrolyte on the aging of a PP(Au) electrode is

Fig. 3. $I/(I_1 - I)$ vs E for H_2Q oxidation (—) and Q reduction (---) in $\text{H}_2\text{SO}_4/\text{EtOH}$. $v = 0.010 \text{ V s}^{-1}$, $f = 64 \text{ Hz}$. Electrodes aged 10 min. Uncovered Au disk (x); PP(Au) electrodes with formation charges: 0.30 kC m^{-2} (o), 0.60 kC m^{-2} (Δ) and 1.20 kC m^{-2} ($\bullet$).

Fig. 4. $1/I$ vs $1/\sqrt{f}$ for a PP(Au) electrode in $\text{H}_2\text{SO}_4/\text{EtOH} + 5.0 \text{ mM H}_2\text{Q}$. I is the oxidation current at $E = 0.70 \text{ V}$. Aging time: 10 min (x), 1 h (o) and 2 h (Δ).

Fig. 5. Voltammograms of a PP(Au) electrode in $\text{H}_2\text{SO}_4/\text{EtOH} + 5.0 \text{ mM H}_2\text{Q}$. $\nu = 0.010 \text{ V s}^{-1}$. — $f = 0 \text{ Hz}$; ---- $f = 16 \text{ Hz}$. Aging time: 10 min (a), 1 h (b) and 2 h (c).

Fig. 6. Voltammograms of a PMP(Au) electrode in $\text{H}_2\text{SO}_4/\text{EtOH} + 5.0 \text{ mM H}_2\text{Q}$. $\nu = 0.010 \text{ V s}^{-1}$. — $f = 0 \text{ Hz}$; ---- $f = 16 \text{ Hz}$. Aging time: 10 min (a), 1 h (b) and 2 h (c).

studied for both the oxidation of H_2Q and the reduction of Q. The electrodes, rotated with $f = 10 \text{ Hz}$, were aged for 2 h by a continuous potential sweep between 0.0 and 0.70 V with $\nu = 0.01 \text{ V s}^{-1}$.

From these experiments it has been found that addition of water to the formation electrolyte retards the aging process. For example, the PP(Au) electrode, formed after addition of 5 vol % water to the formation electrolyte, shows a small aging effect for the oxidation of H_2Q and practically no aging effect for the reduction of Q.

The aging of a PP(Au) electrode is also studied at

polymer layers of varying thickness. It is found that there is no unequivocal effect of the polymer layer thickness on the aging of the PP electrode.

3.2. $\text{H}_2\text{SO}_4/\text{acetonitrile}$ electrolyte

The deposition of a PP or a PMP layer on an Au electrode has a similar effect on the cyclic voltammogram in $\text{H}_2\text{SO}_4/\text{CH}_3\text{CN}$ electrolyte as in the $\text{H}_2\text{SO}_4/\text{EtOH}$ electrolyte.

For the uncovered Au electrode in $\text{H}_2\text{SO}_4/\text{CH}_3\text{CN} + \text{H}_2\text{Q}$, the anodic and cathodic peaks are separated

with $\Delta E_p \approx 430$ mV, which is 230 mV more than in $\text{H}_2\text{SO}_4/\text{EtOH} + \text{H}_2\text{Q}$; $E_p - E_{p/2} = 45$ mV for the anodic peak and $E_p - E_{p/2} = 90$ mV for the cathodic peak. Deposition of a polypyrrole film reduces the peak separation to $\Delta E_p \approx 70$ mV for a 10 min-aged electrode and $E_p - E_{p/2}$ becomes 40 mV for the anodic peak and 45 mV for the cathodic peak. For a poly-*N*-methylpyrrole film, the peak separation is $\Delta E_p \approx 210$ mV, with $E_p - E_{p/2} = 70$ mV for the anodic peak and $E_p - E_{p/2} = 95$ mV for the cathodic peak.

Generally, the behaviour of the PP and PMP electrodes in $\text{H}_2\text{SO}_4/\text{CH}_3\text{CN}$ is analogous to the behaviour in $\text{H}_2\text{SO}_4/\text{EtOH}$ electrolyte: the H_2Q oxidation and Q reduction occurs at the polymer/electrolyte interface; there is only a small effect of the polymer layer thickness on the I vs $\sqrt{f}$ plot and the electrodes show also an aging effect. The aging of the PP electrode, however, occurs at a higher rate than in ethanolic electrolyte, whereas the aging rate for the PMP electrode is about equal in both electrolytes.

Fig. 7 shows a plot of $1/I$ vs $1/\sqrt{f}$ for the H_2Q oxidation at an uncovered Au, PP(Au) and PMP(Au) electrode after 2 h of aging. During the aging of the PP and PMP electrodes, the cyclic voltammograms of the electrodes tend increasingly to that of the uncovered Au electrode.

The magnitude of the aging effect at a PP(Au) electrode is less for the reduction of Q than for the oxidation of H_2Q . For a PMP(Au) electrode the opposite of this is found.

3.3. H_2SO_4 electrolyte

The cyclic voltammogram at an uncovered Au, a PP(Au) and a PMP(Au) electrode in H_2Q -containing 0.5 M H_2SO_4 is given in Fig. 8. For the uncovered Au electrode it appears that $\Delta E_p \approx 280$ mV, whereas for both the PP(Au) and

Fig. 8. Cyclic voltammogram in $\text{H}_2\text{SO}_4 + 5.0$ mM H_2Q . $v = 0.010$ V s $^{-1}$, $f = 0$ Hz. Electrode aged 10 min. — uncovered Au disk; ---- PP(Au) electrode; PMP(Au) electrode.

PMP(Au) electrode it is found that $\Delta E_p \approx 60$ mV and that for the anodic peak, $E_p - E_{p/2} = 35$ mV for the PP electrode and $E_p - E_{p/2} = 40$ mV for the PMP electrode. For the cathodic peak, $E_p - E_{p/2} = 40$ mV for both the PP and PMP electrode. The aging effect for the various electrodes in $\text{H}_2\text{SO}_4 + \text{H}_2\text{Q}$ electrolyte follows from Fig. 9. As for the other electrolytes, the magnitude of the aging effect is larger for the PMP electrode than for the PP electrode.

The aging effect for the uncovered Au and PP(Au) electrode in $\text{H}_2\text{SO}_4 + \text{Q}$ electrolyte is comparable to the aging effect, shown in Fig. 9. However, for a PMP(Au) electrode, the aging effect during Q reduction is considerably larger than during H_2Q oxidation. The voltammograms recorded during the aging of a

Fig. 7. $1/I$ vs $1/\sqrt{f}$ for various electrodes in $\text{H}_2\text{SO}_4/\text{CH}_3\text{CN} + 5.0$ mM H_2Q . I is the oxidation current at $E = 0.70$ V. Electrodes aged 2 h. Uncovered Au disk ($\times$); PP(Au) electrode ($\circ$); PMP(Au) electrode (Δ).

Fig. 9. $1/I$ vs $1/\sqrt{f}$ for various electrodes in $\text{H}_2\text{SO}_4 + 5.0$ mM H_2Q . I is the oxidation current at $E = 0.70$ V. Electrodes aged 2 h. Uncovered Au disk ($\times$); PP(Au) electrode ($\circ$); PMP(Au) electrode (Δ).

PP(Au) electrode in $\text{H}_2\text{SO}_4 + \text{H}_2\text{Q}$, are similar to the voltammograms in Fig. 5. The voltammograms show one wave in the curve at $f = 16$ Hz; the height of this wave decreases with increasing aging time.

The voltammograms for the PP(Au) electrode during Q reduction are given in Fig. 10. The curves in this figure exhibit an extra anodic and cathodic peak around a potential of 0 V. These extra peaks are not caused by the presence of either H_2Q or Q, but probably arise from redox reactions of the polymer film.

The aging of a PMP(Au) electrode in $\text{H}_2\text{SO}_4 + \text{H}_2\text{Q}$ is illustrated by Fig. 11. Comparing Fig. 11(a) with Figs 11(b) and (c) suggests that the not-well-shaped wave in

Fig. 11(a) actually consists of two waves, which have been split in Figs 11(b) and (c).

During the aging of the electrode, the half-wave potential $E_{1/2}$ of the second wave in the curve at $f = 16$ Hz (i.e. the wave at the most anodic potential) increases with increasing aging time, whereas the $E_{1/2}$ of the remaining first wave remains constant. The height of the second wave increases with increasing rotation frequency, while the first wave becomes increasingly independent of the rotation frequency with increasing aging time. The second wave appears as a small anodic peak in the voltammogram at $f = 0$ Hz [Figs 11(b) and 11(c)]; this small anodic peak has a small and broad cathodic counterpart [Fig. 11(c)].

Fig. 10. Voltammograms of a PP(Au) electrode in $\text{H}_2\text{SO}_4 + 5.0$ mM Q. $v = 0.010$ Vs^{-1} . — $f = 0$ Hz; ---- $f = 16$ Hz. Aging time: 10 min (a), 1 h (b) and 2 h (c).

Fig. 11. Voltammograms of a PMP(Au) electrode in $\text{H}_2\text{SO}_4 + 5.0$ mM H_2Q . $v = 0.010$ Vs^{-1} . — $f = 0$ Hz; ---- $f = 16$ Hz. Aging time: 10 min (a), 1 h (b) and 2 h (c).

Fig. 12. Voltammograms of a PMP(Au) electrode in $\text{H}_2\text{SO}_4 + 5.0 \text{ mM Q}$. $v = 0.010 \text{ V s}^{-1}$, $f = 64 \text{ Hz}$. Aging time: 30 min (a), 1 h (b) and 2 h (c). ---- in (a): electrode aged 10 min, $f = 0 \text{ Hz}$.

When Q is reduced at a PMP electrode in $0.5 \text{ M H}_2\text{SO}_4$, a rapid change of the voltammogram occurs at the beginning of the experiment. The cyclic voltammogram for a PMP(Au) electrode in $\text{H}_2\text{SO}_4 + \text{Q}$, initially shows the well-known redox peaks with $\Delta E_p \approx 45 \text{ mV}$ [Fig. 12(a), dashed curve]. After 30 min aging, however, the potential sweep curve is practically independent of the rotation frequency and the peak separation is reduced to $\Delta E_p \approx 30 \text{ mV}$ [Fig. 12(a), solid curve]. After an aging period of 1 h or more, the potential sweep curve is completely independent of the rotation frequency with $\Delta E_p \approx 25 \text{ mV}$ and $E_p - E_{p/2} = 30 \text{ mV}$ for the anodic peak [Figs 12(b) and (c)]. An extra pair of redox peaks develops at $E \approx 0 \text{ V}$, which is similar to the results found for the PP electrode in $\text{H}_2\text{SO}_4 + \text{Q}$. The extra peaks at $E \approx 0 \text{ V}$ are also found in $0.5 \text{ M H}_2\text{SO}_4$ containing no Q, so they probably arise from redox reactions of the PMP film.

4. DISCUSSION

4.1. Location of the electrochemical reaction

Santhanam and O'Brien[7] studied the H_2Q oxidation at a polypyrrole electrode in anhydrous acetonitrile. It can be shown that their results are significantly affected by H_2Q , present in the polymer film at the start of the electrolysis. Consequently, their conclusion about the reaction site cannot be used for the stationary electrolysis at the limiting current.

For the polypyrrole electrode in $\text{H}_2\text{SO}_4/\text{EtOH}$ electrolyte, the I_l vs $\sqrt{f}$ curves in Fig. 2 and measurement in Q-containing solution show that the limiting currents are nearly independent of the polymer layer thickness and equal those at the uncovered metal. This indicates that the oxidation of H_2Q and the reduction of Q occur at the polymer/electrolyte interface.

4.2. Aging of the polymer electrodes

The PP and PMP electrodes show an aging effect in all the three electrolytes. The rate of the aging process is considerably less for the PP electrode than for the PMP electrode.

The voltammogram of the PP electrode exhibits a well-shaped wave for the H_2Q oxidation at a 10 min-aged electrode in $\text{H}_2\text{SO}_4/\text{EtOH}$ (Fig. 5), $\text{H}_2\text{SO}_4/\text{CH}_3\text{CN}$ and H_2SO_4 . A well-shaped wave is

also found for the Q reduction at a 10 min-aged PP electrode in $\text{H}_2\text{SO}_4/\text{EtOH}$ and in H_2SO_4 (Fig. 10).

For longer aging periods, the single voltammetric wave either decreases in height (Fig. 5), or splits into two waves, of which the sum of the heights is less than the height of the original single wave for the 10 min-aged electrode (Fig. 10). The voltammogram of a PMP electrode exhibits a well-shaped wave for the oxidation of H_2Q at a 10 min-aged electrode in H_2SO_4 (Fig. 11) and for the reduction of Q at a 10 min-aged electrode in $\text{H}_2\text{SO}_4/\text{EtOH}$.

Taking into account the difference in rate of aging between PP and PMP electrodes, it can be concluded that for both types of electrodes similar results have been obtained. The degree of aging determines mainly the occurrence or not-occurrence of two waves.

For the Q reduction at a PMP electrode in $0.5 \text{ M H}_2\text{SO}_4$, the aging effect is enormous and the electrochemical response becomes that of an electrode of which the redox couple is immobilized by attachment to the electrode surface: the peaks become independent of the electrode's rotation frequency (Fig. 12).

The immobilized species will be of a quinone-like structure, since no other organic species are involved.

That some redox compound becomes immobilized during the aging of the PMP electrode in $0.5 \text{ M H}_2\text{SO}_4$ is also supported by the fact that ΔE_p decreases during the aging process from $\Delta E_p \approx 45 \text{ mV}$ after 10 min to $\Delta E_p \approx 25 \text{ mV}$ after 1 h aging (Fig. 12). After 2 h of aging, ΔE_p is still 25 mV , indicating that the aging process is complete and that the surface redox process is probably not completely reversible (for an ideal reversible surface redox reaction, $\Delta E_p = 0$ [16]).

The immobilization of a redox compound during potential sweep experiments has also been observed for the H_2Q oxidation at a PP(Pt) electrode in anhydrous acetonitrile[6]. The immobilized oxidation product is identified as HQ^+ by cyclic voltammetry and is assumed to be electrostatically bound to the polymer[6].

Since HQ^+ is abundant in a solution of Q in $0.5 \text{ M H}_2\text{SO}_4$ and no inhibition effect is observed without electrochemical treatment of the electrode, the immobilized compound discussed here is not HQ^+ , but presumably HQ^{ad} , which is formed by reduction of HQ^+ according to $\text{HQ}^+ + e^- \rightarrow \text{HQ}^{\text{ad}}$. The superscript "ad" indicates that HQ is chemically or physically adsorbed.

The peaks in the cyclic voltammogram for the surface-attached species, Fig. 12, appear at about the same potentials as where the peaks were measured that corresponded to the oxidation of H_2Q and the reduction of Q when these reactions were not yet inhibited. So it is likely that the immobilized redox couple is closely related to the H_2Q/Q redox couple.

From the voltammogram in Fig. 12, it follows that an electrochemical reaction is the rate-determining step.

The same aging process as for the PMP electrode in 0.5 M H_2SO_4 occurs probably for the other electrodes and electrolytes that were investigated, however, with a decreased rate.

During the aging process, the polymer electrode will become increasingly blocked by immobilized HQ^{ad} and H_2Q^{ad} species and there is a decreasing number of sites at the polymer/electrolyte interface, at which further H_2Q oxidation or Q reduction occurs. Since a decreasing part of the electrode surface is oxidizing or reducing dissolved species, a diffusion-limited anodic or cathodic current will be observed, which decreases with increasing aging time. Such an effect has indeed been found for the PP and PMP electrodes in various electrolytes: Fig. 6 clearly shows the decreasing limiting-current plateau, together with the redox peaks coming from the immobilized H_2Q and HQ species.

4.3. Electrocatalytical behaviour of the polymer electrode

The results show that the behaviour of the H_2Q/Q redox couple in aqueous acid medium is strongly affected by the deposition of a polypyrrole or a poly-*N*-methylpyrrole layer on a gold substrate. Among the three electrolytes, viz $H_2SO_4/EtOH$, H_2SO_4/CH_3CN and H_2SO_4 , there are no large differences in the behaviour of the H_2Q/Q couple, except for the PMP(Au) electrode in H_2SO_4 electrolyte. For the last-named electrode, it appeared that, after some aging time, the voltammogram became independent of the electrode's rotation frequency (Fig. 12).

The mechanism of the hydroquinone oxidation and the quinone reduction in acid electrolyte was established by Vetter in 1952[5]. Additionally, it was found by Peters and Lingane, that platinum and gold exhibit the same chronopotentiogram in H_2Q - or Q -containing 1 M H_2SO_4 [17].

For the reduction of Q to H_2Q at a platinum electrode in aqueous electrolyte with $pH < 5$, the mechanism is found to be[5]:

For the oxidation of H_2Q at $pH < 5$, the reactions (1)–(4) occur in the reverse direction[5].

From cyclic voltammograms, measured at the uncovered Au electrode (Figs 1, 8 and experiments in H_2SO_4/CH_3CN electrolyte), it is likely that the reduction of Q at an uncovered Au electrode occurs also according to the CECE mechanism, described

above; the first *E*-step (2) will be the rate-determining step.

When a PP or a PMP film is deposited, ΔE_p in the cyclic voltammogram considerably decreases for all the electrolytes used (Figs 1 and 8). The value of ΔE_p mostly becomes about 60 mV, which corresponds to the ΔE_p for a reversible one-electron reaction or for a two-electron reaction with activation polarization[18].

It is likely that $n = 2$ for both the Q reduction and the H_2Q oxidation at PP and PMP electrodes, since a plot of I_1 vs $\sqrt{f}$ shows a slope which is practically equal to the slope, found for the uncovered Au electrode (Fig. 2), for which $n = 2$ is obtained for the Q reduction in $H_2SO_4/EtOH$. This means that the cyclic voltammogram at PP and PMP electrodes correspond to a two-electron reaction with some activation polarization.

The fact that the plot of $\log[I/(I_1 - I)]$ vs *E* for the PP and PMP electrodes shows a slope, almost equal to that observed at an uncovered Au electrode (Fig. 3), indicates that the rate-determining steps are probably the same for the three types of electrodes. Although definite conclusions about the mechanism of the Q reduction and the H_2Q oxidation cannot be drawn from the results presented here, it is likely that the mechanism of the reduction of Q to H_2Q and the oxidation of H_2Q to Q is the same at Pt, PP and PMP electrodes[reactions (1)–(4)].

The major effect of the polymer film appears to be an increase of the heterogeneous rate constant of the rate-determining reaction, viz reaction (2) for reduction and the reverse of (4) for oxidation. That the rate constants of Q reduction and H_2Q oxidation on the polymer film are higher than on gold, becomes acceptable when it is considered that, for a PP or PMP electrode, the organic molecules react on an organic electrode interphase, which is likely to occur more rapidly than on a metallic electrode interphase.

Irrespective of the exact nature of the effect, introduced by the polymer film, the influence of the film on the behaviour of the electrode is a good example of electrocatalysis.

REFERENCES

1. R. C. M. Jakobs, L. J. J. Janssen and E. Barendrecht, *Electrochim. Acta* **30**, 1085 (1985).
2. R. C. M. Jakobs, L. J. J. Janssen and E. Barendrecht, *Electrochim. Acta*, to be published.
3. R. C. M. Jakobs, Thesis, Eindhoven University of Technology, pp. 88 (1984).
4. *Encyclopedia of Electrochemistry of the Elements* (Edited by A. J. Bard), p. 272. Marcel Dekker, New York (1978).
5. K. J. Vetter, *Z. Elektrochem.* **56**, 797 (1952).
6. N. S. Sundaresan and K. S. V. Santhanam, *Trans. SAEST* **16**, 117 (1981).
7. K. S. V. Santhanam and R. N. O'Brien, *J. electroanal. Chem.* **160**, 377 (1984).
8. R. C. M. Jakobs, L. J. J. Janssen and E. Barendrecht, *Recl. Trav. Chim. pays-Bas Belg.* **103**, 275 (1984).
9. A. J. Bard and L. R. Faulkner, *Electrochemical Methods*, p. 150. John Wiley, New York (1980).
10. J. Timmermans, in *The Physico-chemical Constants of Binary Systems in Concentrated Solutions*, Vol. 4, p. 563. Interscience, New York (1960).
11. Ref.[6], p. 188.

12. *Landolt-Börnstein Zahlenwerte und Funktionen*, 211341, 884. Springer, Berlin (1971).
13. *International Critical Tables*, Vol. 5, p. 22. McGraw-Hill, New York (1929).
14. (a) M. Delamer, M. C. Pham, P. C. Lacaze and J. E. Dubois, *J. electroanal. Chem.* **108**, 1 (1980); (b) P. C. Lacaze, M. C. Pham, M. Delamar and J. E. Dubois, *J. electroanal. Chem.* **108**, 9 (1980).
15. J. Koutecký and V. G. Levich, *Zh. fiz. Khim.* **32**, 1565 (1958).
16. E. Laviron, *J. electroanal. Chem.* **100**, 263 (1979).
17. D. G. Peters and J. J. Lingane, *J. electroanal. Chem.* **2**, 1 (1961).
18. Ref.[5], p. 213.