Small-particle effects in Mössbauer spectra of a carbon-supported iron catalyst

Citation for published version (APA):

Niemantsverdriet, J. W., Van Der Kraan, A. M., Delgass, W. N., & Vannice, M. A. (1985). Small-particle effects in Mössbauer spectra of a carbon-supported iron catalyst. *Journal of Physical Chemistry*, 89(1), 67-72.
<https://doi.org/10.1021/j100247a018>

DOI:

[10.1021/j100247a018](https://doi.org/10.1021/j100247a018)

Document status and date:

Published: 01/12/1985

Document Version:

Publisher's PDF, also known as Version of Record (includes final page, issue and volume numbers)

Please check the document version of this publication:

- A submitted manuscript is the version of the article upon submission and before peer-review. There can be important differences between the submitted version and the official published version of record. People interested in the research are advised to contact the author for the final version of the publication, or visit the DOI to the publisher's website.
- The final author version and the galley proof are versions of the publication after peer review.
- The final published version features the final layout of the paper including the volume, issue and page numbers.

[Link to publication](#)

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal.

If the publication is distributed under the terms of Article 25fa of the Dutch Copyright Act, indicated by the "Taverne" license above, please follow below link for the End User Agreement:

www.tue.nl/taverne

Take down policy

If you believe that this document breaches copyright please contact us at:

openaccess@tue.nl

providing details and we will investigate your claim.

which is bonding relative to C and Li but antibonding relative to Li_2 . This picture of the tetrahedral singlet is of course equivalent to the conventional model involving a substituted sp^3 carbon atom.

The planar triplet has one electron in the carbon p_π orbital (b_1) and its triplet coupled companion in a very diffuse orbital of a_1

symmetry localized on the side of Li_2 away from the carbon atom. Rotating the Li_2 group about the C_2 axis of CH_2 has little effect on the electron distribution.

Registry No. CH_2Li_2 , 21473-62-1.

Small-Particle Effects in Mössbauer Spectra of a Carbon-Supported Iron Catalyst

J. W. Niemantsverdriet,* A. M. van der Kraan,

Interuniversitair Reactor Instituut, 2629 JB Delft, The Netherlands

W. N. Delgass,

School of Chemical Engineering, Purdue University, West Lafayette, Indiana 47907

and M. A. Vannice

Department of Chemical Engineering, The Pennsylvania State University, University Park, Pennsylvania 16802
(Received: August 3, 1984)

Highly dispersed iron catalysts, consisting of 5 wt % Fe on high-purity carbon black (Carbolac-1), have been studied by in situ Mössbauer spectroscopy at 295, 77, and 4 K. About 75–80% of the iron in the Fe/C-1 catalyst is reduced to α -Fe in H_2 at 740 K, whereas the remaining iron is present as Fe^{2+} . The α -Fe particles in reduced Fe/C-1 exhibit behavior characteristic of very small (2 nm) particles. First, the most interesting feature of this work is the occurrence of substantial contributions of superparamagnetic α -Fe in the Mössbauer spectra at 295 and 77 K. Second, the magnetic hyperfine fields of the α -Fe in the spectra at 4 K are enhanced by about 7 kOe, due to the influence of the demagnetizing field in the particle. Third, the effective Debye temperatures of the Fe/C-1 catalysts are much smaller than in iron bulk compounds. Exposure of reduced Fe/C-1 to air results in the oxidation of all iron to Fe^{3+} . Carburization in syngas ($\text{H}_2/\text{CO} = 3$) converts all α -Fe in the reduced catalyst to iron carbides, whereas the Fe^{2+} remains unaffected. Conversion of the Fe^{2+} spectrum from a singlet at room temperature to a doublet at 77 K shows that the unusual ferrous singlet is caused by cancellation of electron and lattice field gradients of opposite sign. The work illustrates the usefulness of in situ Mössbauer spectroscopy at cryogenic temperatures in the investigation of highly dispersed systems.

Introduction

Carbon has recently attracted attention as a support material for iron catalysts in CO hydrogenation¹⁻⁴ and for metal sulfide catalysts in hydrodesulfurization.⁵ Jung et al.¹ reported that iron supported on the porous carbon black Carbolac-1 (C-1) shows excellent retention of catalytic activity in the CO hydrogenation reaction at 508 K and atmospheric pressure, whereas $\text{Fe}/\text{Al}_2\text{O}_3$ catalysts deactivated severely under these conditions. Characterization by means of CO chemisorption, magnetization, and Mössbauer spectroscopy at room temperature revealed that the iron in these Fe/C-1 catalysts was highly dispersed (average diameters between 2 and 3 nm) and that the degree of reduction was much higher than is usually observed in silica- or alumina-supported iron catalysts with comparable dispersion.^{2,6} Obviously, the Fe/C-1 catalyst is a potentially interesting system for studying magnetism and lattice dynamics in small metallic iron particles.

In investigating highly dispersed iron systems with their characteristically low effective Debye temperatures, application of Mössbauer spectroscopy at cryogenic temperatures is often advantageous.⁷ At liquid nitrogen or liquid helium temperatures the recoilless fraction increases significantly and hence the quality of the spectra may improve considerably. Moreover, when components which are paramagnetic or superparamagnetic at 295 K become magnetically split at low temperature, identification of iron phases in the spectrum can be greatly facilitated.

Small particles often exhibit different magnetic properties than bulk materials. Superparamagnetism and decreased magnetic splitting due to thermal excitations of the magnetization (collective

magnetic excitations) are often observed in supported iron catalysts.^{6,8} In single-domain ferromagnetic particles yet another effect may be observed: the influence of the demagnetizing field on the magnetic hyperfine splitting, caused by the magnetic poles at the surface of the particle.⁸⁻¹⁰ At 295 or 77 K the influence of the demagnetizing field may be obscured by thermal excitations, which decrease the magnetic splitting. At 4 K, however, thermal excitations are virtually absent and at this temperature the influence of the demagnetizing field should be discernable.

When several particles stick together in a "grape cluster" type of arrangement, dipole interactions between the magnetic moments of neighboring particles can partially compensate the demagnetizing field¹⁰ and also prevent superparamagnetism. However, when the iron particles are sufficiently separated from each other,

(1) Jung, H.-J.; Walker, P. L.; Vannice, M. A. *J. Catal.* **1982**, *75*, 416.

(2) Jung, H.-J.; Vannice, M. A.; Mulay, L. N.; Stanfield, R. M.; Delgass, W. N. *J. Catal.* **1982**, *76*, 208.

(3) Vannice, M. A.; Walker, P. L.; Jung, H.-J.; Morena-Castilla, C.; Mahajan, O. P. *Proc. 7th Int. Cong. Catal. Tokyo 1980*, 460.

(4) Morena-Castilla, C.; Mahajan, O. P.; Walker, P. L.; Jung, H.-J.; Vannice, M. A. *Carbon* **1980**, *18*, 271.

(5) Duchet, J. C.; van Oers, E. M.; de Beer, V. H. J.; Prins, R. *J. Catal.* **1983**, *80*, 386.

(6) Topsøe, H.; Dumesic, J. A.; Mørup, S. In "Applications of Mössbauer Spectroscopy"; Cohen, R. L., Ed.; Academic Press: New York, 1980; Vol. II, p 55.

(7) Niemantsverdriet, J. W.; van der Kraan, A. M.; Delgass, W. N. *J. Catal.* **1984**, *89*, 138.

(8) Mørup, S.; Dumesic, J. A.; Topsøe, H. In "Applications of Mössbauer Spectroscopy"; Cohen, R. L., Ed.; Academic Press: New York, 1980; Vol. II, p 1.

(9) von Eynatten, G.; Bömmel, H. *Appl. Phys.* **1977**, *14*, 415.

(10) Tamura, I.; Hayashi, M. *J. Magn. Magn. Mater.* **1983**, *31-34*, 945.

* Present address: Laboratory for Inorganic Chemistry, Eindhoven University of Technology, 5600 MB Eindhoven, The Netherlands.

TABLE I: Mössbauer Parameters of Unreduced Fe/C-1

parameters ^a	<i>T</i> = 295 K	<i>T</i> = 77 K	<i>T</i> = 4 K	
			doublet	sextet
IS, mm/s	0.64 ± 0.02	0.77 ± 0.02	0.80 ± 0.02	0.80 ± 0.02
QS, mm/s	0.75 ± 0.03	0.91 ± 0.04	1.00 ± 0.06	0
LW, mm/s	0.50 ± 0.05	0.60 ± 0.06	0.72 ± 0.08	0.5 ± 0.1
<i>A</i> , au	0.35 ± 0.01	0.85 ± 0.02	0.56 ± 0.02	0.44 ± 0.02

^a IS relative to SNP.

as for example in supported catalysts of low metal loading, one may expect that dipole interactions between the magnetic moments of the particles will be negligible.

Here we report Mössbauer spectra, recorded in situ at 4, 77, and 295 K, of a Carbolac-supported iron catalyst before and after reduction in H₂, and after carburization in synthesis gas. The α -Fe particles in the reduced catalyst exhibit superparamagnetism at 295 and 77 K, whereas their magnetic hyperfine splitting at 4 K is enhanced by the demagnetizing field. The investigation illustrates that Mössbauer spectra at 295 K are less informative in the study of well-dispersed particles and that application of the technique at cryogenic temperatures is essential.

Experimental Section

The Fe/C-1 catalyst was prepared by an incipient wetness technique and contained 5 wt % iron on a Carbolac-1 (Cabot, 950 m²/g) support.^{1,3} For Mössbauer experiments quantities of about 200 mg were pressed into a wafer, using a pressure of about 100 atm.

Reduction and carburization experiments were carried out in a cell which can be closed vacuum tight inside a chemical reactor. This cell permits the measurements of Mössbauer spectra of the catalyst under the desired gaseous environment, at temperatures down to 4 K.¹¹ Reduction occurred in flowing H₂ (100 mL/min) for 0.5 h at 400 K, followed by 17 h at 675 or 740 K. The catalyst reduced at 740 K was treated with synthesis gas (CO:H₂ = 1:3, 140 mL/min) at 510 K for 18 h. The gases H₂ (Hoekloos, purity >99.9%) and CO (Hoekloos, >99.5%) were purified separately over a Cu catalyst (BASF, R3-11) and a molecular sieve (Union Carbide, 5A).

Mössbauer spectra were taken with a constant acceleration spectrometer, using an ⁵⁷Fe in Rh source. Isomer shifts (IS) are reported with respect to the NBS standard sodium nitroprusside (SNP). Magnetic hyperfine fields (*H*) were calibrated with the 515-kOe field of α -Fe₂O₃ at room temperature. The spectra were not corrected for the varying distance between source and absorber. Hence, the spectra show a curved background of instrumental origin. After recording spectra at 295, 77, and 4 K with the vacuum-tight absorber holder in a bath cryostat, another room temperature spectrum was measured in order to verify that the absorber holder had not leaked at cryogenic temperatures.⁷ Mössbauer spectra were fitted by computer using a least-squares program of Lorentzian-shaped lines, whereas the curved background was accounted for by a parabola. Total resonant absorption areas were calculated independently by integrating the spectra after correction for the background parabola.

Results

Unreduced Fe/C-1. The Mössbauer spectra of the unreduced catalyst at 295 and 77 K (Figure 1) consist of doublets with parameters characteristic of high-spin Fe³⁺ compounds (Table I). At 4 K about 40% of the spectrum has become magnetically split. The broad lines indicate the presence of a distribution in hyperfine fields, *H*. This distribution has been calculated with the method proposed by Wivel and Mørup.¹² The *H* distribution contains contributions from fields between about 370 and 530 kOe, with a weighted average of about 450 kOe. The Mössbauer parameters in Table I indicate that both the magnetically split

Figure 1. Mössbauer spectra of unreduced Fe/C-1 catalysts at the temperatures indicated.

Figure 2. In situ Mössbauer spectra of Fe/C-1 catalysts after reduction in H₂ at 675 K for 17 h.

pattern and the doublet correspond to Fe³⁺, most probably in an iron(III) oxide. The temperature dependence of the isomer shift indicates that the effective Debye temperature, θ_D , of the iron(III) compound is 200 ± 50 K.

(11) Niemantsverdriet, J. W.; Flipse, C. F. J.; van der Kraan, A. M.; van Loef, J. J. *Appl. Surf. Sci.* **1982**, *10*, 302.

(12) Wivel, C.; Mørup, S. *J. Phys. E.* **1981**, *14*, 605.

Figure 3. In situ Mössbauer spectra of Fe/C-1 catalysts after H_2 reduction at 740 K for 17 h.

Reduced Fe/C-1. Figures 2 and 3 show the in situ Mössbauer spectra of Fe/C-1 after reduction at 675 and 740 K, respectively. Before we discuss computer fitting, we will give a qualitative discussion of the spectra. The spectra at room temperature are poorly resolved and leave much freedom for computer analysis. Fortunately, the spectra of the same samples at 77 and 4 K show more details. The liquid helium spectra consist of a sharp sextuplet which corresponds to α -Fe and an additional broad magnetically split component. The spectra at 77 K contain also a contribution of an α -Fe sextuplet, but in comparison with the 4 K spectra a strong single line appears in the center of the spectrum at a velocity where contributions from superparamagnetic iron are expected. Furthermore, the 77 K spectra contain a peak at about 2.5 mm/s, a velocity at which α -Fe does not exhibit resonant absorption. We attribute this peak to a doublet of Fe^{2+} with its low-velocity counterpart in the central region of the spectrum. In summary, the 77 K spectra contain a sextet of α -Fe, a singlet of superparamagnetic α -Fe, and a doublet of Fe^{2+} .

The room temperature spectra show a barely visible magnetically split α -Fe contribution, but the majority of the resonant absorption occurs in the centrum of the spectrum. Note that well-resolved doublets due to Fe^{2+} are absent. Based on the interpretation of the spectra at 77 K we suggest that the spectra at room temperature consist of two single lines, one of superparamagnetic α -Fe and another representing an unresolved doublet due to Fe^{2+} ions. The assignment of a single line to Fe^{2+} may at first sight appear surprising, but is consistent with ref 2, where it has convincingly been shown that Fe^{2+} singlets can occur in carbon-supported iron catalysts, at intermediate stages of reduction.

Curve fitting, based on the qualitative interpretation given above, yields the Mössbauer parameters presented in Table II. A few simplifying assumptions were necessary. The 4 K spectra are dominated by the sharp α -Fe sextuplet, but they also contain a broad magnetically split component, probably Fe^{2+} , which has been accounted for by six unconstrained Lorentzian lines. We do not attach significance to the parameters of the latter; they only serve to fill the part of the spectrum which is not due to α -Fe.

TABLE II: Mössbauer Parameters of Reduced Fe/C-1

Fe state	parameters ^a	reduced at	
		675 K	740 K
<i>T</i> = 295 K			
Fe ⁰	IS, mm/s	0.30 ± 0.05	0.30 ± 0.05
	LW, mm/s	0.9 ± 0.1	0.9 ± 0.1
	<i>A</i> , au	0.11 ± 0.01	0.12 ± 0.01
Fe ²⁺	IS, mm/s	1.2 ± 0.1	1.2 ± 0.1
	LW, mm/s	1.1 ± 0.2	1.1 ± 0.2
	<i>A</i> , au	0.11 ± 0.01	0.12 ± 0.01
<i>T</i> = 77 K			
Fe ⁰	IS, mm/s	0.40 ± 0.02	0.41 ± 0.02
	<i>H</i> , kOe	343 ± 3	340 ± 3
	LW, mm/s	0.48 ± 0.04	0.69 ± 0.04
	<i>A</i> , au	0.17 ± 0.02	0.21 ± 0.02
Fe ⁰	IS, mm/s	0.40 ± 0.04	0.41 ± 0.04
	LW, mm/s	1.6 ± 0.2	1.6 ± 0.15
	<i>A</i> , au	0.35 ± 0.03	0.32 ± 0.02
Fe ²⁺	IS, mm/s	1.50 ± 0.04	1.56 ± 0.04
	QS, mm/s	1.9 ± 0.1	2.0 ± 0.1
	LW, mm/s	0.9 ± 0.2	1.0 ± 0.2
	<i>A</i> , au	0.21 ± 0.02	0.17 ± 0.02
<i>T</i> = 4.2 K			
Fe ⁰	IS, mm/s	0.40 ± 0.04	0.42 ± 0.04
	LW, mm/s	0.57 ± 0.04	0.58 ± 0.04
	<i>H</i> , kOe	345 ± 3	347 ± 3
	<i>A</i> , au	0.6 ± 0.1	0.77 ± 0.05

^a IS relative to SNP.

The small, magnetically split contributions of α -Fe in the room temperature spectra have been ignored in the fit. Within the accuracies, the isomer shifts and resonant absorption areas of all components satisfy the requirement of the theory of lattice dynamics, that they increase with decreasing temperature.¹³ Unfortunately, the isomer shifts are not sufficiently accurate to permit calculation of Debye temperatures from the second-order Doppler shift.

Note that the magnetic hyperfine field of the α -Fe at 4 K is 345 ± 3 kOe, which is significantly higher than the 338-kOe field of bulk α -Fe at 4 K.¹⁴ The spectra of the Fe/C-1 catalyst after the two reduction treatments show very similar features. The main difference appears at 4 K, where it is seen that reduction at 740 K yields more metallic iron (77% of the spectral area) than reduction at 675 K.

Exposure of the reduced Fe/C-1 catalyst to air at 295 K causes the oxidation of all iron to Fe^{3+} , which appears as a doublet with IS = 0.64 mm/s and QS = 0.75 mm/s in the Mössbauer spectrum at 295 K (not shown).

Carburized Fe/C-1. The catalyst reduced at 740 K was carburized in synthesis gas ($H_2:CO = 3:1$) at 510 K for 18 h. Among the Mössbauer spectra at 295, 77, and 4 K (Figure 4), the one at 77 K shows the best-resolved peaks. This spectrum has been analyzed with a doublet for Fe^{2+} , the same species as in the spectra of reduced Fe/C-1 catalysts, and a single peak or unresolved doublet. The isomer shift of the latter is 0.6 mm/s with respect to SNP, which is in the range expected for iron carbides at 77 K. Note that the spectrum also contains poorly resolved, magnetically split contributions which cannot easily be accounted for in the computer analysis. If we conclude that the main part of the 77 K spectrum consists of an Fe^{2+} doublet and a broadened singlet due to iron carbide, then it follows that the broad peak in the spectrum at room temperature consists of two single peaks, one for superparamagnetic iron carbide and one for an unresolved Fe^{2+} doublet, as in the reduced catalyst.

The spectrum at 4 K consists mainly of poorly resolved magnetically split subspectra, including the broad Fe^{2+} sextuplet that was also encountered in the 4 K spectrum of the reduced catalyst.

(13) Wertheim, G. K. "Mössbauer Effect: Principles and Applications"; Academic Press: New York, 1964.

(14) Preston, R. S.; Hanna, S. S.; Heberle, J. *Phys. Rev.* **1962**, 128, 2207.

Figure 4. In situ Mössbauer spectra of Fe/C-1 catalysts after treatment in CO + 3 H₂ at 510 K for 18 h.

Figure 5. Resonant absorption areas of the Fe/C-1 spectra in Figures 1-4, along with theoretical curves according to the Debye model.

Significant contributions of α -Fe are not observed, indicating that all or almost all metallic iron present before carburization was indeed converted into iron carbides. The spectra do not enable a further identification of the kind of iron carbide formed.

Resonant Absorption Areas. Resonant absorption areas, A , of the Fe/C-1 catalysts were calculated after correcting the spectra of Figures 1-4 for their geometrical background parabola. As the spectra of Figures 2-4 were obtained with different catalyst wafers, the values of A as given in Figure 5 have been normalized to unity at 4 K. The wafers used in the Mössbauer experiments contained only between 2 and 3 mg of iron/cm². Saturation effects do not occur at these low concentrations and hence the relative absorption areas in Figure 5 reflect the temperature dependence of the recoilless fraction, f . In fact, A , normalized to unity at 4 K, equals $f(T)/f(T = 4 \text{ K})$. This ratio can be calculated in the Debye model, with the Debye temperature, θ_D , as a parameter.^{7,13} Figure 5 indicates that the characteristic Debye temperatures are near 200 and 150 K for the iron in the unreacted and the reduced Fe/C-1 catalysts, respectively. For the unreacted catalyst this value is in good agreement with $\theta_D = 200 \pm 50 \text{ K}$, derived from

the temperature dependence of the isomer shift. We note, for comparison, that the Debye temperatures for bulk α -Fe or α -Fe₂O₃ are in the order of 450-500 K.¹⁵

Discussion

The Mössbauer spectra of the Fe/C-1 catalysts before and after reduction exhibit various features which are characteristic of small-particle behavior. The unreacted catalysts contain iron(III) oxide, which is superparamagnetic at 295 and 77 K. Even at 4 K more than half of the Fe³⁺ in the sample is in a superparamagnetic state. For comparison, all bulk iron(III) oxides show full magnetic splitting at room temperature. The value of the quadrupole splitting at 295 K is 0.75 mm/s, considerably higher than the 0.52 mm/s of α -Fe₂O₃ bulk material. According to van der Kraan,¹⁶ the quadrupole splitting of small particles of α -Fe₂O₃ can be described in terms of a central core which corresponds to a doublet with QS = 0.52 mm/s, the bulk value, and a surface shell with a doublet characterized by QS = 0.9 mm/s. The observed QS is an average of these two limiting values, depending on the relative fraction of surface atoms in the particle. For comparison, unsupported α -Fe₂O₃ particles with an average diameter of 4 nm have QS = 0.64 mm/s at 295 K and show partial magnetic splitting at 77 K and full magnetic splitting at 4 K.¹⁶ The large quadrupole splitting at 295 K and the absence of magnetic splitting at 77 K in the spectra of unreacted Fe/C-1 indicate that the iron oxide in these catalysts is highly dispersed, probably with particle dimensions well below 4 nm.

The investigation of the reduced Fe/C-1 catalysts illustrates that Mössbauer spectra of highly dispersed systems taken only at room temperature are not sufficient to identify all iron phases present. After the reduced catalysts were cooled in situ to liquid helium temperature, 4 K, the presence of metallic iron could be established without doubt and this knowledge allows the assignment of single-line contributions in the spectra at 77 and 295 K to superparamagnetic metallic iron. Similar considerations facilitate the identification of the Fe²⁺ component in the spectra of reduced Fe/C-1. Since the liquid nitrogen spectra contain a doublet of Fe²⁺, one of the singlets contributing the broad composite peak in the spectrum at 295 K can be attributed to the Fe²⁺ component.

Usually, ferrous compounds exhibit quadrupole-split Mössbauer spectra at room temperature. To explain why the Fe²⁺ component in Fe/C-1 catalysts appears as a singlet, Jung et al.² suggested that the environment of the Fe²⁺ ions is unusually symmetric. This interpretation, however, is contradicted by the results reported here, which indicate that the Fe²⁺ contribution is a doublet at 77 K. We propose the following explanation, based on a discussion of quadrupole splittings in iron compounds by Travis.¹⁷ In the case of Fe²⁺ ions, the electric field gradient (EFG) contains two contributions, one from the asymmetric distribution of the six 3d electrons over their energy levels, and one from the lattice when the symmetry is noncubic. The former depends on temperature, the latter almost not. When the electron and lattice contribution to the EFG have opposite signs, they may compensate each other at a certain temperature and in such cases the Mössbauer spectrum shows a singlet which, as is the case here, is an unresolved doublet.

Assignment of the Fe²⁺ contribution to a certain phase is not possible yet. The parameters of the Fe²⁺ at 77 and 295 K do not belong to known compounds as, for example, FeO. It seems likely that the Fe²⁺ subspectrum corresponds to ferrous oxide coordinated to adsorption sites on the Carbolac support.

The α -Fe in the reduced Fe/C-1 catalysts exhibits interesting magnetic behavior, with the occurrence of superparamagnetic α -Fe in the spectra at liquid nitrogen temperature as the most remarkable feature. Obviously, the α -Fe particles must be very small, in qualitative agreement with the diameter of about 2 nm which follows from CO chemisorption experiments. Superpara-

(15) Niemantsverdriet, J. W.; Flippe, C. F. J.; Selman, B.; van Loef, J. J.; van der Kraan, A. M. *Phys. Lett. A* **1984**, *100A*, 445.

(16) van der Kraan, A. M. *Phys. Status Solidi A* **1973**, *18*, 215.

(17) Travis, J. C. in "An Introduction to Mössbauer Spectroscopy"; May, L., Ed.; Plenum Press: New York, 1971.

magnetism has not been observed very often in metallic iron. Sometimes small contributions of a superparamagnetic α -Fe peak occur in Mössbauer spectra at 295 K of reduced Fe/SiO₂ catalysts. The Fe/C-1 catalysts, however, show superparamagnetic iron even at 77 K. In general, the occurrence of superparamagnetism in an isolated particle is determined by its magnetic anisotropy energy. When the energy, kT , of thermal excitations is sufficiently high to overcome the anisotropy barrier, the magnetic moment of the particle will fluctuate rapidly between the easy directions of the lattice, and magnetic splitting is not observed.⁸

In iron oxides such as Fe₂O₃ and FeOOH, the magnetocrystalline anisotropy per unit volume is high^{8,16,18} and it is by far the dominating contribution to the anisotropy energy. In metallic iron, however, the magnetocrystalline contribution is much smaller⁸ and the magnetic anisotropy is largely determined by the shape and the fraction of surface atoms of the particle, and by the influence of neighboring particles. When ferro- or ferrimagnetic particles are close together, dipole interactions occur between their magnetic moments. The moments of neighboring particles tend to align each other in their dipole fields. This dipole interaction is the origin of interaction anisotropy, with an easy direction depending on the relative positions of the particles. Moreover, when neighboring particles are in contact, exchange anisotropy is caused by an exchange interaction at the interface between the particles. A recent study by Tamura and Hayashi¹⁰ showed that the influence of exchange interaction on the total magnetic anisotropy in 10-nm α -Fe particles can be considerable. In short, whether or not a metallic iron particle is superparamagnetic depends not only on its size and shape but also on the proximity of other iron particles. We regard the fact that the α -Fe particles in the reduced Fe/C-1 catalysts exhibit superparamagnetism at 77 K as strong evidence that the particles are not in contact and, moreover, are sufficiently separated from each other to make the influence of dipole interactions and exchange anisotropy negligible. Apparently, the sum of magnetocrystalline, surface, and shape anisotropy has a value such that superparamagnetism can occur already at 77 K.

The particle size of the α -Fe particles in the reduced Fe/C-1 catalyst is about 2 nm. Another investigation of iron particles of comparable small size has been described by Boudart et al.¹⁹ These authors report that Mössbauer spectra of 1.5-nm α -Fe particles in Fe/MgO catalysts are magnetically split at room temperature, and their superparamagnetic transition temperature, T_B , is estimated to be about 800 K. Figures 2 and 3 show that in our Fe/C-1 catalysts T_B is even lower than 77 K. As T_B and the total magnetic anisotropy energy are proportional, we conclude that the magnetic anisotropy energy in the 1.5-nm α -Fe particles in Fe/MgO catalysts is more than 10 times higher than that in the 2-nm iron particles in Fe/C-1 catalysts. A quantitative comparison of the anisotropy energies in the two catalyst systems would require precise knowledge of the shape and dimensions of the iron particles and cannot be made. Whatever the correct explanation of the difference between the two systems may be, comparison of the Mössbauer spectra of Fe/MgO in¹⁹ and Fe/C-1 presented here illustrates clearly that the occurrence of superparamagnetism at a certain temperature is not governed by particle size only, and that differences in morphology, which can be caused by different metal-support interactions, may play an important role as well.

The magnetic hyperfine field of the metallic iron in the reduced Fe/C-1 catalysts at 4 K is 345 ± 3 kOe, whereas in bulk α -Fe at 4 K it is 338 kOe.¹⁴ We attribute this difference to the demagnetizing field, caused by the poles of the magnetization vector at the surface of the single-domain particles. In metallic iron, the magnetic hyperfine field is oriented antiparallel with respect to the magnetization, and therefore the demagnetizing field increases the magnetic splitting.⁸ The enhancement of H in small

iron particles has been observed before in unsupported iron particles with diameters in the range of 6.6 to 10 nm.^{9,10} The magnetic hyperfine field can be written as

$$H = H_{\text{bulk}} + H_{\text{dem}} - H_{\text{dip}} \quad (1)$$

in which H_{bulk} is the magnetic hyperfine field of nonmagnetized α -Fe bulk material, H_{dem} the demagnetizing field, and H_{dip} the magnetic field of neighboring particles. The demagnetizing field of spherical, single-domain α -Fe particles is about 7 kOe.⁸⁻¹⁰ As we discussed above, the occurrence of superparamagnetism at relatively low temperatures suggests that the particles are at a distance such that $H_{\text{dip}} = 0$. If we assume approximately spherical particle shape for the iron particles and we use $H_{\text{dem}} = 7$ kOe and $H_{\text{bulk}} = 338$ kOe, then eq 1 predicts a magnetic hyperfine field of 345 kOe, in excellent agreement with the observed values of 345 ± 3 and 347 ± 3 kOe for α -Fe in the Fe/C-1 catalysts after reduction at 675 and 740 K, respectively (Table II).

The Mössbauer spectra of Fe/C-1 after carburization in CO and H₂ at 510 K for 18 h indicate that all metallic iron originally present in the reduced catalyst has been converted into carbides, whereas the Fe²⁺ contribution is hardly or not affected by this treatment. Unfortunately, identification of the carbides formed is impossible and has not offered an explanation of the remarkably high resistance of the Fe/C-1 catalyst to deactivation at reaction conditions.

The effective Debye temperatures, θ_D , of the iron in the Fe/C-1 catalysts, determined from the temperature dependence of the spectral areas, $A(T)$, are in the order of 150–200 K, whereas θ_D of the corresponding bulk materials is between 450 and 500 K.¹⁵ In general, two reasons can be given for low θ_D values. First, according to Somorjai,²⁰ θ_D of atoms at the surface is about half that of atoms in the bulk. As a large fraction of the atoms in 2-nm particles are at the surface, one expects a θ_D which is lower than in bulk material. Second, it is not certain whether the α -Fe particles in reduced Fe/C-1 are bound to the carbon support or loosely contained in the pores of the support. In the latter case, thermal motion of the particles causes the recoilless fraction of such particles to decrease more rapidly with temperature than is expected on the base of lattice vibrations alone. This effect can mistakenly be interpreted in terms of a decreased Debye temperature and can be recognized from the temperature dependence of the isomer shift, $\text{IS}(T)$, which yields a θ_D independent of particle motion.^{15,21} For unreduced Fe/C-1 the Debye temperature from $A(T)$ and $\text{IS}(T)$ are equal, indicating that particle motion plays no role. For the reduced catalysts the $\text{IS}(T)$ values are not accurate enough to determine θ_D . We suggest that both the large fraction of surface atoms (near $1/3$) and thermal motion of particles inside the pores of the support are responsible for the low value of θ_D .

It is interesting to note that the effective Debye temperature decreases somewhat upon reduction. This is in contrast to our experience with SiO₂- and Al₂O₃-supported iron catalysts where θ_D is always found to increase as a result of reduction.^{7,22} The interpretation in the case of oxide-supported catalysts is that after impregnation and drying a highly dispersed metal oxide layer has formed on the support, whereas after reduction metal particles of lower dispersion have formed, bound to the support. The decrease in θ_D of the Fe/C-1 catalysts upon reduction may indicate that the iron particles formed after reduction are not tightly bound to the support. However, further investigation will be necessary before firm conclusions concerning this point can be drawn.

Conclusions

(1) The Fe/C-1 catalysts after impregnation and drying contain iron as Fe³⁺ in an iron(III) oxide. The large quadrupole splitting at room temperature, the fact that magnetic splitting sets in below

(18) Amelse, J. A.; Arcuri, K. B.; Butt, J. B.; Matyi, R. J.; Schwartz, L. H.; Shapiro, A. *J. Phys. Chem.* **1981**, *85*, 708.

(19) Boudart, M.; Dumesic, J. A.; Topsøe, H. *Proc. Natl. Acad. Sci. U.S.A.* **1977**, *74*, 806.

(20) Somorjai, G. A. "Chemistry in Two Dimensions: Surfaces"; Cornell University Press: Ithaca, NY, 1980; p 170.

(21) Hayashi, M.; Tamura, I.; Fukano, Y.; Kanemaki, S.; Fujio, Y. *J. Phys. C* **1980**, *13*, 681.

(22) Flipse, C. F. J., M.Sc. Thesis, Delft, 1982 (unpublished).

77 K, and the low effective Debye temperature all indicate that the iron(III) oxide is highly dispersed.

(2) After reduction in H_2 at 675 or 740 K the Fe/C-1 catalysts contain about 60 and 77% metallic iron, respectively. At 295 and 77 K this α -Fe is predominantly in a superparamagnetic state. At 4 K, however, all the α -Fe exhibits magnetic splitting, with a magnetic hyperfine field which is about 7 kOe larger than the 338-kOe field of bulk α -Fe. The difference is in agreement with the influence expected from the demagnetizing field in single-domain α -Fe particles.

(3) The occurrence of superparamagnetic α -Fe in Mössbauer spectra at 77 K indicates that the distance between the α -Fe particles is such that dipole-dipole interactions between the magnetic moments of the particles are negligible. Also, the total magnetic anisotropy energy of the particles must be small.

(4) The reduced Fe/C-1 catalysts contain an Fe^{2+} phase which in the Mössbauer spectra appears as a broadened magnetic sextet at 4 K, a doublet at 77 K, and an unresolved doublet at 295 K. The unusual occurrence of a single line for Fe^{2+} is explained by

electronic and lattice contributions to the electric field gradient which are opposite in sign and compensate each other at 295 K.

(5) All iron in the reduced Fe/C-1 catalyst becomes oxidized upon exposing the Fe/C-1 catalyst to air at 295 K, in agreement with the small particle size (2 nm) which follows from CO chemisorption, and the occurrence of superparamagnetism at relatively low temperatures.

(6) Treatment of reduced Fe/C-1 catalysts at 510 K in CO and H_2 converts all α -Fe into iron carbides which are superparamagnetic at 295 K, whereas the Fe^{2+} -phase remains unaffected.

The various interesting aspects of small-particle behavior could only be revealed after application of Mössbauer spectroscopy in situ at liquid nitrogen and helium temperatures. The present investigation illustrates that equipment which permits measurement of spectra in situ at cryogenic temperatures is an absolute necessity for complete Mössbauer studies of highly dispersed catalysts.

Registry No. Fe, 7439-89-6.

Intracrystalline Site Preference of Hydrogen Isotopes in Borax

Trinetra M. Pradhananga* and Sadao Matsuo

Department of Chemistry, Tokyo Institute of Technology, O-Okayama, Meguro-Ku, Tokyo 152, Japan
(Received: August 24, 1984)

The total hydrogen involved in borax synthesized at 25 °C in aqueous solution is enriched in deuterium by 5.3‰ compared with the mother liquor. There is no change in the value of the D/H fractionation factor between the hydrogen in borax and those in the mother liquor with changes in the degree of supersaturation. The fractionation factor changes slightly with a change in the crystallization temperature of borax in the range from 5 to 25 °C. The D/H ratio in the different sites of borax was estimated by a fractional dehydration technique. The results show that hydrogen atoms of the polyanionic group $[B_4O_5(OH)_4]$ are much more enriched in deuterium than those of the cationic group $[Na_2 \cdot 8H_2O]$. The δD values, referred to the mother liquor from which the borax was crystallized, for the cationic group (site A) and the polyanionic group (site B) are -35 ± 3 and 167 ± 13 ‰, respectively, based on the fractional dehydration results obtained at -21 °C. At -21 °C, isotopic exchange between different sites during dehydration is assumed not to occur. The mechanism for dehydration of borax is discussed.

Introduction

The difference in the isotopic composition of oxygen between free water and water molecules in the hydration sphere of cations and anions in aqueous salt solutions was first discussed by Taube.¹ The effects of ions on the isotopic fractionation between aqueous solutions were investigated and expanded by a number of researchers.²⁻⁴ In addition, information on the fractionation of hydrogen and/or oxygen isotopes between crystals and their saturated solutions has also been accumulated.⁵⁻¹⁰ Bigeleisen¹¹ and Matsuo et al.¹² advocated that the temperature dependence

of the hydrogen isotope fractionation factor between hydrates and aqueous solution can be used as a geothermometer. However, the water of crystallization in a hydrate crystal is not always in the same geometric and/or energetic site, so that there should be an isotopic site preference in the crystal of hydrates as was pointed out by Heinzinger and Rao.¹³ Heinzinger and Maiwald¹⁴ conducted a fractional dehydration experiment on $CuSO_4 \cdot 5H_2O$ and verified such a site preference for this compound. Heinzinger and Götz¹⁵ further estimated a temperature dependence for the site preference. Based on their results, Heinzinger¹⁶ suggested that even a single mineral with isotopic site preference can be used as a geothermometer. Kita and Matsuo¹⁷ concluded that water molecules in the coordination sphere of Cu^{2+} were depleted in deuterium by 32‰ and water molecules bound to SO_4^{2-} through hydrogen bonding were enriched by 22.6‰ compared with the mother liquor. Hamza and Epstein¹⁸ found that there is a significant difference in the $^{18}O/^{16}O$ ratio between the OH groups

(1) Taube, H. *J. Phys. Chem.* **1954**, *58*, 523.

(2) Sofer, Z.; Gat, J. R. *Earth Planet. Sci. Lett.* **1972**, *15*, 232.

(3) Truesdell, A. H. *Earth Planet. Sci. Lett.* **1974**, *23*, 387.

(4) Stewart, M. K.; Friedman, I. *JGR J. Geophys. Res.* **1975**, *80*, 3812.

(5) Barrer, R. M.; Denny, A. F. *J. Chem. Soc.* **1964**, 4677.

(6) Tanaka, H.; Negita, H. *Bull. Chem. Soc., Jpn.* **1970**, *43*, 3079.

(7) Gonfiantini, R.; Fontes, J. C. *Nature (London)* **1963**, *200*, 644.

(8) Fontes, J. C.; Gonfiantini, R. *C. R. Acad. Sci., Ser. D* **1967**, *265*, 4.

(9) Johansson, M.; Holmberg, K. E. *Acta Chim. Scand.* **1969**, *23*, 765.

(10) Matsubaya, O.; Sakai, H. *Geochem. J.* **1973**, *7*, 153.

(11) Bigeleisen, J. *J. Chem. Phys.* **1961**, *34*, 1485.

(12) Matsuo, S.; Friedman, I.; Smith, G. I. *Geochim. Cosmochim. Acta* **1972**, *36*, 427.

(13) Heinzinger, K.; Rao, T. S. *Z. Naturforsch., A* **1967**, *22A*, 2111.

(14) Heinzinger, K.; Maiwald, B. *Bull. Chem. Soc. Jpn.* **1972**, *45*, 2237.

(15) Heinzinger, K.; Götz, D. *Earth Planet. Sci. Lett.* **1975**, *27*, 219.

(16) Heinzinger, K. *J. Radioanal. Chem.* **1976**, *30*, 227.

(17) Kita, I.; Matsuo, S. *J. Phys. Chem.* **1981**, *85*, 792.

(18) Hamza, M. S.; Epstein, S. *Geochim. Cosmochim. Acta* **1980**, *44*, 173.