Formation of paramagnetic surface species during the oxidation of nonstoichiometric $\text{TiO}_2(\text{A})$, SnO_2 , and ZnO

Citation for published version (APA):

Hooff, van, J. H. C. (1968). Formation of paramagnetic surface species during the oxidation of nonstoichiometric $\text{TiO}_2(\text{A})$, SnO_2 , and ZnO . *Journal of Catalysis*, 11(3), 277-279. [https://doi.org/10.1016/0021-9517\(68\)90047-X](https://doi.org/10.1016/0021-9517(68)90047-X)

DOI:

[10.1016/0021-9517\(68\)90047-X](https://doi.org/10.1016/0021-9517(68)90047-X)

Document status and date:

Published: 01/01/1968

Document Version:

Publisher's PDF, also known as Version of Record (includes final page, issue and volume numbers)

Please check the document version of this publication:

- A submitted manuscript is the version of the article upon submission and before peer-review. There can be important differences between the submitted version and the official published version of record. People interested in the research are advised to contact the author for the final version of the publication, or visit the DOI to the publisher's website.
- The final author version and the galley proof are versions of the publication after peer review.
- The final published version features the final layout of the paper including the volume, issue and page numbers.

[Link to publication](#)

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal.

If the publication is distributed under the terms of Article 25fa of the Dutch Copyright Act, indicated by the "Taverne" license above, please follow below link for the End User Agreement:

www.tue.nl/taverne

Take down policy

If you believe that this document breaches copyright please contact us at:

openaccess@tue.nl

providing details and we will investigate your claim.

orders of magnitude larger than the kinetic site density.

The Ward model predicts that the acid faujasite is the ultimate since the role of other cations is to provide an increasing number of acid-type hydroxyl groups. The model in my discussion, however, predicts that a cation with high ionic potential (to provide polarization) mixed with the H-faujasite (to provide the OH concentration) could be more acidic than the pure acid faujasite. Indications that this is the case for a rare earth-hydrogen faujasite have been claimed (14) but for stability reasons. Experiments with acid strength distribution measurements are needed to decide this issue.

Finally, the role of direct cation interaction, although minimized for carbonium activity by many authors, still may play an important role for other types of reactions, e.g., the radical dehydrogenation of cumene (3). Measurements of the field strengths through spectroscopic or ESR techniques will be required, in addition to experimental verification of the cation time-dependent field proposed by Tung (6).

REFERENCES

1. HIRSCHLER, A. E., *J. Catalysis* **11**, 275 (1968).

2. RICHARDSON, J. T., *J. Catalysis* **9**, 182 (1968).
3. HIRSCHLER, A. E., *J. Catalysis* **2**, 428 (1963).
4. PICKERT, P. E., RABO, J. A., DEMPSEY, E., AND SHOMAKER, B., *Proc. Intern. Congr. Catalysis, 3rd, Amsterdam, 1964* **2**, 1264 (Wiley, New York, 1965).
5. WARD, J. W., *J. Catalysis* **10**, 34 (1968).
6. TUNG, S. E., AND MCNINCH, E., *J. Catalysis* **10**, 166 (1968).
7. RICHARDSON, J. T., *J. Catalysis* **9**, 172 (1967).
8. BENSON, J. E., USHIBA, K., AND BOUDART, M., *J. Catalysis* **9**, 91 (1967).
9. KUBOKAWA, Y., AND MIYATA, H., *J. Phys. Chem.* **72**, 356 (1968).
10. MAATMAN, R. W., LEENSTRA, D. L., LEENSTRA, A., BLANKESPOOR, R. L., AND RUBINCH, D. W., *J. Catalysis* **7**, 1 (1967).
11. PRATER, C. D., AND LAGO, R. M., *Advan. Catalysis* **8**, 298 (1956).
12. BETT, J. A. S., AND HALL, W. K., *J. Catalysis* **10**, 105 (1968).
13. ROMANOVSKII, V. B., THONG, H. S., AND TOPCHIEVA, K. V., *Kinetika i Kataliz* **7**, 197 (1966).
14. PLANK, C. J., AND ROSINSKI, E. J., U.S. Patent 3,140,253 (1964).

JAMES T. RICHARDSON

*Synthetic Fuels Research Laboratory
Esso Research and Engineering Company
Baytown, Texas 77520*

Received May 29, 1968

Formation of Paramagnetic Surface Species during the Oxidation of Nonstoichiometric $\text{TiO}_2(\text{A})$, SnO_2 , and ZnO

Iyengar, Codell, and Turkevich (1) recently published some ESR observations on the oxidation of nonstoichiometric rutile with oxides of nitrogen.

Similar measurements have been performed by us on TiO_2 (anatase), SnO_2 , and ZnO and preceding a future and more detailed report we believe it relevant to summarize our results here, the more so, since

they lead to a somewhat different explanation than that earlier given by Cornaz, van Hooff, Pluym, and Schuit (2) and van Hooff and van Helden (3).

TiO_2 (anatase) after outgassing at 500°C shows a similar signal as given by Iyengar *et al.* in their Fig. 1A. After admission (at room temperature) of O_2 and reevacuation (also at room temperature) this signal dis-

FIG. 1. Observed EPR Spectrum after admission of O_2 at outgassed TiO_2 (A) and the three EPR signals from which this spectrum can be built up.

appears and is replaced by a new signal observable at room temperature (see Fig. 1). The new signal is considered to consist of three separate signals, A, B, and C as shown in Fig. 1. The C signal is trivial because it originates from the quartz glass sample tube. Signal A is a $1g$ -value signal, signal B a $3g$ -value signal. The arguments to split the observed spectrum in A and B are as follows:

- (i) A is easily saturated, B is not.
- (ii) Admission of 1-butene, subsequent to the formation of the ESR spectrum mentioned above, causes the B signal to disappear rapidly, while the A signal decreases only slowly in intensity.
- (iii) Only signal A is observed after contacting the "reduced" TiO_2 with either N_2O or NO .

The formation of ESR-active surface species on nonstoichiometric SnO_2 and ZnO is very similar. However, the g values of

the B signal are different, while the A signal hardly varies in its g value (see Table 1).

The analysis of the spectrum given is obviously different from our earlier suggestions and it is therefore necessary to compare the two proposals. Signal B is similar to our earlier signal *e* and moreover to the $3g$ signals given by Iyengar *et al.* (4), Kazanskii (5), and Lu Tun Sin *et al.* (6).

Signal A is related to our earlier signal *d*. The central line d_2 of *d* coincides with A and also with the central line of the O_2^+ signal of Iyengar *et al.* The disappearance

TABLE 1
 g VALUES OF THE DIFFERENT ESR SIGNALS

	Signal A g	Signal B		
		g_1	g_2	g_3
$TiO_2(A)$	2.003	2.019	2.010	2.004
SnO_2	2.002	2.028	2.009	2.002
ZnO	2.003	2.051	2.009	2.002

of the satellites d_1 and d_3 in our new samples is somewhat mysterious. We have observed, however, that they can be reproduced by contacting the TiO_2 sample before evacuation with 4n ammonia.

The signal C earlier reported is now considered to be caused by line-broadening of B as a consequence of physical adsorption of O_2 .

Consequent to the reevaluation of the ESR spectrum we consider it necessary to replace our former suggestions concerning the structure of the species by a new one. As in the earlier hypothesis the B signal is ascribed to the species O_2^- , but the A signal is now believed to belong to O^- [see Kwan (7)]. Full details of the work will be reported in the near future.

REFERENCES

1. IYENGAR, R. D., CODELL, M., AND TURKEVICH, J., *J. Catalysis* **9**, 305 (1967).
2. CORNAZ, P. F., VAN HOOFF, J. H. C., PLUYM, F. J., AND SCHUIT, G. C. A., *Discussions Faraday Soc.* **41**, 290 (1966).
3. VAN HOOFF, J. H. C., AND VAN HELDEN, J. F., *J. Catalysis* **8**, 199 (1967).
4. IYENGAR, R. D., CODELL, M., KARRA, J. S., AND TURKEVICH, J., *J. Am. Chem. Soc.* **88**, 5055 (1966).

5. KAZANSKII, V. B., Intern. Symp. on Heterogeneous Catalysis, Roermond, 1967.
6. LU TUN SIN, AND RAPOPORT, V. L., *Vestn. Leningradskogo Universiteta. Ser. Fiz. Khim.* **21**, 45 (1966).
7. KWAN, T., *Proc. Intern. Congr. Catalysis*, 3rd, Amsterdam, 1964 **1**, 493.

J. H. C. VAN HOOFF

*Dept. of Inorganic Chemistry
Technological University Eindhoven
The Netherlands*

Received May 9, 1968