High-speed NMR imaging of capillary action in thin nontransparent porous media

Citation for published version (APA):

Nicasy, R., Huinink, H. P., Erich, S. J. F., & Adan, O. C. G. (2021). High-speed NMR imaging of capillary action in thin nontransparent porous media. *Physical Review E*, 104(4), [L043101].
<https://doi.org/10.1103/PhysRevE.104.L043101>

DOI:

[10.1103/PhysRevE.104.L043101](https://doi.org/10.1103/PhysRevE.104.L043101)

Document status and date:

Published: 01/10/2021

Document Version:

Accepted manuscript including changes made at the peer-review stage

Please check the document version of this publication:

- A submitted manuscript is the version of the article upon submission and before peer-review. There can be important differences between the submitted version and the official published version of record. People interested in the research are advised to contact the author for the final version of the publication, or visit the DOI to the publisher's website.
- The final author version and the galley proof are versions of the publication after peer review.
- The final published version features the final layout of the paper including the volume, issue and page numbers.

[Link to publication](#)

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal.

If the publication is distributed under the terms of Article 25fa of the Dutch Copyright Act, indicated by the "Taverne" license above, please follow below link for the End User Agreement:

www.tue.nl/taverne

Take down policy

If you believe that this document breaches copyright please contact us at:

openaccess@tue.nl

providing details and we will investigate your claim.

High-Speed NMR profiling of capillary action in thin non-transparent porous mediaR.Nicasy,¹ H.P.Huinink,^{1,*} S.J.F.Erich,^{1,2} and O.C.G.Adan^{1,2}¹*Eindhoven University of Technology, Applied Physics Department,
PO Box 513, 5600MB Eindhoven, The Netherlands*²*Organization of Applied Scientific Research, TNO The Netherlands, P.O. Box 49, 2600 AA Delft, The Netherlands
(Dated: October 22, 2021)*

An improved High-Speed NMR profiling method is introduced that enables to measure capillary action in thin, non-transparent porous media. Liquid profiles can be measured as fast as 10 ms with a spatial resolution of $14.5\ \mu\text{m}$. Capillary absorption of microliter-sized droplets into non-transparent nylon-6,6 porous membranes was studied. In nylon-6,6 sharp fronts obeying a 1D-Darcy model were observed. In paper uptake did not follow this model: retardation in uptake, broader fluid fronts and swelling was observed. These measurements nicely demonstrate the possibilities and versatility of the developed method.

Fast capillary imbibition processes of liquids into thin porous media are widely studied due to the occurrence in many applications, including printing [1], porous coatings [2], filtration [3] and cooling of microelectronics [4, 5]. These imbibition processes are often described with a combination of Washburn [6] and Darcy's law [7], [8]. Over the years, many theoretical studies tried to extend these fundamental relations to special cases like swellable media [9, 10] and imbibition of liquid droplets [11]. Obtaining experimental verification of these models is still challenging as it faces short time scales and high resolution to capture these processes. For example, the penetration of an ink droplet in paper happens at micrometer scale during the first 30-100 ms [1]. Furthermore, most of these processes happen in non-transparent media like paper or polymers. Common measuring techniques are not able to deal with these requirements coherently. Measurement techniques like optical microscopy cannot access fluids in non-transparent media, which limits their application. Automatic Scanning Absorptometer (ASA) [8] or weight measurements [12] are able to measure global properties like mass uptake on time scales of 10 ms, but do not give access to the liquid distribution inside the porous media. Depth information is crucial for validating Washburn and Darcy models of adsorption. More importantly, density profiles during more complex processes may provide information about swelling, front broadening, front splitting, particles motion et cetera, and could not be probed at this time and length scales before. Nuclear Magnetic resonance (NMR) on the other hand is able to extract liquid profiles, inside non-transparent porous media [13] with high resolution. However, NMR is a relatively slow technique due to its poor signal-to-noise ratio. Conventional NMR techniques cannot access the time scale and resolution needed for capillary action in thin porous media. In this letter, we demonstrate high-speed NMR to visualize liquid profiles inside thin porous media (100 - 200 μm) with a spatial resolution of $14.5\ \mu\text{m}$ and a time resolution of 10 ms. To our knowledge, for the first time liquid distribution profiles in non-transparent thin porous layers during fast

imbibition are reported. The obtained liquid profiles are used to study liquid fronts in time for different liquid mixtures inside different porous media. Finally, the technique is used to demonstrate its potential by performing capillary imbibition in printing paper. The measured liquid profiles reveal a change in sharpness of the wetting front, retardation in uptake combined with swelling of the substrate.

The NMR measurements were performed using a GARField ¹H NMR [14], designed with special poles to generate a magnetic field of 1.46 T with a gradient (G) of 40.3 [T/m]. Signals were acquired using the following pulse sequence ($90_x^\circ - \tau - [90_y^\circ - \tau - (\text{echo}) - \tau - 90_{-y}^\circ - \tau - (-\text{echo}) - \tau]_n$), which is a modification of the well known Ostroff-Waugh sequence [15]. The difference is inserting a 90_{-y}° pulse to remove the constant background signal, which after the Fourier transform would give a peak at 0 KHz, by generating alternating positive and negative echo's which after addition will cancel out this constant background. The echo time $t_e = 2\tau$ is equal to 50 μs with an acquisition time (t_a) of 40 μs from which the theoretical resolution can be calculated with $\Delta x = 1/t_a \gamma G = 14.5\ \mu\text{m}$ [16], where the gyromagnetic ratio of water was used ($\gamma = 42.58\text{MHz/T}$). The solid-state echo is preferred above the more widely used carr-purcell-meiboom-gill (CPMG) sequence because it only uses 90_{-y}° pulses. A CPMG sequence will use both 90° and 180° pulses that will excite slightly different regions because the excitation bandwidth will depend on the type of pulse (length and power) [17]. The use of only one type of pulse (90°) ensures to have always the same excitation profile. Because every hydrogen nuclei has a small magnetic moment, the signal will be linear dependent on the hydrogen content. Between two measurements, the delay time is set larger than 3 times T_1 to ensure 95% signal restoration. Because some penetration experiments take only 100 ms, measurement speed is the most important factor. Therefore, 3 times T_1 was chosen above the more conventional 5 times T_1 which only reduces signal recovery from 99% ($5T_1$) to 95% ($3T_1$) but halves the measurement time. To be able to reduce this

TABLE I: Physical properties of water-glycerol mixtures used in this study

Mixture composition Water:Glycerol (wt%)	Viscosity η ($mPa.s$)	Surface tension σ (mN/N)
100:0	0.89	72.3
75:25	1.89	70.7
50:50	5.38	68.5
30:70	20	66.1

delay time, 0.1 M $CuSO_4$ was added to the liquid mixtures to lower the corresponding T1 times. Depending on the timescale of the imbibition process, the delay time used in our experiments was set between 10-50 ms. The final hydrogen profiles are obtained by adding the first 16 even positive echoes and subtracting the first 16 odd negative echoes ($n = 16$) off the above mention sequence. Depending on the penetration speed of the experiment, n was set to 32 in order to increase signal-to-noise increasing the measurement time to 3.2 ms. By using different echoes of the sequence to generate a single profile, the signal-to-noise can be improved. Using this method, the averaging repetition of a conventional NMR-sequence is avoided and circumventing waiting 3 times T1 between every measurement. This effectively results in averaging every echo time ($50 \mu s$) leading to a 1.6 ms ($n = 16$) or 3.2 ms ($n = 32$) total acquisition time to measure a single liquid profile. The obtained profiles were normalised with a reference measurement performed on a 0.1 M $CuSO_4$ solution to compensate for the coil sensitivity. Finally, to lower signal-to-noise, individual points were time averaged but not averaged over different positions which by consequence leaves the resolution unchanged. Displayed in figure 1 is a schematic representation of the setup. The sample lies directly above the RF-coil which has a diameter of 4 mm, corresponding to the sensitive region [18]. Lastly, the setup used a mounted Hamilton micro syringe to generate microlitre droplets that fall on top of a porous sample. To cover a range of viscosity, water-glycerol mixture were used. The composition of the liquids and their physical parameters are shown in table I. The porous materials used in this study are Whatman nylon-6,6 membranes and Mondi Niveus Top printing paper. The Whatman nylon-6,6 membranes have two different pore diameters, $0.42 \mu m$ and $0.53 \mu m$ and a thickness of $165 \mu m$. The porosity of the membranes were 0.62 and 0.67, respectively. Both porosity and pore diameter were measured using mercury intrusion porosimetry (MIP). The Mondi Niveus Top printing paper is an uncoated paper with a pore radius of $4 \mu m$, thickness of $90 \mu m$ and weight of $80 gsm$.

To start the experiment, a microliter-sized droplet is jetted from the syringe. When the droplet reaches the top of the nylon sample, it starts to penetrate the porous

FIG. 1: Schematic representation of the measurement setup.

media. Liquid profiles were measured for all water glycerol mixtures in both nylon substrates. The 1D liquid profiles from a 50wt% glycerol mixture penetrating the $0.42 \mu m$ pore diameter nylon membrane are shown in figure 2. The top of the nylon membrane, determined experimentally, is set to the zero position and liquid profiles are taken every 25 ms. In blue, the liquid profile is shown just before the droplet falls on the nylon membrane. As time progresses, the liquid penetrates into the nylon membrane, indicated by the black arrow. The penetration continues until the liquid reaches the bottom of the membrane at $165 \mu m$. The signal intensity after complete filling is 0.63, which agrees with the porosity of the sample as determined by MIP. The low signal-to-noise ratio of the experiments causes the undulations observed in the maximum signal intensity of the liquid profiles. The profiles in figure 2 reveal that also on micrometer scale the liquid penetrates with a sharp moving front inside the porous media. From these liquid profiles, the front position ($l[m]$) is taken at the position where the liquid signal is around 50% of its saturation level. This exact point is calculated by interpolating the two nearest measurements points. Some deviations may still occur due to the spatial resolution of the measurements points ($14.5 \mu m$).

To describe front progress shown in figure 2, we adopted a sharp front formalism in combination with Darcy's law. Assuming an incompressible liquid, the fluid flow can be described by 3D mass conservation with $\nabla \cdot \mathbf{q} = \nabla^2 P = 0$ [8]. Where $\mathbf{q}[m^2/s]$ represent the fluid flux through the porous media, described by Darcy's Law, [8]

$$\mathbf{q} = \frac{-k}{\eta} \nabla P \quad (1)$$

with $k[m^2]$ the permeability, $\eta[Pa.s]$ the viscosity and $P[Pa]$ the pressure. Because the pressure gradient scales with liquid penetration, we will compare the pressure gradients in all directions. As the main pressure component in spontaneous imbibition is the capillary pressure P_c , the maximum pressure drop P observed in any direc-

tion should be similar to P_c . P_c can be described by the Young-Laplace equation for capillary pressure,

$$P_c = \frac{2\sigma \cos(\theta)}{r} \quad (2)$$

where $r[m]$ is the pore radius, $\sigma[N/m]$ the surface tension and $\theta[^\circ]$ the liquid-surface contact angle. After using cylindrical coordinates and leaving out the angular coordinate, because the droplet is axisymmetric, we obtain:

$$\nabla^2 P = \frac{1}{R^2} \frac{1}{r'} \frac{\partial}{\partial r'} \left(r' \frac{\partial P}{\partial r'} \right) + \frac{1}{l^2} \frac{\partial^2 P}{\partial z'^2} = 0 \quad (3)$$

where we have introduced normalized coordinates $r' = r/R$ and $z' = z/l$ with the droplet radius $R[m]$ and nylon thickness l . After rewriting this expression, we end up with

$$\epsilon \frac{1}{r'} \frac{\partial}{\partial r'} \left(r' \frac{\partial P}{\partial r'} \right) + \frac{\partial^2 P}{\partial z'^2} = 0 \quad (4)$$

FIG. 2: Liquid profiles measured by GARField ^1H NMR of a 50 wt% glycerol mixture inside a $0.42 \mu\text{m}$ pore diameter nylon membrane. Profiles are measured every 25 ms and the top of the nylon membranes is set to the 0 position. The squares mark the fluid front positions. In blue, the signal acquired just before the droplet hits the sample surface is shown.

where $\epsilon = (l/R)^2$. From eq. 4, it becomes clear that the problem can be assumed 1D, when the following condition is met, $\epsilon \ll 1$. By comparing the typical droplet radius (2 mm) and the nylon thickness ($165 \mu\text{m}$), ϵ can be estimated to be 0.0068, showing that the process can be considered as a 1D process. The same condition also holds for paper with a thickness of $90 \mu\text{m}$.

Now that we have proven that the liquid penetration in the setup can be assumed to be 1D, we are able to compare our results to 1D-models found in literature. Assuming a homogeneous porous structure, the imbibition

of the liquid front l can be described according to Darcy's Law in 1D [19], where a constant and isotropic permeability $K[m^2]$ is assumed throughout the sample. Using the capillary pressure (eq. 2) and the following scaling relation for permeability in function of the pore radius $K = K_0 r^2$ [20], an expression for the imbibition front in 1D is obtained [8],

$$l(t)^2 = \frac{4K_0 \cos(\theta)}{\phi} \frac{\sigma r t}{\eta} \quad (5)$$

with $\phi[\%]$, the porosity of the substrate. To test the Darcy scaling with surface tension σ , pore radius r and viscosity η , imbibition experiments were carried out with different water-glycerol mixtures and nylon membranes with two different pore diameters ($0.42 \mu\text{m}$ and $0.53 \mu\text{m}$). The front positions are determined as described in figure 2. Results are shown in figure 3, where the front position is plotted as function of the square root of time. For all different viscosities and pore radii, a linear behaviour between l and $\sqrt{t}$ is observed.

FIG. 3: Imbibition experiments for different water-glycerol mixtures (0, 25, 50 and 75wt% glycerol) in nylon membranes with different pore radius ($r = 0.21 \mu\text{m}$ and $r = 0.27 \mu\text{m}$). The legend gives the amount of glycerol in wt% and the pore radius of the nylon membranes in μm . The fluid front position is given as function of $\sqrt{t}$.

The experiments stop at $l = 165 \mu\text{m}$, where the end of the membrane is reached. For both pore radii, the rate of penetration slows down with increasing glycerol concentration. In addition, a smaller pore radius leads to a slower imbibition at similar glycerol water ratios. To validate the predicted scaling by Darcy's law (eq. 5), the penetration fronts are plotted as a function of rescaled time $\sqrt{\sigma r / \eta} \sqrt{t} [mm]$, figure 4. After rescaling, the absorption measurements coincide on a single master curve. Because other scaling parameters like the permeability and

porosity are media dependent, this indicates that the dependency on viscosity and surface tension are correct. The corresponding slope of the mastercurve, being 170, can be used to estimate the dimensionless permeability K_0 . When using a typical contact angle for water on nylon-6,6 of 70° [21] and the according porosity, K_0 was calculated to be 0.016 and 0.018 for the 0.43 and 0.53 μm pore diameters, respectively. This value is in good agreement with values found in Tomadakis et al. [22], who summarised values for the dimensionless permeability in function of porosity, calculated from different models and experimental results.

Extracting moisture profiles at this timescale during capillary imbibition has never been done before. Measuring these profiles allows to investigate physical phenomena with spatial resolution. To illustrate the capability of the measurement technique, imbibition experiments with a top printing paper (Mondi Niveus) were measured. Profiles were taken every 0.3 s with a 0.25M CuSO_4 solution and can be seen in figure 5. In blue, the signal acquired just before the droplet hits the sample surface is shown. In the beginning of the experiment, the paper-liquid interface situates at position 0, marked with a dashed line in figure 5. The initial paper position ranges from 0 - 100 μm and has a maximum intensity of 0.6 due to the porosity of paper. Positions above the paper have a signal intensity of one and are taken up by the droplet. The first liquid profiles overlap indicating a retardation in the fluid front which was not observed in nylon-6,6. After this retardation, the liquid starts to penetrate inside the paper indicated by the black arrow. The measurement also revealed a swelling front of the paper, red arrow in figure 5, that could be measured over time. A corresponding front versus time graph for swelling (red) and penetration (black) is shown on the top right of figure 5. From this figure, it can be clearly observed that a retardation period is followed by a period of penetration. The retardation is probably the effect of sizing, a technique commonly used in paper to provide resistance against penetration of liquids [23]. Mondi Niveus top printing paper has a high amount of AKD sizing which can clarify the retardation. However, further studies are required to investigate this relationship. When comparing swelling with penetration it can be concluded that in the case of water, the swelling front and penetration front will start at almost the same time round 3 minutes. The liquid profiles during penetration are less sharp than the ones found in nylon-6,6. This can be easily viewed when comparing the profiles from figure 2 and 5 where in the printing paper it can be observed that liquid fronts span the whole width of the sample while in the nylon-6,6 this is not the case. From the last experiment, it can be concluded that liquid penetration in paper is a much more complex process where swelling, broader liquid fronts and retardation in uptake are observed.

Explaining these phenomena requires further research but lies beyond the scope of this letter. Measuring the shape of the fluid front, combined with swelling in one experiment at this time and length scales have not been recorded before.

In this study, we developed a High-speed NMR technique able to measure the liquid penetration in thin porous media with a time resolution of 10 ms and a spatial resolution of 14.5 μm . We demonstrated that this technique can be used to measure liquid profiles inside non-transparent thin porous media from which penetration behaviour can be studied. The measurements revealed that for the nylon-6,6 and water-glycerol mixtures, imbibition at this scale happens with a sharp moving liquid front. The liquid front position for different water-glycerol mixtures varied with the square root of time and could be described by a 1D-Darcy model for capillary action. It was shown that in this media the Darcy scaling with viscosity, surface tension and pore radius could be observed at this particular time and length scales. Using this model, the dimensionless permeability of the nylon samples were calculated, which agreed well with values found in literature. Lastly, measurements in paper revealed deviations from this 1D-Darcy law, a retardation in uptake, broader fluid fronts and the occurrence of swelling. For the first time, the high spatial and time resolution of this technique allows to study the liquid penetration process in thin non-transparent porous media at small time and length scales.

We acknowledge Hans Dalderop (TU/e) and Jef Noijen (TU/e) for their support with regarding the setup and sample preparation. The authors would like to thank Peter Lipman (TU/e) for doing the MIP measurements. This publication is part of the project PQP (Print Quality and Particles) (with project number 17099) of the research programme Collaboration program High Tech Systemen en Materialen (HTSM) 2018 TTW] which is (partly) financed by the Dutch Research Council (NWO). Lastly we would like to thank DSM and Canon Production Printing for their support.

FIG. 4: The liquid penetration depth as function of the rescaled time for the different water-glycerol mixtures (0, 25, 50 and 75wt% glycerol) in nylon membranes with different pore radii ($r = 0.21 \mu\text{m}$ and $r = 0.27 \mu\text{m}$) membranes.

FIG. 5: Liquid profiles for a 0.25M CuSO_4 solution in Mondi Niveus Top printing paper. For clarity, the initial paper-liquid interface at position $0 \mu\text{m}$ is marked with a dashed line. Shown in top right are the liquid front (black) and swelling front/paper-liquid interface (red) which are indicated by arrows in the main figure. In blue, the signal acquired just before the droplet hits the sample surface is shown.

- [1] S. Krainer, C. Smit, and U. Hirn, The effect of viscosity and surface tension on inkjet printed picoliter dots, *RSC advances* **9**, 31708 (2019).
- [2] A. Genbach, N. Jamankulova, I. Iliev, and A. Terziev, Study of fragile capillary-porous coatings in power installations, *E3S Web of Conferences* **85**, 10.1051/E3SCONF/20198505002 (2019).
- [3] H. A. Fadel, Water treatment by fabric capillary action: New technique with ancient origins, *Journal-American Water Works Association* **106**, 44 (2014).
- [4] S. H. Moon and G. Hwang, Development of the micro capillary pumped loop for electronic cooling, *Collection of Papers Presented at The 13th International Workshop on THERMal INvestigation of ICs and Systems, THERMINIC*, 72 (2007).
- [5] W. Wits, R. Legtenberg, and J. Mannak, Selecting capillary structures for heat pipes in multilayer printed circuit boards, *European Thermal-Science, The Netherlands* (2008).
- [6] J. Schoelkopf, P. A. Gane, C. J. Ridgway, and G. P. Matthews, Practical observation of deviation from lucas-washburn scaling in porous media, *Colloids and Surfaces A: Physicochemical and Engineering Aspects* **206**, 445 (2002).
- [7] J. Fabricius, J. G. I. Hellström, T. S. Lundström, E. Miroshnikova, and P. Wall, Darcy's law for flow in a periodic thin porous medium confined between two parallel plates, *Transport in Porous Media* **115**, 473 (2016).
- [8] C. Kuijpers, T. van Stiphout, H. Huinink, N. Tomozeiu, S. Erich, and O. Adan, Quantitative measurements of capillary absorption in thin porous media by the automatic scanning absorptometer, *Chemical Engineering Science* **178**, 70 (2018).
- [9] M. Kwick, D. M. Martinez, D. R. Hewitt, and N. J. Balmforth, Imbibition with swelling: Capillary rise in thin deformable porous media, *Physical Review Fluids* **2**, 074001 (2017).
- [10] R. Masoodi and K. Pillai, Darcy's law-based model for wicking in paper-like swelling porous media, *AIChE Journal* **56**, 2257 (2010).
- [11] A. Clarke, T. Blake, K. Carruthers, and A. Woodward, Spreading and imbibition of liquid droplets on porous surfaces, *Langmuir* **18**, 2980 (2002).
- [12] S. Gruener and P. Huber, Capillarity-driven oil flow in nanopores: Darcy scale analysis of lucas-washburn imbibition dynamics, *Transport in Porous Media* **126**, 599 (2019).
- [13] C. Kuijpers, H. Huinink, N. Tomozeiu, S. Erich, and O. Adan, Sorption of water-glycerol mixtures in porous Al_2O_3 studied with nmr imaging, *Chemical Engineering Science* **173**, 218 (2017).
- [14] P. Glover, P. Aptaker, J. Bowler, E. Ciampi, and P. McDonald, A novel high-gradient permanent magnet for the profiling of planar films and coatings, *Journal of Magnetic Resonance* **139**, 90 (1999).
- [15] E. Ostroff and J. Waugh, Multiple spin echoes and spin locking in solids, *Physical Review Letters* **16**, 1097 (1966).
- [16] P. J. McDonald and B. Newling, Stray field magnetic resonance imaging, *Reports on Progress in Physics* **61**, 1441 (1998).
- [17] B. Blumich, NMR Imaging of Materials, *NMR Imaging of Materials* 10.1093/ACPROF:OSO/9780198526766.001.0001

* To whom correspondence should be addressed. h.p.huinink@tue.nl

- (2010).
- [18] S. J. Erich, J. Laven, L. Pel, H. P. Huinink, and K. Kopinga, Influence of catalyst type on the curing process and network structure of alkyd coatings, *Polymer* **47**, 1141 (2006).
 - [19] H. Huinink, *Fluids in Porous Media*, 2053-2571 (Morgan , Claypool Publishers, 2016).
 - [20] J. B. Walsh and W. Brace, The effect of pressure on porosity and the transport properties of rock, *Journal of Geophysical Research: Solid Earth* **89**, 9425 (1984).
 - [21] D. K. Owens and R. Wendt, Estimation of the surface free energy of polymers, *Journal of applied polymer science* **13**, 1741 (1969).
 - [22] M. M. Tomadakis and T. J. Robertson, Viscous permeability of random fiber structures: comparison of electrical and diffusional estimates with experimental and analytical results, *Journal of Composite Materials* **39**, 163 (2005).
 - [23] H. L. Lee and J. Shin, Surface sizing with cationic starch: Its effect on paper quality and papermaking process, *Article in Tappi Journal* (2002).