Chemical reaction engineering aspects of a rotary reactor for carbothermal synthesis of SiC

Citation for published version (APA):

van Dijen, F. K., & Metselaar, R. (1989). Chemical reaction engineering aspects of a rotary reactor for carbothermal synthesis of SiC. *Journal of the European Ceramic Society*, 5(1), 55-61.
[https://doi.org/10.1016/0955-2219\(89\)90009-5](https://doi.org/10.1016/0955-2219(89)90009-5)

DOI:

[10.1016/0955-2219\(89\)90009-5](https://doi.org/10.1016/0955-2219(89)90009-5)

Document status and date:

Published: 01/01/1989

Document Version:

Publisher's PDF, also known as Version of Record (includes final page, issue and volume numbers)

Please check the document version of this publication:

- A submitted manuscript is the version of the article upon submission and before peer-review. There can be important differences between the submitted version and the official published version of record. People interested in the research are advised to contact the author for the final version of the publication, or visit the DOI to the publisher's website.
- The final author version and the galley proof are versions of the publication after peer review.
- The final published version features the final layout of the paper including the volume, issue and page numbers.

[Link to publication](#)

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal.

If the publication is distributed under the terms of Article 25fa of the Dutch Copyright Act, indicated by the "Taverne" license above, please follow below link for the End User Agreement:

www.tue.nl/taverne

Take down policy

If you believe that this document breaches copyright please contact us at:

openaccess@tue.nl

providing details and we will investigate your claim.

Chemical Reaction Engineering Aspects of a Rotary Reactor for Carbothermal Synthesis of SiC

F. K. van Dijen

DSM Research, Ceramics Department, Geleen, The Netherlands

&

R. Metselaar

Laboratory for Physical Chemistry/Centre for Technical Ceramics, Eindhoven University of Technology, The Netherlands

(Received 30 January 1989; revised version received 30 March 1989; accepted 14 April 1989)

Abstract

Heat transfer in a rotary reactor is described for a reactor consisting of a graphite tube with graphite heating elements, and operating at temperatures between 1773 and 2273 K. Under those conditions heat transfer is very good due to radiation and the high thermal conductivity of graphite. An overall coefficient of heat transfer of at least 400 W/m²K is estimated. As an example of the application of a rotary reactor the carbothermal production of SiC is described. A general conclusion is that rotary reactors are well suited for the endothermal reactions.

Der Wärmetransport in einem Rotationsreaktor wird für einen Reaktor, der aus einem Graphitrohr mit Graphitheizelementen besteht, im Temperaturbereich zwischen 1773 und 2273 K beschrieben. Unter diesen Bedingungen ist der Wärmetransport aufgrund der Wärmestrahlung und der hohen Wärmeleitfähigkeit von Graphit sehr gut. Es wurde ein totaler Wärmeübergangskoeffizient von 400 W/m² K bestimmt. Als Anwendungsbeispiel für einen Rotationsreaktor wird die karbothermische Reaktion von SiC beschrieben. Generell kann gesagt werden, daß Rotationsreaktoren sich gut für endotherme Reaktionen eignen.

On décrit les transferts de chaleur dans un réacteur tournant pour un réacteur constitué d'un tube de graphite muni d'éléments chauffants en graphite et travaillant entre 1773 et 2273 K. Dans ces conditions, le transfert de chaleur est très bon en raison du rayonnement et de la conductivité thermique élevée du graphite. On estime le coefficient global de transfert thermique à au moins 400 W/m²K. La synthèse carbothermique de SiC est choisie comme exemple d'application d'un réacteur rotatif. De manière

générale, les réacteurs de ce type sont bien adaptés aux réactions endothermiques.

1 Introduction

Pure, submicron SiC powder can be produced from SiO₂ and C on a small scale.¹ However, on a larger scale considerable problems are encountered, the selection of the type and design of reactor being poorly described in literature. The moving bed reactor and the rotary reactor have attracted most attention.^{2–4} The application of a simple moving bed reactor with indirect heating is limited to reactors with relatively small diameters. The inner diameter of such reactors is usually smaller than 150 mm due to poor heat transfer.⁵ Part of the chemical reaction engineering of a simple, indirectly heated moving bed reactor is described in the literature.^{5,6} We discuss here the chemical reaction engineering aspects of a rotary reactor applied to the carbothermal production of SiC from silica and carbon. We will also describe some experimental results obtained with such a reactor.

2 Reactor Engineering Aspects of Carbothermal Production of SiC

2.1 The carbothermal reaction

The formation of SiC is described by the overall reaction

1 kg of a silica–carbon mixture will result in 415 g of SiC at 100% conversion. Usually a small carbon excess is used. Above a temperature of 1510°C the

partial CO pressure is higher than 1 bar (10^5 Pa) and, when the reaction takes place at 1 bar total pressure, the CO is forced out of the granules, the bed and the reactor. Under such conditions a reaction rate controlled by gas diffusion or mass transfer is not expected. The reaction is endothermic, with a reaction enthalpy of 604 kJ/mol SiC.

The reaction involves nucleation and growth of SiC particles. Two mechanisms for the growth are possible. The first is a direct solid state reaction;⁶ the second consists of a solid state reaction followed by a gas-solid reaction and involves the gaseous SiO:

and

Although direct solid state diffusion is probably the main mechanism, the formation of SiO is always observed in practice.

The main parameters determining the particle size of SiC are reaction time, temperature, impurities, type of carbon, and the presence of SiC particles which act as nuclei.

Usually β -SiC is obtained. When the reaction is carried out on a laboratory scale with excess silica in a nitrogen atmosphere, α -SiC is then obtained due to the incorporation of nitrogen in the structure.⁷

2.2 The rotary reactor

Rotary reactors are often used for the processing of solids. They have the advantage that the heat transfer is good and that the operation is simple. We can distinguish between directly and indirectly heated reactors. Examples of the first type are rotary reactors used for the production of cement and ferrites. Examples of the second type with a graphite tube are less common, but are found in the production of tungsten carbide and for some other high temperature processes in non-oxidizing atmospheres.⁸ Although some authors suggest that the indirectly heated reactors are new, this is certainly not the case.³ An example of such a reactor for the synthesis of SiC with heating elements inside the tube is described in a Japanese patent.⁹ We have applied this type of reactor to the carbothermal synthesis of SiC, using a rotary reactor with a graphite tube and graphite heating elements outside the tube.

The working conditions are the following. The degree of filling is usually 5–25% volume. The ideal movement of the solid particles is shown in Fig. 1.

Fig. 1. Ideal radial movement of solids in a rotary reactor. The hatched area indicates the volume where the granules move upwards. The blank area with the arrow is the volume where the granules are rolling downwards.

Typical data are: rotational speed 1–10 rpm, inclination 1–5°, residence time 0.25–3 h and length to diameter ratio about 10. The heated length may be up to 3.5 m. Under the right conditions the bed is radially mixed after 3 rotations.¹⁰ When the rotational speed is too low the movement of the solid is poor and there is insufficient radial mixing.¹¹ At a high rotational speed the particles are pressed against the wall by the centrifugal force. The residence time in the heated zone can be estimated from eqns (1a) and (1b):

$$t = KL / (ND \tan \alpha) \quad (1a)$$

and

$$t = 4V_f / (\gamma \pi DL) \quad (1b)$$

Here L is the length of the heated zone, N the rotational speed in revolutions per unit time, γ the degree of filling, V_f the volume flow, D the inner tube diameter, and α the angle of inclination. K is a factor depending on the degree of filling.

Equation (1a) is the mathematical description of the movement of a particle or granule in the heated zone. The displacement in the longitudinal direction of the heated zone is $D \tan \alpha / K$ per revolution. The dimensionless constant K is approximately 0.2. Equation (1b) gives the volume flow divided by the volume of the bed in the heated zone.

Under most reaction conditions the residence time distribution can be neglected, i.e. the particles move like in a plug flow.^{11,12} In order to prevent segregation the use of a uniform granulate is advised.¹³

2.3 Heat transfer

When a reaction is both fast and endothermic, like the carbothermal reaction of SiO_2 with C, it is of importance to have a high heat transfer in order to prevent a reaction rate limited by heat transfer. In this section we consider the heat transfer characteristics of a rotary reactor. To this end we distinguish heat transfer from the heating elements to the tube, heat transfer through the tube and heat transfer from the tube to the bed. These terms contribute to the overall resistance to heat transfer, $1/U$, according to

$$1/U = (R \ln(1 + d/R))/\lambda + R/(\alpha_1(R + d)) + 1/\alpha_2 \quad (2)$$

R is the inner radius of the tube, d the tube thickness, λ the thermal conductivity of the tube, α_1 the coefficient of heat transfer from the elements to the outer tube surface, and α_2 is the coefficient of heat transfer from the inner tube surface to the bed.

Both conduction, convection and radiation will be taken into account. Heat losses, e.g. axial heat losses from the tube, or losses through the insulation, etc. are not considered however. The heat produced by the elements is consumed by heating up the SiO_2/C granules and by the reaction only.

For the reaction zone we can write

$$U_1 A_1 \Delta T = HV \quad (3)$$

where A_1 is the surface through which the heat is transported, ΔT the temperature difference between the heating elements and the bed, V the volume of the bed in the reaction zone and H the reaction enthalpy per unit volume and per unit time. When L_1 is the length of the reaction zone and γ the degree of filling, we have $A_1 = 2\pi R L_1$ and $V = \gamma \pi R^2 L_1$.

For the zone where the granulate is heated eqn (4) holds

$$F C_p dT_1 = dA_2 U_2 (T_0 - T_1) \quad (4)$$

F is the mass flow, C_p the specific heat, dA_2 the surface through which the heat is transported, $(T_0 - T_1)$ the temperature difference between the elements and the bed and dT_1 the temperature increase of the bed. This equation indicates that the energy which is transferred from the heating elements to the bed is used entirely to heat up the granules or particles which enter the heated zone. It takes time to heat up the granules; this heating time is equivalent to the distance travelled by the granules before they are heated up. Then dL_2 is the length of the zone where the material is heated to, say, 97% of the reaction temperature we have

$$dA_2 = 2\pi R dL_2 \quad (5)$$

Table 1. The thermal conductivity of Ar, CO and N_2 in W/mK

Temperature (K)	Gas		
	Ar	CO	N_2
293	0.017	0.025	0.025
2073	0.084	0.125	0.125

We shall subsequently describe the three contributions to U .

2.3.1 Heat transfer from the elements to the tube

The coefficient of heat transfer from the elements to the outside of the tube, α_1 , can be written as

$$\alpha_1 = \alpha_{\text{cond}} + \alpha_{\text{conv}} + \alpha_{\text{rad}}$$

The conduction term can be calculated from the thermal conductivity, λ_g , and the distance x between the tube and the elements: $\alpha_{\text{cond}} = \lambda_g/x$. Table 1 gives conductivity values for some gases. For $x \geq 0.05$ m one gets $\alpha_{\text{cond}} \leq 2.5 \text{ W/m}^2\text{K}$. This is a relatively small value and we will see that this term can be neglected in our calculations.

The coefficient of heat transfer due to convection can be calculated from the Nusselt number, N_u ¹⁴

$$N_u = 0.55 (P_r G_r)^{1/4} \quad (6)$$

Here the Prandtl number P_r is only weakly temperature dependent and is 0.68 for N_2 and CO and 0.53 for Ar. G_r , the Grashof number can be calculated from eqn (7)¹⁴

$$G_r = \Delta Q Q g h^3 / (\mu^2) \quad (7)$$

Q is the density of the gas when at the heating element temperature, ΔQ the difference in density of the gas at the tube and at the elements, μ the dynamic viscosity, g the gravitational constant and h the outside tube diameter. Table 2 gives some physical data of the relevant gases and Table 3 gives data for α'_{conv} as a function of the tube diameter and the temperature difference. The average temperature is taken at 2073 K. From Table 3 it can be seen that the value for α'_{conv} is maximally $6 \text{ W/m}^2\text{K}$. As we have heat transfer from the elements to the gas and from the gas to the tube $\alpha_{\text{conv}} = \frac{1}{2} \alpha'_{\text{conv}}$, which is less than $3 \text{ W/m}^2\text{K}$.

Table 2. The dynamic viscosity μ and the density Q for three gases at 2073 K.

Gas	$\mu (\text{Ns/m}^2)$	$Q (\text{kg/m}^3)$
N_2	65×10^{-6}	0.165
CO	67×10^{-6}	0.165
Ar	85×10^{-6}	0.235

Table 3. α'_{conv} in $\text{W/m}^2\text{K}$ at 2073 K as a function of the outer tube diameter $2(d + R)$ and temperature difference ΔT between the heating elements and the outer tube surface

Diameter (m)	CO or N ₂		Ar	
	$\Delta T = 100\text{ K}$		$\Delta T = 200\text{ K}$	
	$\Delta T = 100\text{ K}$	$\Delta T = 200\text{ K}$	$\Delta T = 100\text{ K}$	$\Delta T = 200\text{ K}$
0.1	4.7	5.6	3.1	3.6
0.5	3.1	3.7	2.0	2.4

Finally we estimate the contribution of radiation to the heat transfer from the elements to the tube. Here we use the well known expression^{14,15}

$$\alpha_{\text{rad}} = \{(T_1/100)^4 - (T_2/100)^4\} C_{12}/(T_1 - T_2) \quad (\text{W/m}^2\text{K}) \quad (8)$$

Here T_1 is the temperature of the elements, T_2 is the temperature of the outer tube surface. The radiation factor C_{12} can be calculated from eqn (9)

$$C_{12} = 5.67/\{1/e + F_1/F_2(1/e - 1)\} \quad (\text{W/m}^2\text{K}^4) \quad (9)$$

When both the elements and the tube are made of graphite the emissivity coefficient e is about 0.9. F_2 is the surface area of the tube in the heated zone, $F_2 = 2\pi(R + d)L$. F_1 is the surface area of the elements and it also accounts for the heating of the outer tube surface by reflection from the insulation. For our calculation we take F_1 as a cylinder with surface $2\pi(R + d + x)L$, x being the distance between the tube and elements/insulation. In Table 4 values for C_{12} are given as a function of x and the outside tube diameter. From this table we can see that C_{12} decreases with x , but is approximately equal to 4.0. In Table 5 we show α_{rad} for different values of T_1 and T_2 . From these data it is evident that α_{rad} is much larger than α_{conv} and α_{cond} . It can also be seen that α_{rad} is large when the difference $T_1 - T_2$ is small or when T_1 is high.

From these calculations we conclude that heat transfer from the heating elements to the tube is dominated by radiation and that both conduction and convection can be neglected. The value for α_1 is estimated to be 1000–1800 $\text{W/m}^2\text{K}$.

Table 4. The influence of the tube-element distance x and the outer tube diameter on C_{12} , with emissivity $e = 0.9$

$x(\text{m})$	Outer tube diameter (m)		
	0.1	0.3	0.5
0.05	4.26	4.51	4.57
0.10	3.93	4.38	4.49
0.20	3.41	4.15	4.33

Table 5. α_{rad} and α_{wbr} in $\text{W/m}^2\text{K}$ for different values of T_1 , T_2 , T_3 and T_4 , with $C_{12} = 4.0$

T_2 or T_4 (K)	T_1 or T_3 (K)					
	2 273	2 173	2 073	1 973	1 873	1 773
2 173	1 760					
2 073	1 650	1 530				
1 973	1 540	1 430	1 330			
1 873	1 440	1 330	1 230	1 140		
1 773	1 340	1 240	1 140	1 050	907	
1 673	1 260	1 160	1 060	980	890	820

2.3.2 Heat transfer through the tube

Heat is transported through the tube by conduction only. The thermal conductivity of graphite depends on the temperature, the orientation of the particles, the porosity, etc. For our purpose we will assume a value for the thermal conductivity of graphite at high temperatures of 30 W/mK .¹⁶ The second term in eqn (2) can be simplified to d/λ when $d/R \ll 1$. In Table 6 values for $R \ln(1 + d/R)/\lambda$ are given as a function of d and R . The average value for the inverse quantity $\lambda/(R \ln(1 + d/R))$ is estimated to be between 1000 and 3300 $\text{W/m}^2\text{K}$, which is comparable with α_1 . At lower temperatures this value increases due to a decrease of λ with increasing temperature.¹⁶

Table 6. The influence of the thickness d and inner diameter $2R$ of the tube on the term $R \ln(1 + d/R)/\lambda$ with $\lambda = 30\text{ W/m K}$

$d(\text{m})$	$2R(\text{m})$		
	0.1	0.3	0.5
0.01	3.0×10^{-4}	3.2×10^{-4}	3.3×10^{-4}
0.03	7.8×10^{-4}	9.1×10^{-4}	9.4×10^{-4}

2.3.3. Heat transfer from the tube to the bed

Heat transport from the inner tube surface to the bed takes place by contact between the two, by radiation from the inner tube surface which is not in contact with the bed to the upper side of the bed and by convection and by conduction. Usually there is also a gas flow through the tube. Consequently there is no free convection but instead forced convection. Heat transfer by contact between the bed and tube can be described as a stationary or as an instationary process. For a stationary process the heat transfer can be described with eqn (10)¹⁷

$$\alpha_{\text{wbc}} = 6\lambda_b/(2R) \quad (10)$$

λ_b is the thermal conductivity of the bed; it depends on the temperature and on the size of the granulate, d_p .⁶ At 1973 K one has for a granulate with $d_p = 1\text{ mm}$ $\lambda_b = 1.5\text{ W/mK}$, for $d_p = 5\text{ mm}$ $\lambda_b = 5\text{ W/mK}$ and for $d_p = 10\text{ mm}$ $\lambda_b = 8\text{ W/mK}$. Table 7 gives

Table 7. Heat transfer coefficient by contact from the tube to the bed, according to the stationary model; α_{wbc} in $\text{W/m}^2\text{K}$ at 1973 K

Granulate diameter (mm)	Tube diameter (m)	
	0.2	0.5
1	45	18
5	150	60
10	240	96

values of α_{wbc} as a function of R and d_p . These values only hold for the part of the tube where the granulate is in contact with the tube.

For the instationary model, to describe heat transfer from the inner tube surface to the bed by contact, the Higbie penetration theory can be used.¹⁴ Lehmberg *et al.* showed that the penetration theory should be corrected for film resistance near the inner surface.¹⁰ At low temperatures, when radiation can be neglected, this correction leads to a lower value of α_{wbc} . In this regime the influence of the granulate size on α is explained by an increase of the film thickness with increasing d_p . This results in a decrease of α_{wbc} . At high temperatures radiation becomes important, film resistance becoming relatively less important and so the bed may be considered as a continuum. As far as the contribution of radiation to α_{wbc} is concerned the penetration theory seems applicable. One has

$$\alpha_{wbc,rad} = 2\{\lambda_b Q_b C_p \text{rpm}/(20\pi)\}^{1/2} \quad (11)$$

For a granulate with $d_p = 5$ mm $\lambda_{b,rad} = 4.5 \text{ W/mK}$ at 1973 K.⁶ The density of the bed Q_b , varies during the reaction, but is approximately 500 kg/m^3 . $C_p = 1570 \text{ J/kgK}$ and the rotational speed, rpm, is assumed to be 3 revolutions per minute. Substitution in eqn (11) then gives a radiation contribution to α_{wbc} of $820 \text{ W/m}^2\text{K}$.

According to the model of Lehmberg *et al.* the conduction contribution is about $100 \text{ W/m}^2\text{K}$. Therefore the total value of α_{wbc} becomes about $900 \text{ W/m}^2\text{K}$. For a granulate with $d = 1$ mm a similar calculation leads to $\alpha_{wbc} \approx 500 \text{ W/m}^2\text{K}$ at 1973 K.

For rotary reactors operating at high temperatures the models describing heat transfer by contact between the bed and the inner tube surface have not been proven experimentally. Therefore this leaves us with some uncertainty. For our calculations we use an estimated value of $\alpha_{wbc} \approx 500 \text{ W/m}^2\text{K}$. About 30% of the inner tube surface is in contact with the bed.

Seventy percent of the inner tube surface is in contact with the gas phase. From this, surface heat is transferred to the upper bed surface by radiation.

The corresponding coefficient of heat transfer, α_{wbr} , is described by eqns (12) and (13)

$$\alpha_{wbr} = \{(T_3/100)^4 - (T_4/100)^4\} C_{12}/(T_3 - T_4) \quad (\text{W/m}^2\text{K}) \quad (12)$$

$$C_{12} = 5.67/(1/e_3 + F_3/F_4(1/e_4 - 1)) \quad (\text{W/m}^2\text{K}^4) \quad (13)$$

e_3 and e_4 are the coefficients of emissivity for the tube and bed, both are about 0.9, F_3 is the tube surface in contact with the gas phase, F_4 the upper surface of the bed. T_3 is the temperature of the inner tube surface and T_4 of the upper surface of the bed. We have $F_3/F_4 = 2\pi RL0.7/(1.6RL) = 2.72$ and $C_{12} = 4.0$. In Table 5 values of α_{wbr} are given for several values of T_3 and T_4 . From this table it can be seen that α_{wbr} is quite large.

Separate heating of the upper surface of the bed is not accounted for. The heating of the upper surface of the bed is compensated by the higher energy consumption which is due to a higher reaction rate. The residence time of the granulate at the upper surface of the bed is of the order of magnitude of a few seconds, which is relatively short. So, a uniform temperature of the bed is assumed.

Heat transfer by convection between the tube and the gas phase and between the gas phase and the bed is described in literature.¹⁸ It is assumed that the heat transfer by forced convection from the tube to the bed is less than $6 \text{ W/m}^2\text{K}$. A similar calculation as given in section 2.3.1 shows that the contribution by conduction is also very small. This means that again the contributions of conduction and convection can be neglected compared to radiation.

We can now calculate α_2 from

$$\alpha_2 = 0.7\alpha_{wbr} + 0.3\alpha_{wbc} \quad (14)$$

A conservative estimation gives a value of $1000 \text{ W/m}^2\text{K}$ for α_2 .

2.4 The overall coefficient of heat transfer

By application of eqn (2) the overall coefficient for heat transfer can be estimated. Table 8 gives data for U as a function of R and d , assuming

Table 8. The overall coefficient of heat transfer U in $\text{W/m}^2\text{K}$, as a function of the inner tube diameter $2R$ and the thickness d of the tube

$d(\text{m})$	$2R(\text{m})$		
	0.1	0.3	0.5
0.01	510	490	480
0.03	400	380	370

$\alpha_1 = 1300 \text{ W/m}^2 \text{ K}$, $\alpha_2 = 1000 \text{ W/m}^2 \text{ K}$, and $\lambda = 30 \text{ W/m}^2 \text{ K}$. From the table we conclude that a value of $U = 400 \text{ W/m}^2 \text{ K}$ is a conservative estimation. This is a relatively high value, which is due to the large radiation contribution and the high thermal conductivity of graphite.

3 Experimental Results

We have performed a series of experiments to verify that a rotary reactor can be used for the production of SiC. Since solid state diffusion is important in our case for the formation of SiC the particle sizes of both silica and carbon have to be small and they have to be well mixed. Table 9 gives the analysis of the starting powders. An experimental, precipitated silica with properties similar to Aerosil ox 50 was

Table 9. Analysis of silica and carbon black

	SiO ₂ (Aerosil ox 50) ^a	Carbon (Printex U) ^a
Type	fumed	gas black
BET surface (m ² /g)	50	110
Metal content (% wt)	<0.05	<0.03
Volatile matter (% wt)	<1	<6
Moisture (% wt)	<1.5	<1
Density (g/l)	—	410 (pearls)

^a Raw materials: Degussa, Frankfurt, FRG.

Fig. 2. Optical micrograph of a precipitated silica-carbon black mixture after attrition milling. Bar length 20 μm. The white particles are silica, the black particles are carbon black.

used. The powders with a mole ratio of 1:3 were wet mixed in an attritor for 45 min, using SiC balls of 3 mm diameter. Nuclei were added prior to milling. The use of an organic liquid instead of water results in a higher chemical reaction rate, probably due to improved mixing and milling.¹⁹ After attrition milling the mixture is dried and granulated. Figure 2

Fig. 3. Thermogravimetric analysis of the carbothermal synthesis of SiC. Region 1-2 indicates the heating of the pellets, 2-3 is the isothermal part (i.e. 15 min at 1600°C), 3 indicates the cooling range.

shows an optical micrograph of the mixed powder. Each type of reactor requires a granulate with a specific size and strength. For our experiments with a rotary reactor, we used tablets with a diameter and height of 5 mm and a density of 1.1 g/ml.

First some experiments were carried out in a thermobalance (Netzsch STA 429). The tablets were heated in an alumina crucible at a rate of 20 K/min. The alumina reacts slightly with the tablets, but this does not influence the present results. As shown in Fig. 3 volatile matter is lost between 100 and 1000°C. At about 1200°C the reaction starts. At 1600°C, in flowing helium, the reaction time is usually less than 10 min. This shows that the carbothermal synthesis of SiC is fast indeed. Some SiO deposits at the outlet of the thermobalance.

The next experiments were performed in a rotary reactor with a heated length of 1.6 m and an inner tube diameter of 0.1 m. Both the reactor tube and the heating elements were made of graphite. Both ends of the tube were water cooled. The reactor was purged with 1 m³ nitrogen per hour. The tablets were fed through a lock by a vibrating feeder, and were removed from the reactor through a lock. The rotation speed was 3 rpm, the angle of inclination 2°. Further reaction conditions were: inner tube temperature 1850°C (determined by pyrometry), feed 2.0 kg/h, degree of fill about 20% vol., residence time in the heated zone about 30 min. Under these conditions 0.9 kg/h of reaction product were obtained. Runs normally lasted 9 h. The product contained maximal 10% free carbon and less than 0.5% wt of oxygen. No dust problems were encountered.

4 Discussion and Conclusion

According to eqn (3) with $U = 400 \text{ W/m}^2\text{K}$, $\gamma = 0.2$, $H = 1600 \text{ kJ/m}^3\text{s}$ and a reaction time of 30 min, the temperature difference between the heating elements and the bed is estimated to be $\Delta T = 20 \text{ K}$ for the reactor used. The experiments showed that the carbothermal reaction runs smoothly under these conditions. It should be possible to use rotary

reactors with inner diameters larger than 0.1 m, increase the degree of fill and decrease the residence time. The temperature difference ΔT increases in proportion to the tube diameter. This limits the diameter to about 0.4 m. According to eqn (4) with $U = 400 \text{ W/m}^2\text{K}$ and $C_p = 1570 \text{ J/kg K}$, the tablets were heated up after 30 mm. So, from this point of view also, a larger rotary reactor seems possible. As mentioned before, heat losses were not considered here. Cautiously, one may say that the rotary reactor seems attractive for all carbothermal reactions where CO is forced out of the granulate and out of the bed, like in the production of SiC, TiC, and others.

References

1. Shaffer, P. T. B., *Cer. Proc.*, **6** (1985) 1289.
2. Wei, G. C., *J. Am. Ceram. Soc.*, **66** (1983) C111.
3. Shaffer, P. T. B., Blakeley, K. A. & Janney, M. A., *Advances in Ceramics* Vol. 21 *Ceramic Powder Science*. The American Ceramic Society Inc., Westerville, OH 1987, p. 257.
4. Japanese Patent JP-A-59039709 A, Ibiden Co. Ltd.
5. van Dijen, F. K., Metselaar, R. & Siskens, C. A. M., *Fortschrittsber. Dtsch. Keram. Gesell.* (1985) 113.
6. van Dijen, F. K., The carbothermal production of $\text{Si}_3\text{Al}_3\text{O}_3\text{N}_5$ from kaolin, Ph.D. Thesis. Eindhoven University of Technology, 1986.
7. Dobson, M. M., *Silicon Carbide Alloys*. The Parthenon Press, Casterton Hall, Carnforth, UK, 1986.
8. Dahlstrom, D. W., Innovations in energy conservation for rotary calciners, *CEP*, November (1985) 43.
9. Atsuo Nukamoto, Japanese Patent JP-A-61236603, Nihon Cement Co. Ltd.
10. Lehmborg, J., Hehl, M. & Schugerl, K., *Powder Techn.* **18** (1977) 149.
11. Rutgers, R., *Chem. Eng. Sci.*, **20** (1965) 1079.
12. Rutgers, R., *Chem. Eng. Sci.*, **20** (1965) 1089.
13. Helmrich, H. & Schugerl, K., *Chem. Ing. Tech.*, **51** (1979) 771.
14. Bird, R. B., Stewart, W. E. & Lightfoot, E. N., *Transport Phenomena*. J. Wiley and Sons, New York, 1960.
15. Pietermaat, F. P., *Elektrothermie*, Eindhoven University of Technology, Acco, Leuven, Belgium, 1979.
16. Documentation 'Syngraphorm' Sigri Elektrographit GmbH, Meitingen, FRG.
17. Kulkarni, B. D. & Doraiswamy, L. K., *Catal. Rev. Sci. Eng.*, **22** (1980) 431.
18. Tscheng, S. H. & Watkinson, A. P., *Canad. J. Chem. Eng.*, **57** (1979) 433.
19. Hajime Saito, Japanese Patent JP-A-60246210, Kyoritsu Yogyo Genr.