Effects of the characteristics of silicon nitride powders on the preparation of α' -sialon ceramics

Citation for published version (APA):

Cao, G. Z., Metselaar, R., & Ziegler, G. (1992). Effects of the characteristics of silicon nitride powders on the preparation of α' -sialon ceramics. *Journal of Materials Science Letters*, 11(24), 1685-1686.
<https://doi.org/10.1007/BF00736208>

DOI:

[10.1007/BF00736208](https://doi.org/10.1007/BF00736208)

Document status and date:

Published: 01/01/1992

Document Version:

Publisher's PDF, also known as Version of Record (includes final page, issue and volume numbers)

Please check the document version of this publication:

- A submitted manuscript is the version of the article upon submission and before peer-review. There can be important differences between the submitted version and the official published version of record. People interested in the research are advised to contact the author for the final version of the publication, or visit the DOI to the publisher's website.
- The final author version and the galley proof are versions of the publication after peer review.
- The final published version features the final layout of the paper including the volume, issue and page numbers.

[Link to publication](#)

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal.

If the publication is distributed under the terms of Article 25fa of the Dutch Copyright Act, indicated by the "Taverne" license above, please follow below link for the End User Agreement:

www.tue.nl/taverne

Take down policy

If you believe that this document breaches copyright please contact us at:

openaccess@tue.nl

providing details and we will investigate your claim.

Effects of the characteristics of silicon nitride powders on the preparation of α' -sialon ceramics

G. Z. CAO

Laboratory of Inorganic Chemistry, Materials Science and Catalysis, University of Twente, 7500 AE Enschede, The Netherlands

R. METSELAAR

Eindhoven University of Technology, Centre for Technical Ceramics, PO Box 513, 5600 MB, Eindhoven, The Netherlands

G. ZIEGLER

Universität Bayreuth, Institut für Materialforschung (IMA), Postfach 101251, 8580 Bayreuth, FRG

Oxygen impurity is always present at the surface of silicon nitride particles [1], which plays a very important role in the densification of silicon nitride or oxynitride ceramics by forming a eutectic oxide liquid phase with oxide sintering additives during firing. Furthermore, the α -silicon nitride content, particle size and other impurities also affect the densification behaviour. This letter reports the influence of the characteristics of silicon nitride powders on the preparation of α' -sialon ceramics, which promise improved thermal shock resistance and excellent mechanical properties at high temperatures [2].

The chemical composition and properties of the silicon nitride powders used are summarized in Table I, which shows the difference in oxygen impurity and α -phase content. After powder processing the oxygen content increases and the differences become smaller. Three sets of specimens were prepared by mixing 15.25 wt % AlN (Grade C, Starck) and 9.34 wt % Y_2O_3 (99.99% purity, Ventron) to 75.41 wt % Si_3N_4 using for the different sets powders A, B and C (see Table I). After sintering α' -sialon ceramics are formed [3]. Sintering was conducted in a gas pressure furnace with a dilatometer.

The reaction sequence of the formation of α' -sialon is determined by means of X-ray diffraction (XRD). The experimental results indicate that the oxide eutectic liquid phase appears above 1300 °C, the dissolution of silicon nitride into the liquid occurs at approximately 1380 °C and the

precipitation of α' -sialon follows immediately (Fig. 1). When the temperature rises to 1800 °C the formation of α' -sialon is nearly completed. Although the impurities affect the surface tension of particles and the composition of the liquid phase, and the solubility and mobility of silicon nitride in the liquid phase are consequently varied, no difference in the reaction sequence has been observed. Similar results have been observed after the addition of some oxides into the mixtures [4]. Thus, the formation of α' -sialon is assumed to be a process which requires the presence of a liquid phase, but is not strongly influenced by the quantity and composition of this liquid phase.

The densification of α' -sialon ceramics was followed by means of *in situ* dilatometry during sintering. The shrinkage behaviour is strongly affected by the powder characteristics, as can be seen in Fig. 2. The densification of these three samples starts approximately at or above 1380 °C, which corresponds to the dissolution of nitrides into and the precipitation of α' -sialon from the liquid. However, samples B and C exhibited a very poor sinterability. Up to 1800 °C only a relative density of <76% theoretical had been reached and a large number of open pores remained. When a high nitrogen pressure of 10^7 Pa was subsequently employed at higher temperatures, no further densification was observed. In contrast, the densities decreased slightly, accompanied by a large weight

TABLE I Chemical composition of silicon nitride powders used in this investigation

	LC-12 A	DFV0014 B	DFV0015 C
O (wt %)	1.57	1.10	0.34
	1.80 ^a	1.50 ^a	0.61 ^a
C (wt %)	0.18	0.12	0.12
Fe (p.p.m.)	50	71	15
Al (p.p.m.)	44	12	8
Ca (p.p.m.)	4	3	3
$\alpha/(\alpha + \beta)$	95	71	73
FSSS (μm)	0.55	0.66	0.53

^aAfter powder processing.

Figure 1 The reaction sequence of the formation of α' -sialon; heating rate $10\text{ }^{\circ}\text{C min}^{-1}$. M, $Y_2O_3\text{-}Si_3N_4$.

(a)

(b)

Figure 2 (a) Shrinkage and (b) shrinkage rate curves for the sintering of α' -sialon ceramics based on various starting silicon nitride powders, $10^\circ\text{C min}^{-1}$.

loss (Fig. 3), probably due to a large internal surface area. The microstructure evolution suggests that for the sintering of α' -sialon ceramics contact-flattening is dominant in the early stage below 1600°C , whereas further densification is brought about mainly by the Ostwald ripening mechanism, resulting in a fast grain growth [4]. The mixtures based on silicon nitride powders with a small amount of oxygen impurity and a low α -phase content exhibit a very poor sinterability. Thus, a certain amount of oxygen impurity and high α -phase content in silicon nitride powder are considered necessary to achieve fully dense α' -sialon ceramics.

Figure 3 Densities and weight loss of α' -sialon ceramics based on various starting silicon nitride powders. (■) I, 1800°C , 0.5 MPa N_2 ; (□) II, 1900°C , 10 MPa N_2 ; and (▨) weight loss.

Figure 4 SEM micrographs of α' -sialon ceramics for samples (a) A, (b) B and (c) C.

Acknowledgement

The authors appreciate the support of the laboratory grades B and C of silicon nitride powders from Dr Wötting, Cremer Forschungsinstitut GmbH, Rödental, FRG.

References

1. M. PEUCKERT and P. GREIL, *J. Mater. Sci.* **22** (1987) 3717.
2. K. H. JACK, in "Progress in nitrogen ceramics", edited by F. L. Riley, NATO ASI Series E65 (Martinus Nijhoff, The Hague, 1983) p. 45.
3. Z. K. HUANG, P. GREIL and P. PETZOW, *J. Amer. Ceram. Soc.* **66** (1983) C96.
4. G. Z. CAO, R. METSELAAR and G. ZIEGLER, in "Ceramics Today-Tomorrow's Ceramics", edited by P. V. Vincenzini (Elsevier Science Publishers B.V., Amsterdam 1991), p. 1285.

Received 29 October
and accepted 20 December 1990