An ^{27}Al NMR study of the interaction of water with $\text{AlPO}_4\text{-11}$

Citation for published version (APA):

Peeters, M. P. J., Haan, de, J. W., Ven, van de, L. J. M., & Hooff, van, J. H. C. (1992). An ^{27}Al NMR study of the interaction of water with $\text{AlPO}_4\text{-11}$. *Journal of the Chemical Society, Chemical Communications*, (21), 1560-1562. <https://doi.org/10.1039/c39920001560>

DOI:

[10.1039/c39920001560](https://doi.org/10.1039/c39920001560)

Document status and date:

Published: 01/01/1992

Document Version:

Publisher's PDF, also known as Version of Record (includes final page, issue and volume numbers)

Please check the document version of this publication:

- A submitted manuscript is the version of the article upon submission and before peer-review. There can be important differences between the submitted version and the official published version of record. People interested in the research are advised to contact the author for the final version of the publication, or visit the DOI to the publisher's website.
- The final author version and the galley proof are versions of the publication after peer review.
- The final published version features the final layout of the paper including the volume, issue and page numbers.

[Link to publication](#)

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal.

If the publication is distributed under the terms of Article 25fa of the Dutch Copyright Act, indicated by the "Taverne" license above, please follow below link for the End User Agreement:

www.tue.nl/taverne

Take down policy

If you believe that this document breaches copyright please contact us at:

openaccess@tue.nl

providing details and we will investigate your claim.

A ^{27}Al NMR Study of the Interaction of Water with $\text{AlPO}_4\text{-11}$

Mart P. J. Peeters, Jan W. de Haan, Leo J. M. van de Ven and Jan H. C. van Hooff

Schuit Institute of Catalysis, Eindhoven University of Technology, PO Box 513, 5600 MB Eindhoven, The Netherlands

Spectral simulations of ^{27}Al MAS and double rotation (DOR) NMR spectra measured at 7.0 T prove the preferential hydration of one tetrahedral Al site in $\text{AlPO}_4\text{-11}$, transforming this site reversibly into octahedral aluminium.

$\text{AlPO}_4\text{-11}$ is built of alternating AlO_4^- and PO_4^+ tetrahedra linked together *via* joined oxygen atoms to form a microporous three-dimensional network with a uni-dimensional pore system of $4.4 \times 6.7 \text{ \AA}$. In recent literature, some discrepancies arose concerning the nature of water adsorption by this important molecular sieve. Meinhold and Tapp¹ observed that $\text{AlPO}_4\text{-11}$ reversibly adsorbs water. X-Ray diffraction measurements indicated that upon hydration the crystal symmetry changes from body-centred orthorhombic

($a = 13.54$, $b = 18.51$, $c = 8.37 \text{ \AA}$) to primitive orthorhombic ($a = 13.54$, $b = 18.02$, $c = 8.12 \text{ \AA}$) within two hours. With ^{27}Al MAS NMR significant differences were noticed between the dry and the wet samples, however, no octahedral aluminium was reported. IR measurements indicated the presence of physisorbed water only.

Barrie *et al.*² studied hydrated $\text{AlPO}_4\text{-11}$ using ^{27}Al MAS and DOR NMR at 9.4 and 11.7 T. The MAS spectrum at 9.4 T of the hydrated sample (five crystallographically different

Fig. 1 ^{27}Al DOR NMR spectra at different magnetic fields

T-sites) showed three peaks in the tetrahedral region with intensity ratios of 21.3 : 60.2 : 18.5, together with an octahedral signal (approximately 20% of the total area). To simulate the tetrahedral region of the MAS spectra at 9.4 T, five signals were needed. DOR NMR resulted in a significant decrease of the linewidths of two resolved peaks in the tetrahedral region while the linewidth of the octahedral signal did not decrease. This led to the conclusion that all five aluminium sites are hydrated to about the same extent.

Recently Prasad *et al.*³ reported the preferential adsorption of water on the T_3 site (located at the junction of 6-, 6-, 10-membered rings) according to MNDO calculations. On the basis of these calculations both the ^{27}Al and ^{31}P MAS NMR spectra were interpreted.

Here we report ^{27}Al DOR NMR experiments of wet $\text{AlPO}_4\cdot 11\text{H}_2\text{O}$ at 4.7, 7.0, 9.4 and 11.7 T as well as ^{27}Al MAS NMR

Fig. 2 ^{27}Al NMR peak positions as a function of $1/(B_0)^2$. No octahedral signal could be observed at 4.7 T.

Fig. 3 ^{27}Al NMR spectra of wet $\text{AlPO}_4\cdot 11\text{H}_2\text{O}$ at 7.0 T: DOR simulation (a), DOR spectrum (b), MAS spectrum (c) and MAS simulation (d)

at 7.0 T. We reinterpret the ^{27}Al NMR spectra based on spectral simulations of both ^{27}Al MAS and DOR NMR spectra. The results can be reconciled with the calculations of Prasad *et al.*³

The ^{27}Al DOR NMR spectra of fully hydrated $\text{AlPO}_4\cdot 11\text{H}_2\text{O}$ at various magnetic fields are given in Fig. 1. The peak positions shift with changes in the external magnetic field. The DOR spectrum measured at 7.0 T yields the best line separation. Here, four distinct peaks in the tetrahedral region are observed together with an octahedral signal. The observed shifts of the ^{27}Al DOR NMR lines are inversely proportional

Table 1 Quadrupolar parameters used for the simulation

Isotropic chemical shift, δ (± 0.15)	Relative area (%) (± 1.5)	e^2qQ/h (MHz) (± 0.02)	η (± 0.05)
46.1	25	2.23	0
42.1	25	2.69	0.5
40.8	25	1.63	0.5
32.6	25	2.63	0.95

to $(B_0)^2$,⁴ see Fig. 2. Extrapolation of the chemical shifts to infinite magnetic field yields the isotropic chemical shifts at δ 32.6, 40.8, 42.1 and 46.1.

The DOR and MAS NMR spectra at 7.0 T were simulated with the program QNMR.⁵ Centres of gravity were taken from the DOR spectrum at 7.0 T. Combination of the centres of gravity and the isotropic shifts yield information regarding the quadrupolar interaction parameters e^2qQ/h and η . Simulation of the MAS spectra allows the determination of the two parameters separately. MAS and DOR spectral simulations were performed using four peaks with equal areas in the tetrahedral region. The results of the DOR and MAS NMR simulations are shown in Fig. 3. The octahedral aluminium site caused a signal with an equal area. The parameters used for the simulations are listed in Table 1.

On the basis of these experiments we feel that we have presented unambiguous proof of the preferential hydration of one of the aluminium sites, transforming this site into octahedrally coordinated aluminium. More details will follow after the assignments of the isotropic ^{27}Al NMR shifts and/or quadrupolar parameters to the five specific lattice positions in hydrated AlPO-11.

The authors are indebted to Dr A. Samoson for many stimulating discussions and for providing the spectra measured at 4.7, 7.0 and 11.7 T.

Received, 6th July 1992; Com. 2/03551K

References

- 1 R. H. Meinhold and N. J. Tapp, *J. Chem. Soc., Chem. Commun.*, 1990, 219.
- 2 P. J. Barrie, M. E. Smith and J. Klinowski, *Chem. Phys. Lett.*, 1991, **180**, 6.
- 3 S. Prasad, I. Balakrishnan and R. Vetrivel, *J. Phys. Chem.*, 1992, **96**, 3096.
- 4 G. Engelhardt and D. Michel, in *High-resolution Solid State NMR of Silicates and Zeolites*, Wiley, Chichester, 1987, p. 61.
- 5 Program for simulation of solid state NMR lineshapes QNMR, developed and supplied by the Institute of Chemical Physics and Biophysics, Tallinn, Estonia.