Gelation/crystallization of poly(vinyl chloride)

Citation for published version (APA):

Dorrestijn, A., Lemstra, P. J., & Berghmans, H. (1983). Gelation/crystallization of poly(vinyl chloride). *Polymer Communications*, 24(8), 226-230.

Document status and date:

Published: 01/01/1983

Document Version:

Publisher's PDF, also known as Version of Record (includes final page, issue and volume numbers)

Please check the document version of this publication:

- A submitted manuscript is the version of the article upon submission and before peer-review. There can be important differences between the submitted version and the official published version of record. People interested in the research are advised to contact the author for the final version of the publication, or visit the DOI to the publisher's website.
- The final author version and the galley proof are versions of the publication after peer review.
- The final published version features the final layout of the paper including the volume, issue and page numbers.

[Link to publication](#)

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal.

If the publication is distributed under the terms of Article 25fa of the Dutch Copyright Act, indicated by the "Taverne" license above, please follow below link for the End User Agreement:

www.tue.nl/taverne

Take down policy

If you believe that this document breaches copyright please contact us at:

openaccess@tue.nl

providing details and we will investigate your claim.

polymer communications

Gelation/crystallization of poly(vinyl chloride)

Antoon Dorrestijn and Piet J. Lemstra
DSM, Central Laboratory, Geleen, The Netherlands

and Hugo Berghmans
K. U. Leuven, Laboratory of Macromolecular and Organic Chemistry, Leuven, Belgium
(Received 28 December 1982)

The gel formation of PVC and post-chlorinated PVC samples (CPVC) in DOP (di-(2-ethylhexyl)phthalate) was studied by measuring the storage modulus as a function of time/frequency. Random chlorination of PVC in solution completely suppresses gelation when more than 13 mole % additional chlorine is introduced, which is in contrast with bulk chlorinated samples. These differences are ascribed to the influence of intramolecular chlorine distribution on crystallizability.

Keywords Gelation; crystallization, poly(vinyl chloride), chlorination

Introduction

The existence and origin of crystallinity in PVC is still a matter of debate, despite the fact that this particular polymer has a long manufacturing history, being one of the major bulk polymers produced today. Certainly, the presence of crystallinity cannot be denied for those PVC samples which have been prepared by special techniques, like polymerization in the presence of aldehydes^{1,2} or urea^{3,4} and low temperature polymerization⁵, where crystallinity is related to the presence of relatively long syndiotactic sequences in the polymer chains.

The question remains however, whether these observations can be extrapolated to PVC types produced on a commercial scale by for instance, an emulsion or suspension polymerization process. From ¹³C n.m.r. results, it was concluded that these commercially produced PVC's are mainly atactic. The isotactic (mm), heterotactic (mr) and syndiotactic (rr) triads are found to be of the order of 0.2, 0.5 and 0.3 respectively^{6,8}. Taking these data into account one would not expect a measurable amount of crystallinity to be present in bulk PVC. However, the values for crystallinity of standard PVC types which are reported in the literature vary between 0 and 20%, based on various experimental data and interpretations⁷.

The large spread in values for the degree of crystallinity is related to the difficulties encountered in quantitative interpretation of the X-ray, i.r. and d.s.c. data obtained from solid PVC samples.

Crystallization from solution usually enhances crystallinity, and it has been reported in the literature that upon cooling of moderately concentrated PVC solutions, thermoreversible gelation occurs. This gelation phenomenon was interpreted in terms of a crystallization process, probably of the fringed micellar mode^{8,9}. Upon stretching these PVC gels, rather well-pronounced X-ray diffraction patterns were obtained⁸.

This finding demonstrates that PVC, despite its nearly atactic character, is capable of forming a certain amount of crystallinity, but this does not imply that the initial step of the gelation process is a crystallization phenomenon. To investigate the role of crystallization in this gelation

process we chemically modified PVC by post-chlorination. The kinetics of gel formation was studied as a function of chlorine content by measuring the increase of the storage modulus as a function of time in a similar way as described in ref. 9

Experimental

Materials. Varlan S7120, a suspension-polymerized PVC from DSM, having a M_w of 105 000 g/mole and a M_n of 55 000 g/mole, was used as the reference material. This particular PVC sample was chlorinated, in solution and directly as a powder.

Solution-chlorination: The polymer powder was dispersed in tetrachloroethane (TCE) at room temperature, concentration 5 g/100 ml. The suspension was flushed with N₂ and heated in an oil bath, with stirring. After complete dissolution of the PVC polymer, chlorine gas was passed through the solution at 125°C.

No initiator nor u.v. radiation was used to initiate the chlorination reaction.

At regular intervals, aliquots of the (C)PVC/TCE solutions were transferred to a separate vessel. After chlorine gas removal by N₂ flushing, the different solutions were precipitated in methanol.

The (C)PVC samples precipitated quantitatively as a gelly mass. After filtering and preliminary drying, the precipitated mass was redissolved in tetrahydrofuran (THF), after which diethyl ether was added to the (C)PVC/THF solution until the mixture became hazy. These mixtures were added dropwise to vigorously stirred cold (about 0°C) methanol.

Using these procedures, a finely divided powder was obtained.

After filtering and vacuum drying, the chlorine content was measured, using the standard Schöniger method.

Powder-chlorination: In a rotating glass cylinder equipped with a thermostated i.r. heating system, PVC powder was tumbled for at least half an hour at room temperature. After that period the system was heated to about 125°C and chlorine gas was passed through the system at a constant flow rate.

At time intervals ranging from 10 to 60 min, the chlorine was removed by flushing the system with N_2 and samples were isolated. Their chlorine content was determined from the weight increase and by the Schöniger method.

Table 1 summarizes the samples obtained by the solution and powder chlorination procedures, respectively.

Techniques. Gelation kinetics: The PVC and CPVC samples were dissolved in di-(2-ethylhexyl)phthalate (DOP) at 160°C. Stabilizers were added and N_2 flushing was used during the dissolution procedure. The solutions

were poured directly into the measuring cell of a viscometer (Rheometrics RMS-7200).

The storage modulus G' and the loss angle δ were measured as a function of the oscillation frequency and time at 23°C. The molar concentration of the CPVC and PVC/DOP solution was kept constant at 1.6 mol l^{-1} .

^{13}C n.m.r.: The ^{13}C n.m.r. spectra of the CPVC and PVC samples were obtained at 25.2 MHz using a Varian XL-100/15 spectrometer.

The sample concentration was about 10% w/v in a solvent mixture of 1,2,4-trichlorobenzene and per-deuterated benzene (internal lock). Using 12 mm tubes the spectra were recorded in the mixed solvents at 85°C using pulse widths of 35 s (pulse angle 77°) and pulse delays of 2 s. Spectra were generally obtained after the accumulation of 25 000 scans (corresponding to a spectral width of 3000 Hz/digital resolution 0.667 Hz/pt). Peak areas were determined using a planimeter and assuming no differential NOE's and T_1 's to occur; see also refs. 10 and 11.

Results and Discussion

Figures 1, 2 and 3 show the frequency dependence of the storage modulus G' and the loss angle (δ) as a function

Figure 1 Storage modulus G' and loss angle δ vs. frequency for sample A as a function of time, a=3; b=6; c=10; d=21; e=42 min and f=16 h

Figure 2 Storage modulus G' and loss angle δ vs. frequency for sample B as a function of time, a=3; b=5; c=10; d=21 and e=42 min

Figure 3 Storage modulus G' and loss angle δ vs. frequency for sample G as a function of time, a=3; b=5; c=8; d=21 and e=53 min

of time for three selected samples A, B and G. It can be concluded from Figures 1 and 2 that the PVC reference sample A and sample B build up an elastic network in DOP as shown by the appearance of a plateau region in the G' vs. frequency plots and the values for the loss angle delta extrapolated to low frequencies.

In contrast, the solution-chlorinated sample G in DOP remains a fluid and no sign of any network formation is present.

Some semi-quantitative information regarding the kinetics of gel formation can be obtained by plotting the value for G' , at $\log \omega = 0$, vs. $\log$ time (Figure 4). Once more a striking difference is seen between the solution-chlorinated vs. the powder chlorinated PVC samples. This difference is well illustrated by plotting the value for the pseudo-equilibrium modulus G_e at $t=60$ min as a function of the chlorine content. In Figure 5 a gradual decrease in the value for G_e is observed for the powder-chlorinated samples in contrast to a rapid fall in the G_e -moduli for the solution-chlorinated samples. At about 60% w/w chlorine, the solution-chlorinated samples completely lose their gel formation ability. This chlorine content corresponds to a conversion of about 13 mole % monomer units containing one additional chlorine atom each (see Appendix).

It is well known that chlorination of PVC and PE in solution results, at least in the early stages of the process, in an approximately random introduction of chlorine in the polymer chain and no significant amount of $-CCl_2-$ formation¹². On the contrary, chlorination of PVC powder is a non-random process. It was reported recently¹⁰ on the basis of ^{13}C measurements, that during chlorination of PVC powder the amount of syndiotactic sequences remains practically unchanged. If it is assumed that the crystallization of PVC results from the presence of a small amount of syndiotactic sequences of sufficient

Figure 4 Storage modulus G' at 1 Hz vs. gelation time at 23°C for various samples, for explanation see Table 1

length to form microcrystallites, then the differences in gelability of the solution and gas phase chlorinated samples respectively, could be easily explained as follows.

During the chlorination of PVC powder the chlorine molecules are excluded from the microcrystalline domains already formed during the polymerization process, which, as stated above, are supposed to consist mainly of syndiotactic sequences. On the contrary, solution-chlorination randomly attacks the whole polymer chain

Figure 5 Dependence of storage modulus G_e (at $t=60$ min) on chlorine content for various samples

and a minor amount of additional chlorine in the macromolecule is sufficient to decrease the average syndiotactic sequence length below a minimum value necessary for crystallization.

This explanation, although being very attractive, lacks firm experimental evidence. The existence of relatively long syndiotactic sequences in commercially produced PVC/s is rather unlikely. Secondly, the interpretation of the ^{13}C n.m.r. spectra of chlorinated samples cannot be performed in a quantitative way. Figure 6 shows spectra of powder-chlorinated PVC's as a function of % w/w chlorine. At first glance the rr triad resonance peak increases relatively at the expense of the isotactic (mm) and heterotactic absorptions (mr). However, recently Komorowski *et al.*¹¹ showed the presence of severe overlap between the various peaks in the ^{13}C n.m.r. spectra of CPVC samples as shown clearly for instance in Figure 6C.

Consequently it is impossible to deduce quantitative information from the spectra with respect to the preservation of certain tactic sequences. The results of tests on the samples obtained by chlorinating PVC powder with respect to the gel formation kinetics and the gradual decrease in the value for G_e with increasing chlorine content could equally well be explained in terms of a heterogeneous chlorination process with excess surface chlorination of primary PVC particles at the expense of relatively unaltered inner parts of PVC.

Summarizing, the concept of chlorination of PVC aids in understanding the mechanism of gel formation and reaffirms the relation between gel formation and crystallizability, but no firm conclusion can be drawn with respect to the origin of crystallinity in commercial PVC samples. Further investigations, including fractionation experiments, are needed to answer the question whether crystallization is mainly due to specific tactic sequences or a co-crystallization process, an issue raised some time ago¹³ and reconsidered recently by Guerrero and Keller¹⁴.

Figure 6 ^{13}C n.m.r. spectra of PVC (sample A) and chlorinated PVC powder (B and C corresponding to Table 1)

Appendix

Assuming no $-\text{CCl}_2-$ formation the relation between the fractional conversion x vs. the % Cl (w/w) X is given by:

$$x = \frac{(62.5X - 3350)}{(35.5 - 0.345X)} \quad (1)$$

In equation (1) x is the percentage of (base) molar units containing one additional chlorine atom.

Acknowledgement

The authors wish to express their gratitude to Dr G. van der Velden for interpreting the n.m.r. spectra and Messrs. J. Palmen and J. W. A. Sleijpen for performing the rheological measurements.

We are indebted to Professor A. Keller (Bristol University) for stimulating discussions.

References

- 1 Wilkes, C. E., Folt, V. L. and Krimm, S. *Macromolecules* 1973, **6**, 235
- 2 Gouinlock, E. V. J. *Polym. Sci. Polym. Phys. Edn.* 1975, **13**, 961
- 3 White, D. M. J. *Am. Chem. Soc.* 1960, **82**, 5678
- 4 Baker, C., Maddams, W. Q. F. and Preedy, J. E. J. *Polym. Sci. Polym. Phys. Edn.* 1977, **15**, 1041
- 5 Fordham, J. W. L., Burleigh, P. H. and Sturm, C. L. J. *Polym. Sci.* 1959, **39**, 321

- 6 Bovey, F. A. 'High Resolution NMR of Macromolecules', Academic Press, London, (1972), Ch. 5
- 7 *Faraday Discussions* 1979, **68**, 127-138
- 8 Lemstra, P. J., Cudby, M. and Keller, A. *J. Polym. Sci. Polym. Phys. Edn.* 1978, **16**, 1507
- 9 Dorrestijn, A., Keijzers, A. E. M. and te Nijenhuis, K. *Polymer* 1981, **22**, 305
- 10 Keller, F., Opitz, H., Hösselbarth, B., Beckert, D. and Reichert, W. *Faserforsch. Textiltechnik* 1975, **26**, 329
- 11 Komoroski, R., Parker, R. G. and Lehr, M. H. *Macromolecules* 1982, **15**, 844
- 12 Trautvetter, W. *Kunststoffe Plast.* 1966, **2**, 54; Saito, T. and Matsumera, Y. *Polym. J.* 1973, **4**, 124
- 13 Juin, J. A., Gisolf, J. H. and de Jong, W. A. *Kolloid Z.Z. Polym.* 1969, **235**, 1157
- 14 Guerrero, S. J. and Keller, A. *J. Macromol. Sci.-Phys.* 1981, **B20/2**, 167

A new look at the enhanced low-angle scattering in moderately concentrated polymer solutions

Jean-Michel Guenet*, Nigel F. F. Willmott and Paul A. Ellsmore

H. H. Wills Physics Laboratory, Bristol University, Bristol BS8 1TL, UK

(Received 8 March 1983)

In the light of the recent discovery by Tan *et al.* of the gelation ability of some atactic polystyrene solutions at low temperature above the *UCST*, we reexamine the enhanced scattering observed at small angles in moderately concentrated solutions. In this communication we present some results gained from light scattering experiments showing that there seems to be a correlation between these two phenomena: i.e. no abnormal scattering effect when dealing with a solvent preventing gelation whereas abnormal scattering when using a solvent promoting the gelation. The results are discussed and a tentative explanation is given.

Keywords Light scattering; physical gelation; atactic polystyrene; concentrated solutions; decalin; toluene; chloroform; methyl-ethyl ketone; 1,2-dichloroethane

Introduction

Some years ago, the scattering of light by moderately concentrated solutions of polymers was intensively investigated mainly in order to evaluate the concentration effect on the chain dimension¹. Unexpectedly, instead of obtaining a linear variation from a Zimm representation as in dilute solutions, two types of behaviour were observed. While at larger angles the slope of the straight curve remains constant, at smaller angles a downturn appears, the average slope of which becomes steeper and steeper with increasing concentration. This abnormal and unpredicted effect was first imputed to either ill-removed dust or insoluble material. However, it was demonstrated¹ that this phenomenon is genuine and characteristic of particular mixtures of polymer-solvent. Paradoxically, the phenomenon arises for good solvents and tends to vanish for θ -solvents at the θ temperature¹.

Recently, Tan *et al.*² have succeeded in preparing true thermoreversible gels from atactic polystyrene (APS) solutions without quenching under the spinodal curve. Basically, the gels are obtained from moderately concentrated solutions cooled down to low temperature (typically 0°C to $\approx -100^\circ\text{C}$). From d.s.c. experiments, they point out the existence of a melting zone as in more classical physical gels prepared with semi-crystalline polymers³. However, they show that the gelation does not necessarily occur whatever the solvent. Some solvents, in spite of their ability to remain liquids down to very low temperatures, do not allow the polymer solution to gel.

In the light of the Tan *et al.*'s findings, we shall try to discover whether there is a correlation between the abnormal scattering effect and the gelation ability of uncrystallizable polymers. As a matter of fact, some solvents producing the gelation¹ are known to give rise to

abnormal scattering at small angles. This communication is intended to report preliminary investigations performed through the use of a light scattering technique on moderately concentrated polymer solutions using some of the solvents featuring in the study of Tan *et al.*². We have especially aimed at discovering whether the solvents, wherein any physical gelation is absent, exhibit the scattering effect at small angles.

Experimental

Solvents. For this study, five different solvents have been employed. Concerning those wherein gelation can occur, we chose methyl-ethyl ketone (MEK) and toluene. Both these solvents are known to give rise to the scattering effect¹. Thus, they have provided a way of comparing experimental data obtained from them with those obtained from the solvents in which gelation of APS is not observed. In this latter case, three solvents have been used, characterized by a very low freezing point (see Table 1) namely; decalin, 1,2-dichloroethane and chloroform. As no hint is available in Tan's paper² as to the composition of *trans* and *cis* isomers of the decalin, we took a mixture 55% *cis* and 45% *trans*.

The low freezing point is an important parameter, as the gel may form at very low temperature. As an example, benzene which gives rise to the scattering effect¹ is said to be a non-gelation solvent². This does not seem surprising since the freezing point of this solvent is near 5°C. Had it had a lower freezing temperature, then gelation might have been possible.

All the solvents are characterized by a high purity grade. Special care was taken with chloroform which was of i.r.-spectroscopy grade. It contained 2% alcohol as stabilizer that had been washed with distilled water, which was then removed by decantation and finally distilled so as to give chloroform that was free of impurities.

It is worth mentioning that in all these solvents the atactic polystyrene exhibits a high contrast factor (dn/dc)

* Permanent address and where correspondence should be addressed to: C.R.M. (C.N.R.S.) 6, rue Boussingault, 67083 Strasbourg Cédex (France). Visiting Scientist on a joint exchange program Royal Society-CNRS.