Mg-Ti-H thin films for smart solar collectors

Citation for published version (APA):

Borsa, D. M., Baldi, A., Pasturel, M., Schreuders, H., Dam, B., Griessen, R., Vermeulen, P., & Notten, P. H. L. (2006). Mg-Ti-H thin films for smart solar collectors. *Applied Physics Letters*, 88(24), 241910-1/3. [241910]. <https://doi.org/10.1063/1.2212287>

DOI:

[10.1063/1.2212287](https://doi.org/10.1063/1.2212287)

Document status and date:

Published: 01/01/2006

Document Version:

Publisher's PDF, also known as Version of Record (includes final page, issue and volume numbers)

Please check the document version of this publication:

- A submitted manuscript is the version of the article upon submission and before peer-review. There can be important differences between the submitted version and the official published version of record. People interested in the research are advised to contact the author for the final version of the publication, or visit the DOI to the publisher's website.
- The final author version and the galley proof are versions of the publication after peer review.
- The final published version features the final layout of the paper including the volume, issue and page numbers.

[Link to publication](#)

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal.

If the publication is distributed under the terms of Article 25fa of the Dutch Copyright Act, indicated by the "Taverne" license above, please follow below link for the End User Agreement:

www.tue.nl/taverne

Take down policy

If you believe that this document breaches copyright please contact us at:

openaccess@tue.nl

providing details and we will investigate your claim.

Mg-Ti-H thin films for smart solar collectors

D. M. Borsa,^{a)} A. Baldi, M. Pasturel, H. Schreuders, B. Dam, and R. Griessen
*Faculty of Sciences, Department of Physics and Astronomy, Vrije Universiteit, De Boelelaan 1081,
 1081 HV Amsterdam, The Netherlands*

P. Vermeulen
Eindhoven University of Technology, 5600 MB Eindhoven, The Netherlands

P. H. L. Notten
*Eindhoven University of Technology, 5600 MB Eindhoven, The Netherlands
 and Philips Research Laboratories, 5656 AE Eindhoven, The Netherlands*

(Received 24 February 2006; accepted 28 April 2006; published online 14 June 2006)

Mg-Ti-H thin films are found to have very attractive optical properties: they absorb 87% of the solar radiation in the hydrogenated state and only 32% in the metallic state. Furthermore, in the absorbing state Mg-Ti-H has a low emissivity; at 400 K only 10% of blackbody radiation is emitted. The transition between both optical states is fast, robust, and reversible. The sum of these properties highlights the applicability of such materials as switchable smart coatings in solar collectors. © 2006 American Institute of Physics. [DOI: 10.1063/1.2212287]

Many metal hydrides behave as switchable mirrors (i.e., their optical properties switch from reflective in the metallic state to transparent in the hydrogenated state).^{1–4} In addition, magnesium-rare-earth (Mg-RE) and magnesium-transition-metal (Mg-TM) switchable mirrors also exhibit an intermediate highly absorbing optical state on hydrogenation. The possibility to switch a film from a reflective state to an absorbing state suggests that such materials might be interesting for smart solar collectors, which absorb light in normal operation condition and switch to a reflective state to avoid overheating. Limiting the stagnation temperature of the solar collector makes it possible to use cheap materials such as plastics (generally not designed for high temperatures).

In this letter we show that $\text{Mg}_y\text{Ti}_{1-y}$ thin films prepared by dc magnetron co-sputtering of Mg and Ti at room temperature (on quartz and CaF_2) satisfy the following requirements for a smart solar coating: (i) high absorption in the solar regime ($0.5 < \hbar\omega < 4$ eV), (ii) low emissivity in the thermal regime ($\hbar\omega < 0.5$ eV), and (iii) reversibility. Three compositions are studied in detail: $y=0.70$, $y=0.80$, and $y=0.90$. Typical deposition rates are 2 Å/s for Mg (150 W rf power), 0.1–1 Å/s for Ti (25–160 W dc power), and 1.3 Å/s for Pd (50 W dc power). All the films are covered with a Pd layer (10–50 nm) to promote dissociation of H_2 and to prevent oxidation of the underlying film.

Reflection (R) and transmission (T) spectra are measured simultaneously during hydrogenation (pressures up to 1 bar H_2) in a Perkin Elmer Lambda 900 diffraction grating spectrometer ($0.495 < \hbar\omega < 6.51$ eV) and a Bruker IFS 66 Fourier transform infrared spectrometer ($0.2 < \hbar\omega < 1.1$ eV). The R - T spectra are measured through the transparent substrate at near normal incidence of the incoming beam. Figures 1(a) and 1(b) show the reflection and transmission spectra measured for 200 nm $\text{Mg}_y\text{Ti}_{1-y}/10$ nm Pd films ($y=0.90$, 0.80, and 0.70) in the as-prepared and hydrogenated states (in 1 bar H_2 at room temperature). In the metallic state [Fig. 1(a)] all the films have a relatively high and featureless reflection that decreases with increasing Ti content.

After hydrogen absorption, the reflection is low for all compositions, whereas significant transmission is observed only for the $y=0.90$ sample. The combination of low reflection and low transmission in the hydrogenated state ($y=0.80$ and 0.70 samples) gives rise to a highly absorbing state that extends over the entire visible range. For example, $\text{Mg}_{0.80}\text{Ti}_{0.20}\text{H}_x$ absorbs $\sim 87\%$ of the solar radiation in the hydrogenated state and only $\sim 32\%$ in the reflective state.

FIG. 1. (Color online) (a) Reflection spectra measured on 200 nm $\text{Mg}_y\text{Ti}_{1-y}/10$ nm Pd films with $y=0.90$, 0.80, and 0.70 in the as-prepared (metallic) and hydrogenated states (1 bar H_2 at room temperature). (b) Transmission spectra measured on the same films in the hydrogenated state. In the metallic state the transmission is below the detection limit of the spectrometer.

^{a)}Electronic mail: dborsa@nat.vu.nl

The highly absorbing state described here is a final state and not an intermediate optical state as in Mg–Ni–H (Ref. 5) and is thus robust and easily tunable. The same behavior is observed when using electrochemical loading. Again the reflection and transmission vary continuously (R decreasing, T increasing) until the maximum concentration of hydrogen is reached. Thus, this material can be applied both in electrochromic and gasochromic applications.

Despite the limited solubility reported for Ti in bulk Mg, alloying of Mg and Ti is obtained by using physical vapor deposition,⁶ mechanical alloying,⁷ or e -beam deposition.^{8,9} We observe a similar crystalline Mg–Ti alloy phase (hexagonal structure) when co-sputtering Mg and Ti. In hydrogenated films the formation of a MgH_2 -like rutile phase is observed for low Ti contents ($y=0.90$), whereas in $\text{Mg}_y\text{Ti}_{1-y}$ with $y=0.80$ and $y=0.70$, a fluorite-like Mg–Ti–H phase is formed, similar to that identified by Kyojima *et al.*¹⁰ in bulk samples. There are no indications that phase segregation takes place as is the case for Mg–rare-earth systems such as Mg–Gd, Mg–La, and Mg–Y.^{2,11} The influence of phase composition and structure on the optical properties will be published elsewhere.

The optical properties of $\text{Mg}_y\text{Ti}_{1-y}$ ($y=0.85$, $y=0.73$) thin films capped with 10 nm Pd were also studied recently by Farangis *et al.*¹² and Richardson *et al.*¹³ Upon hydrogenation, the x-ray amorphous films prepared by dc magnetron co-sputtering were reported to switch from reflective to transparent similarly to other Mg–TM (TM=Co, Ni, Fe, Mn), with Ti acting primarily as a catalyst for MgH_2 formation.¹³ In comparison with the films studied here, their hydrogenated films do have similar low and featureless reflection, but also rather high transmission. Probably, due to the small thickness of their films (40–50 nm), the difference in the optical properties of the various hydrides does not show up.

For solar collector applications, it is desirable to have coatings that absorb as much solar radiation as possible, while emitting as little as possible in the thermal range. A linear extrapolation to lower energies of the R - T spectra shown in Fig. 1 does not yield the desired low absorption. This is, however, a problem that is easily solved by choosing an appropriate thickness of the $\text{Mg}_y\text{Ti}_{1-y}$ and Pd layers. The thickness dependence of the absorption ($A=1-R-T$) calculated for a $\text{Mg}_y\text{Ti}_{1-y}\text{H}_x/\text{Pd}$ ($y=0.80$) film is shown in Fig. 2(a). For these calculations we use the dielectric function of $\text{Mg}_y\text{Ti}_{1-y}\text{H}_x$ derived from measurements on thick films in the 0.5–6 eV energy range. The overall reflection (from the substrate side) and transmission are then calculated by means of a transfer matrix method.¹⁴ The quartz substrate and the Pd cap layer¹⁵ are also taken into account. The thickness of the Pd layer is fixed to 40 nm. Such a thick layer suppresses any optical transmission and also contributes to the total reflection (measured from the substrate side). The thickness of the Mg–Ti–H layer is varied between 30 and 250 nm. As shown in Fig. 2(a), with increasing layer thickness, the absorption edge shifts to lower energies, while the overall absorption stays very high in the solar range. Therefore, to prevent a high emissivity and still obtain a high solar absorption, we have to choose an intermediate layer thickness. The absorption spectra measured on a 65 nm $\text{Mg}_y\text{Ti}_{1-y}/40$ nm Pd ($y=0.80$) film in the as-prepared and hydrogenated states (1 bar H_2 at room temperature) are shown in Fig. 2(b) and compare quite well with the predicted one. In the hydrogenated state, the total solar absorption is high (87%), but low in

FIG. 2. (Color online) (a) Absorption spectra calculated for a (d nm) $\text{Mg}_y\text{Ti}_{1-y}\text{H}_x/40$ nm Pd ($y=0.80$) film; the thickness of the Mg–Ti–H layer (d) is varied between 30 and 250 nm. (b) Absorption spectra measured for a 65 nm $\text{Mg}_y\text{Ti}_{1-y}/40$ nm Pd ($y=0.80$) film in the as-prepared and hydrogenated states (1 bar H_2 at room temperature). (c) Spectrum of the solar radiation at atmospheric mass (AM) of 1.5 shown together with the blackbody radiation at 400 K. Both are in arbitrary units.

the thermal range. The thermal emissivity of the system is calculated by extrapolating the absorption to zero energies and convoluting the data with the blackbody radiation at 400 K [spectrum shown in Fig. 2(c) together with the spectrum of the solar radiation at atmospheric mass (AM) of 1.5]. The result, a thermal emissivity of 0.10, is quite promising and, indeed, much lower than that of a thick film (~ 0.50).

A key issue for switchable coatings is the reversibility. This is tested by measuring reflection (through the transparent substrate) during gas cycling: hydrogenation with 5% H_2 in Ar (250 ml/m flow) and dehydrogenation with 20% O_2 in Ar (250 ml/m flow). Here we focus on the highly absorbing compositions ($y=0.80$ and $y=0.70$) that also show better switching properties as compared to the $y=0.90$ sample. In Fig. 3(a) we compare the reflection ($\hbar\omega=1.95$ eV) for the first two cycles measured on 65 nm $\text{Mg}_y\text{Ti}_{1-y}/40$ nm Pd films ($y=0.70$ and $y=0.80$). The reflective-to-absorbing transition is very fast and rather independent of composition. An increase in Ti content has a beneficial effect on the absorbing-to-reflective speed, though it decreases slightly the optical contrast. A set of 15 cycles measured for the

FIG. 3. (Color online) (a) Reflection at $\hbar\omega=1.95$ eV measured on 65 nm $\text{Mg}_y\text{Ti}_{1-y}/40$ nm Pd films with $y=0.70$ and $y=0.80$; the first two cycles are shown. Hydrogen is introduced in the system at $t=0$, 730, and 1470 s; the start of the dehydrogenation period is indicated by the two arrows; loading is done with 5% H_2 in Ar flow and unloading with 20% O_2 in Ar flow. (b) Same measurements as in (a) but for more cycles.

$y=0.70$ sample is shown in Fig. 3(b). This result illustrates both the stability and reversibility of the system: the switching time from the reflective to the absorbing state is only a few seconds and stays rather constant similar to the optical contrast. Switching back to the reflective state is, however, slower and increases slightly with cycling. This effect could be related to poisoning of the Pd cap layer and/or intermixing at the interface. Appropriate coatings and/or buffer layers can improve these performances.

Summarizing, we have shown that $\text{Mg}_y\text{Ti}_{1-y}$ thin films have very attractive switchable optical properties that can be tuned by varying the composition and film thickness. In the optimal configuration, the films absorb 87% of the solar radiation in the hydrogenated state and only 32% in the metallic state, improving thus the solar absorption efficiency and reducing the stagnation temperature. Furthermore, in the absorbing state Mg-Ti-H has a low emissivity; at 400 K only 10% of blackbody radiation is emitted. These characteristics are comparable to that of advanced solar coatings such as

ceramic-metal composite materials.¹⁶ Mg-Ti-H , however, has the great advantage of being switchable. The combination of these properties highlights the applicability of Mg-Ti-H thin films as switchable smart coatings for solar collector applications. Moreover, the fast switching together with the high optical contrast between the reflective and the absorbing states make Mg-Ti-H films also interesting for hydrogen sensor applications. The solar collector and sensor applications of Mg-Ti-H thin films described in this letter combined with the very large reversible hydrogen storage capacity of Mg-Ti-H thin film battery electrodes reported earlier by Notten and co-workers^{8,9} make this metal-hydride system truly remarkable.

This work is part of the research program of the Stichting voor Fundamenteel Onderzoek der Materie (FOM) and the Technologiestichting STW. Both are financially supported by the Nederlandse Organisatie voor Wetenschappelijk Onderzoek (NWO). Financial support from the EU sixth framework program Novel Efficient Solid Storage for Hydrogen NESSHY is also acknowledged.

- ¹J. N. Huiberts, R. Griessen, J. H. Rector, R. J. Wijngaarden, J. P. Dekker, D. G. de Groot, and N. J. Koeman, *Nature (London)* **380**, 231 (1996).
- ²P. van der Sluis, M. Ouwkerk, and P. A. Duine, *Appl. Phys. Lett.* **70**, 3356 (1997).
- ³T. J. Richardson, J. L. Slack, R. D. Armitage, R. Kostecki, B. Farangis, and M. D. Rubin, *Appl. Phys. Lett.* **78**, 3047 (2001).
- ⁴T. J. Richardson, J. L. Slack, B. Farangis, and M. D. Rubin, *Appl. Phys. Lett.* **80**, 1349 (2002).
- ⁵J. L. M. van Mechelen, B. Noheda, W. Lohstroh, R. J. Westerwaal, J. H. Rector, B. Dam, and R. Griessen, *Appl. Phys. Lett.* **84**, 3651 (2004).
- ⁶T. Mitchell, S. Diplas, P. Tsakirooulos, J. F. Watts, and J. A. D. Matthew, *Philos. Mag. A* **82**, 841 (2002).
- ⁷G. Liang and R. Schulz, *J. Mater. Sci.* **38**, 1179 (2003).
- ⁸R. A. H. Niessen and P. H. L. Notten, *Electrochem. Solid-State Lett.* **8**, A534 (2005).
- ⁹P. Vermeulen, R. A. H. Niessen, and P. H. L. Notten, *Electrochem. Commun.* **8**, 27 (2006).
- ¹⁰D. Kyoi, T. Sato, E. Rönnebro, N. Kitamura, A. Ueda, M. Ito, S. Katsuyama, S. Hara, D. Noréus, and T. Sakai, *J. Alloys Compd.* **372**, 213 (2004).
- ¹¹I. A. M. E. Giebels, J. Issidorson, and R. Griessen, *Phys. Rev. B* **69**, 205111 (2004).
- ¹²B. Farangis, P. Nachimuthu, T. J. Richardson, J. L. Slack, B. K. Meyer, R. C. C. Perera, and M. D. Rubin, *Solid State Ionics* **165**, 309 (2003).
- ¹³T. J. Richardson, B. Farangis, J. L. Slack, P. Nachimuthu, R. Pereira, N. Tamura, and M. Rubin, *J. Alloys Compd.* **356**, 204 (2003).
- ¹⁴M. Born and E. Wolf, *Principles of Optics* (University Press, Cambridge, 1980).
- ¹⁵*Handbook of Optical Constants of Solids*, edited by E. D. Palik, (Academic, San Diego, 1998), vols. I–III.
- ¹⁶S. Shuxi and E. Wäckelgård, *Sol. Energy Mater. Sol. Cells* **90**, 243 (2006).