

# Dissipative particle dynamics simulation parameters and interactions of a hydrogel

**Citation for published version (APA):**

Kaçar, G. (2018). Dissipative particle dynamics simulation parameters and interactions of a hydrogel. *Journal of the Turkish Chemical Society, Section A: Chemistry*, 5(1), 19-28. <https://doi.org/10.18596/jotcsa.309646>

**DOI:**

[10.18596/jotcsa.309646](https://doi.org/10.18596/jotcsa.309646)

**Document status and date:**

Published: 01/01/2018

**Document Version:**

Publisher's PDF, also known as Version of Record (includes final page, issue and volume numbers)

**Please check the document version of this publication:**

- A submitted manuscript is the version of the article upon submission and before peer-review. There can be important differences between the submitted version and the official published version of record. People interested in the research are advised to contact the author for the final version of the publication, or visit the DOI to the publisher's website.
- The final author version and the galley proof are versions of the publication after peer review.
- The final published version features the final layout of the paper including the volume, issue and page numbers.

[Link to publication](#)

**General rights**

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal.

If the publication is distributed under the terms of Article 25fa of the Dutch Copyright Act, indicated by the "Taverne" license above, please follow below link for the End User Agreement:

[www.tue.nl/taverne](http://www.tue.nl/taverne)

**Take down policy**

If you believe that this document breaches copyright please contact us at:

[openaccess@tue.nl](mailto:openaccess@tue.nl)

providing details and we will investigate your claim.



## Dissipative Particle Dynamics Simulation Parameters and Interactions of A Hydrogel

Gökhan KAÇAR<sup>1, 2</sup> 

<sup>1</sup> Trakya University, Department of Genetics and Bioengineering, 22030 Edirne/Turkey

<sup>2</sup> Laboratory of Physical Chemistry, Department of Chemical Engineering and Chemistry, Eindhoven University of Technology, Eindhoven, The Netherlands

**Abstract:** In this work, we report a parameterization procedure to compute the parameters of a hydrogel consisting of a hydrophilic polymer and a cross-linker. The system is parameterized so that coarse-grained dissipative particle dynamics (DPD) simulations can be performed. Proper computation of the simulation parameters is crucial in order to represent the inherent chemical nature of the hydrogel and to model the correct structure. The polymer is parameterized by considering different volumes for coarse-grained beads. Moreover, the hydrogen bond interactions should be represented and properly defined in the simulations. To that purpose, we use a recently introduced parameterization procedure that incorporates the attraction as a result of the hydrogen bond interactions between relevant beads. This paper serves as an example of how the realistic simulation parameters of a hydrophilic polymer can be straightforwardly computed by leading to a proper determination of the structure and properties. The computational background, the procedures and the results of the computation are reported and discussed in this paper.

**Keywords:** Dissipative Particle Dynamics method, coarse-grained simulations, polymers.

**Submitted:** April 28, 2017. **Accepted:** October 7, 2017.

**Cite this:** KACAR G. Dissipative Particle Dynamics Simulation Parameters and Interactions of A Hydrogel. Journal of the Turkish Chemical Society, Section A: Chemistry. 2018;5(1):19–28.

**DOI:** <http://doi.org/10.18596/jotcsa.309646>

**\*Corresponding author. E-mail:** gokhankacar@trakya.edu.tr.

## INTRODUCTION

Hydrophilic polymers are widely used in biomedical area as hydrophilicity is desired for various properties, such as lubricity, biocompatibility, wear comfort, and anti-fouling, which would reduce the risk of infection or different clinical problems (1-5). A thorough understanding of the proper structure and dynamics of such materials will pave the way of designing new materials with distinctive features for special purposes. In this work, we study the interactions and structural properties of a hydrogel that is formed by the reaction of a hydrophilic polymer and a cross-linker. Being a hydrogel, the material interacts with water during functioning. The material that we investigate in this work is a cross-linked PEG. PEG was previously studied by performing extensive molecular dynamics simulations for example, to model drug encapsulation (6), to stabilize insulin (7) or to model drug release (8). Moreover, there are also coarse-grained simulation approaches to obtain its structure by Lee and co-workers (9), by Prasitnok and co-workers to study its structure in wet environment (10), and in more complex environments such as attached to lipids (11) or dendrimers (12).

In this work, molecular and mesoscopic scale interactions are studied since intrinsic time and length scales that are valid for the creation of hydrogel structure are at nano- and micro-second levels. The simulation method is referred to as Dissipative Particle Dynamics (DPD). DPD is a coarse-grained simulation method where the different number of atoms, that represent different functional groups, are combined to form the so-called *beads*. By this coarse-graining procedure, the polymer can be equilibrated within a reasonable amount of time. DPD is often applied to study the behavior of complex fluids (13), polymers (14-18), surfactants (19), colloids (20) etc. The original DPD parameterization requires beads having similar volumes. This is a serious limitation of the method upon application to real molecular systems. In experimental systems, polymers can have beads with different molar volumes. In this work, we use an alternative parameterization method where a pure-liquid density-dependent parameterization is used (17). This procedure results in beads having different volumes. Especially for cross-linked systems, correct representation of bead volumes is extremely important since the resulting structure cannot be corrected after cross-linking. Besides variable bead volumes of polymeric systems, a particular attention should be paid to modeling the hydrogen bond interactions which are present in hydrophilic systems. For that purpose, we use a recently developed parameterization where the hydrogen bond attraction is explicitly modeled in DPD simulations (21). The parameterization procedure for parameterizing the DPD potential involves addition of a Morse potential term to the DPD potential. A similar procedure is performed to study the  $\alpha$ -helical and  $\beta$ -sheet structures of proteins (22). In this work, the parameters defining the Morse potential are set arbitrarily in order to create the target protein structure with no scaling by physical units, therefore without taking proper chemistry of beads into consideration. However in our work, we attempted to compute the

hydrogen bonding parameters by considering the exact chemical nature of molecules by combining the results of atomistic simulations with experimental Flory-Huggins parameters. The work in reference (21) demonstrates that the experimental negative volume excess of hydrogen bonding for low molecular weight alcohol and water mixtures can be predicted from coarse-grained simulations.

In this work, we aim to present a parameterization for DPD simulations, where polymeric materials interacting with water can be modeled. The procedure presented herein, extends the applicability of DPD to a wider range of polymers in contact with wet environments. The contents of the paper can be outlined as follows: Initially, the details of the DPD method are discussed. Second, the parameterization procedure and the results of the calculations are given. Finally, the values are discussed to demonstrate a qualitative structural analysis of the hydrogel. This paper targets to introduce a coarse-grained parameterization procedure that can be applied to any hydrophilic material, and to discuss the interactions of the polymer resulting in the equilibrium structure.

## MATERIALS AND METHODS

### Dissipative Particle Dynamics Simulation Method

The total force that applies to a particular bead is the addition of conservative, random, and dissipative forces. The conservative force characterizes the equilibrium structure, while the random and dissipative forces operate collectively and regulate the temperature. The non-bonded potential of DPD is given as:

$$V_{\text{DPD},ij}(r) = \begin{cases} \frac{a_{ij}}{2} \left(1 - \frac{r}{r_{\text{DPD}}}\right)^2 & r < r_{\text{DPD}} \\ 0 & r \geq r_{\text{DPD}} \end{cases} \quad (\text{Eq. 1})$$

where  $r_{\text{DPD}}$  is the cut-off value, and  $a_{ij}$  is the DPD interaction strength between beads  $i$  and  $j$  in dimensions  $k_{\text{B}}T$ .

The previously proposed alternative parameterization of DPD dictates the variable volumes of beads as a function of their pure-liquid densities by the relation: (17)

$$a_{ij} = \hat{a}_{ij} + \frac{p}{0.0454(a_{ii}\rho_{i,\text{pure}} + a_{jj}\rho_{j,\text{pure}})} \chi_{ij} k_{\text{B}}T, \quad \hat{a}_{ij} = \sqrt{a_{ii}a_{jj}}$$

$$\text{with } a_{ii} = \frac{p - \rho_{i,\text{pure}} k_{\text{B}}T}{\alpha \rho_{i,\text{pure}}^2 r_{\text{DPD}}^3} \quad (\text{Eq. 2})$$

In Eq. 2,  $a_{ii}$  and  $a_{jj}$  are like-like interactions of beads  $i$  and  $j$ ,  $\hat{a}_{ij}$  is the neutral interaction parameter, and  $\rho_i$  represents the dimensionless number densities of the pure components. The parameter  $\alpha$  is taken here as constant and equals to 0.101 for number densities higher than 3, as demonstrated by Groot and Warren's original work on DPD parameterization (23).

There is a linear relation in between  $\Delta a_{ij}$  and the experimental quantities following  $\Delta a_{ij} = C \times \chi_{ij} k_B T$ . Here,  $\chi_{ij}$  is the Flory-Huggins parameter (24) and  $\Delta a_{ij}$  quantifies the excess repulsion.  $C$  is a constant defining the slope of the linear relationship between Flory-Huggins parameter and the DPD parameter, and is equal to 0.286 for a number density of 3. The pressure  $p$  is set to represent an overall compressibility value of the mixture and taken as  $40 k_B T / r_{\text{DPD}}^3$ . Flory-Huggins  $\chi_{ij}$  parameter is related to the solubility parameters via the relation:

$$\chi_{ij} = \frac{V_m}{RT} (\delta_i - \delta_j)^2 \quad (\text{Eq. 3})$$

where  $\delta$ 's are the solubility parameters and  $V_m$  is the molecular volume of a bead. The relationship between the  $\chi_{ij}$  parameter and the excess repulsion is reported in Groot and Warren's original DPD work (23).


The implementation of hydrogen bonds to DPD method is performed by adding a Morse potential term to the non-bonded DPD potential.

$$V_{\text{Morse}} = D_0 [e^{-2\sigma(r-r_0)} - 2e^{-\sigma(r-r_0)}], \quad r < r_{\text{DPD}} \quad (\text{Eq. 4})$$

In this equation,  $D_0$  represents the strength of the attraction,  $\sigma$  quantifies the curvature, and  $r_0$  is the equilibrium distance (21). We select a value of  $2/r_{\text{DPD}}$  for  $\sigma$ . In Eq. 4, the contribution of hydrogen bonds are not counted for inter-bead distances larger than  $1 r_{\text{DPD}}$ .

### Hydrophilic polymer structure and the coarse-graining

The hydrogel consists of a combination of a trimerized hexamethylene diisocyanate (tHDI) cross-linker and a polyethylene glycol (PEG) spacer with a molecular mass of 2000 g/mol. The mixture is at the stoichiometric ratio of 2:3. As previously mentioned, the coarse-graining is performed by partitioning the chemical structure into chemically meaningful units as depicted in Figure 1. In accordance with the stoichiometry, the total number of beads in each chain are set to 1000 for tHDI and 1500 for PEG chains.



**Figure 1:** Schematic representation of the coarse-grained beads of (a) tHDI and (b) PEG.

## RESULTS AND DISCUSSION

Initially, the Flory-Huggins interaction parameters which quantify the mixing behavior of the molecules (24) are determined. These parameters are obtained from Eq. 3 by identifying the van Krevelen solubility parameters from group contribution methods (25). Here, Molecular Modeling Pro Software (26) is used. In Table 1, we report the computed  $\chi_{ij}$  parameters.

$\chi_{ij}$	<b>N</b> (24.58)	<b>C</b> (13.84)	<b>R</b> (29.56)	<b>L, H</b> (25.09)	<b>K</b> (31.86)	<b>N'</b> (22.01)	<b>W</b> (47.00)
<b>N</b>	0.00	2.84	0.61	0.01	1.30	0.16	12.36
<b>C</b>	2.84	0.00	6.08	3.12	7.99	1.64	27.04
<b>R</b>	0.61	6.08	0.00	0.49	0.13	1.40	7.48
<b>L, H</b>	0.01	3.12	0.49	0.00	1.12	0.23	11.79
<b>K</b>	1.30	7.99	0.13	1.12	0.00	2.39	5.63
<b>N'</b>	0.16	1.64	1.40	0.23	2.39	0.00	15.36
<b>W</b>	12.36	27.04	7.48	11.79	5.63	15.36	0.00

**Table 1:** Computed Flory-Huggins parameters of the coarse-grained beads. N' bead represents the reacted N bead upon cross-linking. Values in parentheses indicate the solubility parameters in dimension  $(\text{J}/\text{cm}^3)^{0.5}$ . W bead represents single water molecule.

A DPD fluid phase separates out if the value of  $\chi$  is above 2 (23). Therefore, the  $\chi$  values in Table 1 higher than 2 indicate a phase-separation. The largest difference of  $\chi$  value is in between C and K beads, whereas the smallest difference is in between N and L (or H). We named L and H beads differently, although they have the same chemical structures.

The reason is to differentiate the head group and the repeating units of PEG. The repelling interactions of C and K can be explained monitoring the internal chemical structures of C and K beads. The C bead is nothing but a butane molecule which is nonpolar in principle. On the other hand, K bead is a polar molecule that can make hydrogen bonds with particular molecules. According to the values in Table 1, the bead pair that like each other the most is the N and L pair. They are similar in size, both are polar and have high chances to form hydrogen bonds with each other.

If we examine water and polymer bead interactions, it is seen that all beads have a tendency to repel each other. The smallest  $\chi$  parameter values are observed in between K and W, and R and W beads among the others. The solubility parameters corresponding to water and polymer beads differ to a large extent. The difference of solubilities and resulting high values of  $\chi$  parameters would lead to a large separation of polymer and water beads in the simulations. The exact repulsive nature of the interactions can be analyzed and discussed in the form of self and pairwise interactions of DPD. To that purpose, Eq. 2 and Table 1 are combined to compute the corresponding  $a_{ij}$  parameters. The calculated values are given in Table 2.

$a_{ij}$	<b>N</b> (0.0113)	<b>C</b> (0.0062)	<b>R</b> (0.0038)	<b>L, H</b> (0.0103)	<b>K</b> (0.0112)	<b>N'</b> (0.0094)	<b>W</b> (0.0033)
<b>N</b>	<b>31.26</b>	65.78	96.80	34.29	36.68	38.10	89.36
<b>C</b>	65.78	<b>106.39</b>	186.28	71.82	80.58	73.54	120.79
<b>R</b>	96.80	186.28	<b>292.22</b>	105.71	96.01	117.28	47.10
<b>L, H</b>	34.29	71.82	105.71	<b>37.55</b>	38.73	41.93	81.08
<b>K</b>	36.68	80.58	96.01	38.73	<b>31.37</b>	46.46	45.89
<b>N'</b>	38.10	73.54	117.28	41.93	46.46	<b>44.96</b>	96.72
<b>W</b>	89.36	120.79	47.10	81.08	45.89	96.72	<b>2.90</b>

**Table 2:** DPD interaction parameters  $a_{ij}$  of the coarse-grained beads. N' bead represents the reacted N bead upon cross-linking. The values in parentheses represent the dimensionless number densities of beads  $\rho_i$  obtained by  $\rho_i = \rho_{i,liquid} / M_{W,i}$ . W bead represents the single water molecule.

We discuss the relative repulsions of beads by considering the difference in the values of pairwise and like-like interactions, which is critical since like-like interactions are different for each bead correlated with the bead volume. For example, the bead having the largest volume is the R bead and the one with the smallest volume is the N bead. Consequently, these beads have the highest and the lowest like-like interaction values, respectively. In line with the Flory-Huggins parameters in Table 1, the most repulsive interaction is in between C and K beads, although the numerical value of corresponding  $a_{ij}$  is smaller than most of the values in Table 2, whereas N and L bead pair has the lowest repulsion strength. This means in a simulation, that C and K will be separated, on the other hand, the L bead would like to stay even closer to N bead rather than itself due to a lower  $a_{ij}$  value than its like-like interaction value.

The like-like interaction value of water is the lowest among the polymer beads due to its smallest size. However, the pairwise interactions between the water bead and the other type of beads are larger. This indicates a preference of water to stay close to the same type of beads rather than moving near polymer beads. The highest repulsion of water is with the C bead since it is purely composed of carbon atoms. The least repulsion strength is observed in between the R and W beads. This value is even smaller than the like-like interaction of the R bead. The hydrogen bond contribution to solubilities has an influence favoring mixing. Obviously, if these values are used in a simulation, the polymer and water would be phase-separated, with the exception of hydrophilic polymers. The analysis of the DPD parameters solely identifies the importance of contribution of hydrogen bonds to the DPD method.

In this section, we use a parameterization that was recently proposed to add hydrogen bond attraction to the purely repulsive DPD potential (21). The added term will be in the form of a Morse potential. A multi-scale procedure is used to compute the Morse potential parameters which take atomistic molecular dynamics simulations as the basis. In this procedure, the hydrogen bond energy is computed for different hydrogen bonding pairs from the potential energy differences of the mixture and the pure components. The second parameter of the Morse potential, namely the equilibrium hydrogen bond distance, is computed from the radial distribution functions (RDF). The exact form of equations and procedure is given in detail in reference (21).

Upon coarse-graining of the PEG, the repeating unit is solely an ethanol molecule. In this work, we adapted the Morse potential values for the system of interest from the reference study. The repeating unit constitutes a large portion of the mixture due to the rule of stoichiometry. Therefore, the structure of polymer is dominantly characterized by the interactions of this bead. For the rest of the beads, the Morse potential parameters are computed by taking the strength of ethanol-water hydrogen bond interaction as reference and scaling its value with the number of possible hydrogen bonds. For example, the strength of hydrogen bond interaction of R and water beads is computed by multiplying ethanol-water hydrogen bond interaction strength by six, since R bead can make six hydrogen bond interactions with water. In this way, we get a reasonable approximation to the overall hydrogen bond interactions, and at the same time differentiate the hydrogen bond strengths of different materials favoring higher attraction if the number of hydrogen bonds is higher. The equilibrium hydrogen bond distance is taken as the same value for ethanol-water interaction without performing any scaling since the hydrogen bond equilibrium distance does not change significantly according to the type of material as observed in reference (21).

The polymer is in the form of a hydrogel. Therefore, if immersed in, the material can take up a significant amount of water. The hydrogen bond strength and hydrogen bond equilibrium



distance values change as a function of water content in the total mixture. The corresponding values are computed by a linear interpolation using the linear fit parameters reported previously (21). As examples, we demonstrate in Table 3, the Morse potential parameters for two mixtures with different water contents.

As shown in Table 3, the values differ following the variation in water content in the total mixtures. This is a result of the linear increase of the hydrogen bond strength with respect to the decrease in the amount of water in the mixture (21). The strongest hydrogen bond attraction with water is observed for the center bead of tHDI molecule, the R bead, whereas the weakest hydrogen bond attraction with water is formed in presence of the K bead of PEG chain. The hydrogen bond strengths tabulated in Table 3 are a function of the number of possible hydrogen bond connections and the overall molar fraction as dictated by the linear relationship reported in reference (21). The equilibrium hydrogen bond distance values also do change according to the change of the physical length-scale of DPD  $r_{\text{DPD}}$ .

Bead type	25%			75%		
	$x_i$	$D_0 [k_B T]$	$r_0 [r_{\text{DPD}}]$	$x_i$	$D_0 [k_B T]$	$r_0 [r_{\text{DPD}}]$
<b>N</b>	0.03	12.95	0.53	0.01	12.53	0.51
<b>R</b>	0.01	37.58	0.51	0.00	37.16	0.50
<b>L, H</b>	0.66	13.07	0.77	0.22	8.46	0.69
<b>K</b>	0.02	12.63	0.51	0.01	12.42	0.50
<b>N'</b>	0.03	12.95	0.53	0.01	12.53	0.51

**Table 3:** Morse potential parameters for 25% and 75% water content in the total mixture.  $x_i$  represents the molar fraction of individual beads.

## CONCLUSIONS

This paper targets to construct a DPD parameterization scheme where a hydrogel is modeled in order to perform coarse-grained simulations. The beads that constitute the hydrogel are parameterized in such a way that their volumes are set to be different and dictated by their pure-liquid volumes. Moreover, we apply a recently proposed parameterization method where a Morse potential mimics the inter-molecular attraction as a result of the hydrogen bonds. The Morse potential parameters, namely hydrogen bond strengths and equilibrium hydrogen bond distances, are computed by taking the internal chemistry into account. Besides providing the coarse-grained parameterization details, we discuss the inherent interactions that are present and make a qualitative analysis of the structure as well. The validation of the parameterization procedure is saved as a separate future work. The coarse-grained parameterization procedure of the specific polymer reported in this work can be used as a general tool that can be applied to any similar material. Nevertheless, the procedure reported herein would drag attention of the researchers not only from computational but experimental communities.

**ACKNOWLEDGMENTS**

The author would like to thank Prof. Dr. Gijsbertus de With of Eindhoven University of Technology for the discussions on the coarse-grained parameterization. This work was partially supported by the TUBITAK 2232 program (116C003) and the Dutch Polymer Institute (DPI) (780).

**REFERENCES**

1. Peppas NA, Hilt JZ, Khademhosseini A, Langer R. Hydrogels in biology and medicine: From molecular principles to bionanotechnology. *Adv Mater.* 2006;18(11):1345-60.
2. Lin CC, Metters AT. Hydrogels in controlled release formulations: Network design and mathematical modeling. *Adv Drug Deliver Rev.* 2006;58(12-13):1379-408.
3. Drelich J, Chibowski E, Meng DD, Terpilowski K. Hydrophilic and superhydrophilic surfaces and materials. *Soft Matter.* 2011;7(21):9804-28.
4. Banerjee I, Pangule RC, Kane RS. Antifouling Coatings: Recent Developments in the Design of Surfaces That Prevent Fouling by Proteins, Bacteria, and Marine Organisms. *Adv Mater.* 2011;23(6):690-718.
5. Shirafkan A, Woodward EG, Port MJA, Hull CC. Surface Wettability and Hydrophilicity of Soft Contact-Lens Materials, before and after Wear. *Ophthal Physl Opt.* 1995;15(5):529-32.
6. Yu CY, Ma L, Li K, Li SL, Liu YN, Zhou YF, et al. Molecular dynamics simulation studies of hyperbranched polyglycerols and their encapsulation behaviors of small drug molecules. *Phys Chem Chem Phys.* 2016;18(32):22446-57.
7. Yang C, Lu DN, Liu Z. How PEGylation Enhances the Stability and Potency of Insulin: A Molecular Dynamics Simulation. *Biochemistry-U.S.* 2011;50(13):2585-93.
8. Lajunen T, Kontturi LS, Viitala L, Manna M, Cramariuc O, Rog T, et al. Indocyanine Green-Loaded Liposomes for Light-Triggered Drug Release. *Mol Pharmaceut.* 2016;13(6):2095-107.
9. Lee H, de Vries AH, Marrink SJ, Pastor RW. A Coarse-Grained Model for Polyethylene Oxide and Polyethylene Glycol: Conformation and Hydrodynamics. *J Phys Chem B.* 2009;113(40):13186-94.
10. Prasitnok K, Wilson MR. A coarse-grained model for polyethylene glycol in bulk water and at a water/air interface. *Phys Chem Chem Phys.* 2013;15(40):17093-104.
11. Lee H, Pastor RW. Coarse-Grained Model for PEGylated Lipids: Effect of PEGylation on the Size and Shape of Self-Assembled Structures. *J Phys Chem B.* 2011;115(24):7830-7.
12. Lee H, Larson RG. Membrane Pore Formation Induced by Acetylated and Polyethylene Glycol-Conjugated Polyamidoamine Dendrimers. *J Phys Chem C.* 2011;115(13):5316-22.
13. Hoogerbrugge PJ, Koelman JMVA. Simulating Microscopic Hydrodynamic Phenomena with Dissipative Particle Dynamics. *Europhys Lett.* 1992;19(3):155-60.
14. Boek ES, Coveney PV, Lekkerkerker HNW, vanderSchoot P. Simulating the rheology of dense colloidal suspensions using dissipative particle dynamics. *Phys Rev E.* 1997;55(3):3124-33.
15. Kacar G, Atilgan C, Ozen AS. Mapping and Reverse-Mapping of the Morphologies for a Molecular Understanding of the Self-Assembly of Fluorinated Block Copolymers. *J Phys Chem C.* 2010;114(1):370-82.
16. Kacar G, Peters EAJF, de With G. Structure of a Thermoset Polymer near an Alumina Substrate as Studied by Dissipative Particle Dynamics. *J Phys Chem C.* 2013;117(37):19038-47.

17. Kacar G, Peters EAJF, de With G. A generalized method for parameterization of dissipative particle dynamics for variable bead volumes. *EPL*. 2013;102(4).
18. Kacar G, Peters EAJF, de With G. Mesoscopic simulations for the molecular and network structure of a thermoset polymer. *Soft Matter*. 2013;9(24):5785-93.
19. Can H, Kacar G, Atilgan C. Surfactant formation efficiency of fluorocarbon-hydrocarbon oligomers in supercritical CO<sub>2</sub>. *J Chem Phys*. 2009;131(12).
20. Zeng QH, Yu AB, Lu GQ. Multiscale modeling and simulation of polymer nanocomposites. *Prog Polym Sci*. 2008;33(2):191-269.
21. Kacar G, de With G. Hydrogen bonding in DPD: application to low molecular weight alcohol-water mixtures. *Phys Chem Chem Phys*. 2016;18(14):9554-60.
22. Vishnyakov A, Talaga DS, Neimark AV. DPD Simulation of Protein Conformations: From alpha-Helices to beta-Structures. *J Phys Chem Lett*. 2012;3(21):3081-7.
23. Groot RD, Warren PB. Dissipative particle dynamics: Bridging the gap between atomistic and mesoscopic simulation. *J Chem Phys*. 1997;107(11):4423-35.
24. Flory PJ. *Principles of Polymer Chemistry*. Ithaca, New York: Cornell University Press; 1953.
25. Krevelen DWv. *Properties of Polymers*. Amsterdam: Elsevier; 1990.
26. *Molecular Modeling Pro*. 6.3.3 ed: Norgwyn Montgomery Software Inc.; 1992.