

## Forming limit diagrams for sheet deformation processes

***Citation for published version (APA):***

Viatkina, E. M., Brekelmans, W. A. M., & Geers, M. G. D. (2001). *Forming limit diagrams for sheet deformation processes*. Poster session presented at Mate Poster Award 2001 : 6th Annual Poster Contest, .

***Document status and date:***

Published: 01/01/2001

***Document Version:***

Publisher's PDF, also known as Version of Record (includes final page, issue and volume numbers)

***Please check the document version of this publication:***

- A submitted manuscript is the version of the article upon submission and before peer-review. There can be important differences between the submitted version and the official published version of record. People interested in the research are advised to contact the author for the final version of the publication, or visit the DOI to the publisher's website.
- The final author version and the galley proof are versions of the publication after peer review.
- The final published version features the final layout of the paper including the volume, issue and page numbers.

[Link to publication](#)

***General rights***

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal.

If the publication is distributed under the terms of Article 25fa of the Dutch Copyright Act, indicated by the "Taverne" license above, please follow below link for the End User Agreement:

[www.tue.nl/taverne](http://www.tue.nl/taverne)

***Take down policy***

If you believe that this document breaches copyright please contact us at:

[openaccess@tue.nl](mailto:openaccess@tue.nl)

providing details and we will investigate your claim.

# Forming limit diagrams for sheet deformation processes

E.M. Viatkina, W.A.M. Brekelmans, M.G.D. Geers

Netherlands Institute for Metals Research, Eindhoven University of Technology, Department of Mechanical Engineering

## Introduction

Forming limit diagrams (FLD's) offer a convenient and useful tool in sheet products manufacturing analysis. They show the critical combinations of major strain and minor strain in the sheet surface at the onset of necking failure (Fig. 1).




Fig.1 An example of an FLD for uniform deformation.

Formability in the context of multiple phase operations strongly depends of the deformation history and therefore demands an investigation of every particular case. This makes the experimental determination of FLD's unappreciative expensive and causes the necessity to develop an accurate and efficient theoretical method for formability prediction.

**The aim** is to develop a numerical method to predict forming limit diagrams for FCC metal sheets.

## Method

To induce the occurrence of strain instability in uniform deformation processes initial **textural inhomogeneities** are used; no additional artificial imperfections have to be introduced. Biaxial stretching of a sheet material configuration has been simulated using the **finite element method** in plane stress conditions. For the description of the material behaviour at integration point level time-dependent **crystal plasticity** units with Taylor interaction model have been used. The limit strain was established from a maximum of power criterion.

## Results

Proportional loading of a metal sheet with **an initially random distribution** of the crystal lattice orientations has been computationally analysed for different uniform strain paths. The RVE consists of 8 by 8 elements and every integration point deals with 10 monocrystals.




Fig.2 Evolution of the second strain field invariant,  $\epsilon_2 = 0$ .




Fig.3 Calculated FLD and strain localization patterns.

## Conclusions

- The results prove the capability of the method to predict strain localization.
- The obtained forming limit diagrams agree qualitatively with experimental data.
- The localization criterion should be improved for a better agreement with experimental observation.